

\*\*\*\*\*  
USACE / NAVFAC / AFCEC / NASA UFGS-26 05 13.00 40 (May 2020)  
-----  
Preparing Activity: NASA Superseding  
UFGS-26 05 13.00 40 (November 2016)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated April 2020

\*\*\*\*\*

SECTION TABLE OF CONTENTS

DIVISION 26 - ELECTRICAL

SECTION 26 05 13.00 40

MEDIUM-VOLTAGE CABLES

05/20

PART 1 GENERAL

- 1.1 REFERENCES
- 1.2 DEFINITIONS
- 1.3 ADMINISTRATIVE REQUIREMENTS
  - 1.3.1 Pre-Installation Meetings
- 1.4 SUBMITTALS
- 1.5 QUALITY CONTROL
  - 1.5.1 Regulatory Requirements
  - 1.5.2 Standard Products
  - 1.5.3 Predictive Testing and Inspection Technology Requirements
- 1.6 DELIVERY, STORAGE, AND HANDLING

PART 2 PRODUCTS

- 2.1 SYSTEM DESCRIPTION
- 2.2 EQUIPMENT
  - 2.2.1 Multiple-Conductor Shielded Cables
    - 2.2.1.1 [Natural] [Synthetic] Rubber with Interlocked Armor
    - 2.2.1.2 Cross-Linked Polyethylene
    - 2.2.1.3 Ethylene Propylene Rubber (EPR) with Jacketed Interlocked Armor
  - 2.2.2 Multiple-Conductor, Nonshielded Cables
    - 2.2.2.1 [Natural] [Synthetic] Rubber with Neoprene Jacket
    - 2.2.2.2 Cross-Linked Polyethylene with PVC Jacket
    - 2.2.2.3 Ethylene-Propylene with PVC Jacket
  - 2.2.3 Single-Conductor Shielded Cables
    - 2.2.3.1 Cross-Linked Polyethylene with PVC Jacket
    - 2.2.3.2 Cross-Linked Polyethylene with Interlocked Armor
    - 2.2.3.3 Ethylene-Propylene-Rubber-Insulated with PVC Jacket
  - 2.2.4 Single-Conductor Nonshielded Cables
    - 2.2.4.1 Cross-Linked Polyethylene
    - 2.2.4.2 Ethylene-Propylene-Rubber-Insulated with PVC Jacket
  - 2.2.5 Portable Cables
  - 2.2.6 Insulated Medium Voltage Connectors
  - 2.2.7 Splices

- 2.2.8 Terminations
- 2.2.9 Cable Supports and Fittings
- 2.2.10 Polyethylene Cable Tags
- 2.2.11 Fireproof Tape
- 2.3 MATERIALS
  - 2.3.1 Conductors
  - 2.3.2 Insulation
  - 2.3.3 Cable Identification
  - 2.3.4 Non-metallic Insulation Shield
  - 2.3.5 Concentric Neutral Shield
  - 2.3.6 Jacket
  - 2.3.7 Interlock Armored Cable
- 2.4 TESTS, INSPECTIONS, AND VERIFICATIONS
  - 2.4.1 FACTORY TESTING

PART 3 EXECUTION

- 3.1 DEMOLITION OR CABLE CUTTING
- 3.2 INSTALLATION
  - 3.2.1 Protection During Splicing Operations
  - 3.2.2 Duct Cleaning
  - 3.2.3 Pulling Cables in Ducts, Manholes and Utility Tunnels
    - 3.2.3.1 Allowable Sidewall Pressure
    - 3.2.3.2 Minimum Bending Radius
    - 3.2.3.3 Coating of Cables
    - 3.2.3.4 Pulling Speed
    - 3.2.3.5 Cable Splice Support And Sealing
  - 3.2.4 Splices and Terminations
  - 3.2.5 Fireproofing
  - 3.2.6 Cable Tag Installation
- 3.3 FIELD QUALITY CONTROL
- 3.4 CLOSEOUT ACTIVITIES

-- End of Section Table of Contents --

\*\*\*\*\*  
USACE / NAVFAC / AFCEC / NASA UFGS-26 05 13.00 40 (May 2020)  
-----  
Preparing Activity: NASA Superseding  
UFGS-26 05 13.00 40 (November 2016)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated April 2020

\*\*\*\*\*

SECTION 26 05 13.00 40

MEDIUM-VOLTAGE CABLES  
05/20

\*\*\*\*\*

NOTE: This guide specification covers the requirements for medium-voltage cables, including shielded and nonshielded single- and multiple-conductor power cables, portable cables, cable splices and terminations, single- and multiple-conductor potheads, and fireproofing cables in manholes and utility tunnels.

Show plan layout of power cable and power-cable terminations on drawings. Show the size, type, electrical characteristics, and raceway system of power cables and type of cable termination on electrical riser diagrams.

Adhere to [UFC 1-300-02](#) Unified Facilities Guide Specifications (UFGS) Format Standard when editing this guide specification or preparing new project specification sections. Edit this guide specification for project specific requirements by adding, deleting, or revising text. For bracketed items, choose applicable item(s) or insert appropriate information.

Remove information and requirements not required in respective project, whether or not brackets are present.

Comments, suggestions and recommended changes for this guide specification are welcome and should be submitted as a [Criteria Change Request \(CCR\)](#).

\*\*\*\*\*

PART 1 GENERAL

[Section 33 71 01.00 40 OVERHEAD TRANSMISSION AND DISTRIBUTION] [33 71 02 UNDERGROUND ELECTRICAL DISTRIBUTION] applies to work specified in this section.

1.1 REFERENCES

\*\*\*\*\*

NOTE: This paragraph is used to list the publications cited in the text of the guide specification. The publications are referred to in the text by basic designation only and listed in this paragraph by organization, designation, date, and title.

Use the Reference Wizard's Check Reference feature when you add a Reference Identifier (RID) outside of the Section's Reference Article to automatically place the reference in the Reference Article. Also use the Reference Wizard's Check Reference feature to update the issue dates.

References not used in the text are automatically deleted from this section of the project specification when you choose to reconcile references in the publish print process.

\*\*\*\*\*

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

ASSOCIATION OF EDISON ILLUMINATING COMPANIES (AEIC)

AEIC CS1 (2012) Impregnated-Paper-Insulated, Metallic Sheathed Cable, Solid Type

AEIC CS8 (2013) Specification for Extruded Dielectric Shielded Power Cables Rated 5 Through 46 kV

ASTM INTERNATIONAL (ASTM)

ASTM B3 (2013) Standard Specification for Soft or Annealed Copper Wire

ASTM B8 (2011; R 2017) Standard Specification for Concentric-Lay-Stranded Copper Conductors, Hard, Medium-Hard, or Soft

ASTM D746 (2014) Standard Test Method for Brittleness Temperature of Plastics and Elastomers by Impact

INSTITUTE OF ELECTRICAL AND ELECTRONICS ENGINEERS (IEEE)

IEEE 48 (2009) Standard for Test Procedures and Requirements for Alternating-Current Cable Terminations Used on Shielded Cables Having Laminated Insulation Rated 2.5 kV through 765 kV or Extruded Insulation Rated 2.5 kV through 500 kV

IEEE 383 (2015) Qualifying Class 1E Electric Cables and, Field Splices for Nuclear Power Generating Stations 2004

IEEE 386 (2016) Separable Insulated Connector Systems for Power Distribution Systems Rated 2.5 kV through 35 kV

IEEE 400.2 (2013) Guide for Field Testing of Shielded Power Cable Systems Using Very Low Frequency (VLF)

IEEE 404 (2012) Standard for Extruded and Laminated Dielectric Shielded Cable Joints Rated 2500 V to 500,000 V

IEEE 1202 (2006; R 2012; CORR 1 2012) Flame-Propagation Testing of Wire and Cable

IEEE C2 (2017; Errata 1-2 2017; INT 1 2017) National Electrical Safety Code

INTERNATIONAL ELECTRICAL TESTING ASSOCIATION (NETA)

NETA ATS (2017; Errata 2017) Standard for Acceptance Testing Specifications for Electrical Power Equipment and Systems

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION (NASA)

RCBEA GUIDE (2004) NASA Reliability Centered Building and Equipment Acceptance Guide

NATIONAL ELECTRICAL MANUFACTURERS ASSOCIATION (NEMA)

ANSI C119.1 (2016) Electric Connectors - Sealed Insulated Underground Connector Systems Rated 600 Volts

ANSI/NEMA WC 71/ICEA S-96-659 (2014) Standard for Nonshielded Cables Rated 2001-5000 Volts for use in the Distribution of Electric Energy

NEMA WC 70 (2009) Power Cable Rated 2000 V or Less for the Distribution of Electrical Energy--S95-658

NEMA WC 74/ICEA S-93-639 (2012) 5-46 kV Shielded Power Cable for Use in the Transmission and Distribution of Electric Energy

NEMA WC 27500 (2015) Standard for Aerospace and Industrial Electrical Cable

NATIONAL FIRE PROTECTION ASSOCIATION (NFPA)

NFPA 70 (2020; ERTA 20-1 2020; ERTA 20-2 2020; TIA 20-1; TIA 20-2; TIA 20-3; TIA 20-4) National Electrical Code

NFPA 70B (2019) Recommended Practice for Electrical Equipment Maintenance

NFPA 70E

(2018; TIA 18-1; TIA 81-2) Standard for Electrical Safety in the Workplace

U.S. GENERAL SERVICES ADMINISTRATION (GSA)

FED-STD-228

(2014; Rev A; Notice 1) Test Methods for Cable and Wire, Insulated

1.2 DEFINITIONS

Medium-voltage power cables include all cables rated above 600 volts up to 35,000 volts.

1.3 ADMINISTRATIVE REQUIREMENTS

1.3.1 Pre-Installation Meetings

No later than [30][ ] days of Contract Award, coordinate with the Contracting Officer to schedule a pre-installation meeting. Submit the following for review and approval prior to the meeting:

- a. Pulling Plan including calculations of pulling tension and side wall pressure anticipated, and the maximum allowable pulling tension for each pull. Do not perform any pull until Government reviews and approves the pulling plan.
- b. Splicer/Terminator Certifications
- c. [List of Splices and Terminations to be Installed by Splicer/Terminator](#)
- d. Manufacturer's catalog data for all cables, cable supports and fittings, cable tags, fireproof tape, splice kits, terminations, and any other product data required to complete the work.
- e. Certificates showing that the cable manufacturer has made factory-conducted tests on each shipping length (reel) of cable. Include certified copies of test data showing conformance with the referenced standards and approval prior to delivery of cable.

1.4 SUBMITTALS

\*\*\*\*\*

**NOTE: Review Submittal Description (SD) definitions in Section 01 33 00 SUBMITTAL PROCEDURES and edit the following list to reflect only the submittals required for the project.**

The Guide Specification technical editors have designated those items that require Government approval, due to their complexity or criticality, with a "G." Generally, other submittal items can be reviewed by the Contractor's Quality Control System. Only add a "G" to an item, if the submittal is sufficiently important or complex in context of the project.

For submittals requiring Government approval on Army projects, use a code of up to three characters within the submittal tags following the "G"

designation to indicate the approving authority. Codes for Army projects using the Resident Management System (RMS) are: "AE" for Architect-Engineer; "DO" for District Office (Engineering Division or other organization in the District Office); "AO" for Area Office; "RO" for Resident Office; and "PO" for Project Office. Codes following the "G" typically are not used for Navy, Air Force, and NASA projects.

An "S" following a submittal item indicates that the submittal is required for the Sustainability eNotebook to fulfill federally mandated sustainable requirements in accordance with Section 01 33 29 SUSTAINABILITY REPORTING. Locate the "S" submittal under the SD number that best describes the submittal item.

Choose the first bracketed item for Navy, Air Force and NASA projects, or choose the second bracketed item for Army projects.

\*\*\*\*\*

Government approval is required for submittals with a "G" designation; submittals not having a "G" designation are [for Contractor Quality Control approval.][for information only. When used, a designation following the "G" designation identifies the office that reviews the submittal for the Government.] Submittals with an "S" are for inclusion in the Sustainability eNotebook, in conformance to Section 01 33 29 SUSTAINABILITY REPORTING. Submit the following in accordance with Section 01 33 00 SUBMITTAL PROCEDURES:

SD-01 Preconstruction Submittals

List of Splices and Terminations to be Installed by Splicer/Terminator; G[, [\_\_\_\_]]

SD-02 Shop Drawings

Pulling Plan; G[, [\_\_\_\_]]

SD-03 Product Data

Multiple-Conductor Shielded Cables; G[, [\_\_\_\_]]

Multiple-Conductor Nonshielded Cables; G[, [\_\_\_\_]]

Single-Conductor Shielded Cables; G[, [\_\_\_\_]]

Single-Conductor Nonshielded Cables; G[, [\_\_\_\_]]

Portable Cables; G[, [\_\_\_\_]]

Cable Supports and Fittings; G[, [\_\_\_\_]]

Polyethylene Cable Tags; G[, [\_\_\_\_]]

Fireproof Tape; G[, [\_\_\_\_]]

Splices; G[, [\_\_\_\_]]

Terminations; G[, [\_\_\_\_]]

Polyethylene Cable Tags; G[, [\_\_\_\_]]

#### SD-06 Test Reports

Field Testing; G[, [\_\_\_\_]]

Qualification Test Reports; G[, [\_\_\_\_]]

Radiographic Tests; G[, [\_\_\_\_]]

#### SD-07 Certificates

Splicer/Terminator Certifications; G[, [\_\_\_\_]]

#### SD-08 Manufacturer's Instructions

Medium-Voltage Power Cables; G[, [\_\_\_\_]]

Terminations; G[, [\_\_\_\_]]

Splices; G[, [\_\_\_\_]]

### 1.5 QUALITY CONTROL

#### 1.5.1 Regulatory Requirements

In each of the publications referred to herein, consider the advisory provisions to be mandatory, as though the word, "shall" had been substituted for "should" wherever it appears. Interpret references in these publications to the "authority having jurisdiction," or words of similar meaning, to mean the Contracting Officer. Ensure equipment, materials, installation, and workmanship are in accordance with the mandatory and advisory provisions of **NFPA 70**, **IEEE C2** unless more stringent requirements are specified or indicated.

#### 1.5.2 Standard Products

Provide materials and equipment that are products of manufacturers regularly engaged in the production of such products which are of equal material, design and workmanship. Provide products which have been in satisfactory commercial or industrial use for 2 years prior to bid opening. Ensure the 2-year period includes applications of equipment and materials under similar circumstances and of similar size. Ensure the product has been on sale on the commercial market through advertisements, manufacturers' catalogs, or brochures during the 2-year period. Where two or more items of the same class of equipment are required, these items must be products of a single manufacturer.

#### Qualifications`

Verify personnel performing Medium Voltage (MV) splicing or terminations have [5][ ] years minimum experience in cable splicing and terminations of the type used in this project. Submit **splicer/terminator certifications** issued by the cable splice and termination manufacturer who has examined and tested a test splice or termination of each type required



by this contract for each cable splicer. Ensure the certification identifies which splices and terminations it applies to.[ Require each individual, certified or not, with the required medium voltage splicing and terminating experience, who is to perform cable splicing or terminating, to perform a minimum of one splice or termination of each type in the presence of the manufacturer's[ and Government's] representative. Supply all materials and tools required for the demonstration splices and terminations.][ Submit each splice or termination performed by individuals without manufacturer's certification to the manufacturer for testing and subsequent certification.][ Certification is not required for load break elbows and dead break connectors.]

Once a splice or termination has been started by a splicer, ensure the same splicer completes that particular splice, and that each termination and splice is started and completed in one continuous work period.

Maintain and submit a list of splices and terminations to be installed by splicer/terminator. Ensure the list includes the following for each splice or termination completed.

- a. Name of splicer/terminator.
- b. Date splice or termination was performed.
- c. Location of splice or termination. For terminations at equipment indicate equipment number as required to completely define the location.[
- d. Feeder number.]

### 1.5.3 Predictive Testing and Inspection Technology Requirements

\*\*\*\*\*  
**NOTE: The Predictive Testing and Inspection (PT&I) tests prescribed in Section 01 86 26.07 40 RELIABILITY CENTERED ACCEPTANCE FOR ELECTRICAL SYSTEMS are MANDATORY for all [NASA] [\_\_\_\_\_] assets and systems identified as Critical, Configured, or Mission-Essential. If the system is non-critical, non-configured, and not mission-essential, use sound engineering discretion to assess the value of adding these test and acceptance requirements. See Section 01 86 26.07 40 RELIABILITY CENTERED ACCEPTANCE FOR ELECTRICAL SYSTEMS for additional information regarding cost feasibility of PT&I.**  
\*\*\*\*\*

This section contains systems and equipment components regulated by NASA's Reliability Centered Building and Equipment Acceptance Program. This program requires the use of Predictive Testing and Inspection (PT&I) technologies in conformance with **RCBEA GUIDE** to ensure that building equipment and systems have been installed properly and contain no identifiable defects that shorten the design life of a system and its components. Satisfactory completion of all acceptance requirements is required to obtain Government approval and acceptance of the Contractor's work.

Perform PT&I and provide submittals as specified in Section 01 86 26.07 40

RELIABILITY CENTERED ACCEPTANCE FOR ELECTRICAL SYSTEMS.

1.6 DELIVERY, STORAGE, AND HANDLING

Ship cables on reels in a way that protects the cable from mechanical injury. Hermetically seal end of each cable length using heat-shrinkable molded cable end caps to exclude moisture and securely attached to the reel..

Make the minimum reel drum diameter [14] [\_\_\_\_\_] times the overall diameter of the cable. Ensure that each cable length is installed with a pulling eye installed by the manufacturer, for installation in ducts, manholes, and utility tunnels.

PART 2 PRODUCTS

2.1 SYSTEM DESCRIPTION

Provide medium-voltage power cables including multiple- and single-conductor cables rated [5,000][15,000][ ] volts, ungrounded neutral, on [2,400/4,160][13,200/13,800][12,470][ ]-volt three-phase, 60-hertz, phase-to-phase, for grounded and ungrounded neutral systems.

Provide conductor cable assemblies consisting of:

- a. Conductor core with an extruded semiconductor shield over the conductors
- b. Insulation
- c. A polyethylene (PE) jacket.[
- d. An extruded semiconductor insulation shield, a concentric neutral]

2.2 EQUIPMENT

Ensure that ethylene-propylene rubber and cross-linked polyethylene-insulated conductors are lead-free.

2.2.1 Multiple-Conductor Shielded Cables

\*\*\*\*\*

**NOTE: Ethylene propylene or cross-linked polyethylene-insulated cables are considered higher quality; however, cross-linked polyethylene insulation has been shown to tree (which breaks down the insulation at the microscopic level, lowering the insulation strength - see AEIC C8) when installed in wet environments. Use of ethylene propylene or anti-treeing cross-link is highly recommended.**

**When the required cables are not listed below, specify cables conforming to the following publications, and, when necessary, adding to or modifying the requirements of the referenced publications:**

**Rubber-insulated - NEMA WC 70, ANSI/NEMA WC 71/ICEA**

S-96-659, NEMA WC 74/ICEA S-93-639, IEEE Std 532

Varnished cloth-insulated - NEMA WC 27500

Thermoplastic-insulated - IEEE Std 532

Cross-linked polyethylene-insulated - NEMA WC 70,  
ANSI/NEMA WC 71/ICEA S-96-659, NEMA WC 74/ICEA  
S-93-639, AEIC C8, IEEE Std 532

Ethylene propylene rubber-insulated - NEMA WC 70,  
ANSI/NEMA WC 71/ICEA S-96-659, NEMA WC 74/ICEA  
S-93-639, AEIC C8, IEEE Std 532

\*\*\*\*\*

2.2.1.1 [Natural] [Synthetic] Rubber with Interlocked Armor

\*\*\*\*\*

NOTE: Specify multiple-conductor, natural- or  
synthetic-rubber-insulated,  
interlocked-armor-covered, shielded cable for  
6,900-volt and 13,200/13,800-volt phase-to-phase  
circuits.

\*\*\*\*\*

Provide multiple-conductor, [natural] [synthetic]-rubber-insulated,  
interlocked-armor-covered, shielded cable that conforms to NEMA WC 70,  
ANSI/NEMA WC 71/ICEA S-96-659 and NEMA WC 74/ICEA S-93-639.

\*\*\*\*\*

NOTE: Change interlocked-armor tape from galvanized  
steel to aluminum if necessary to suit the project  
requirements.

\*\*\*\*\*

Apply close-fitting, interlocked-armor tape of galvanized steel over the  
jacket.

2.2.1.2 Cross-Linked Polyethylene

\*\*\*\*\*

NOTE: Specify multiple-conductor,  
polyethylene-insulated, polyvinylchloride-jacketed,  
shielded cable for 6,900-volt phase-to-phase  
circuits and 13,200/13,800-volt phase-to-phase  
circuits.

\*\*\*\*\*

Provide multiple-conductor, cross-linked polyethylene-insulated, shielded  
cable that conforms to NEMA WC 70, ANSI/NEMA WC 71/ICEA S-96-659,  
NEMA WC 74/ICEA S-93-639 and AEIC CS8. Provide taped shielding that  
consists of 0.13 millimeter 5-mil thick copper shielding lap applied over  
0.30 millimeter 12-mil thick semiconducting tape. Wrap both helically  
with [10] [\_\_\_\_]-percent overlap, providing 100-percent coverage.

[ Shield cross-linked polyethylene (XLP) single- and multiple-conductor  
cables for grounded and ungrounded neutral voltage ratings of 2,000 volts  
or more.

12.2.1.3 Ethylene Propylene Rubber (EPR) with Jacketed Interlocked Armor

Provide multiple-conductor ethylene propylene rubber insulated interlocked armor covered shielded cables that conforms to NEMA WC 70, ANSI/NEMA WC 71/ICEA S-96-659, NEMA WC 74/ICEA S-93-639 and AEIC CS8.

[ Shield ethylene propylene (EP) or ethylene propylene rubber (EPR), single- and multiple-conductor cables for grounded or ungrounded neutral voltage ratings of more than 8,000 volts.

12.2.2 Multiple-Conductor, Nonshielded Cables

2.2.2.1 [Natural] [Synthetic] Rubber with Neoprene Jacket

\*\*\*\*\*  
NOTE: Specify multiple-conductor, natural- or synthetic-rubber-insulated, neoprene-jacketed, nonshielded cable for 2,400-volt phase-to-phase, ungrounded/grounded neutral circuits.  
\*\*\*\*\*

Provide multiple-conductor, [natural] [synthetic]-rubber-insulated, neoprene-jacketed, nonshielded cable that conforms to NEMA WC 70, ANSI/NEMA WC 71/ICEA S-96-659 and NEMA WC 74/ICEA S-93-639.

2.2.2.2 Cross-Linked Polyethylene with PVC Jacket

\*\*\*\*\*  
NOTE: Specify multiple-conductor, polyethylene-insulated, PVC-jacketed, nonshielded cable for 2,400-volt phase-to-ground circuits.  
\*\*\*\*\*

Provide multiple-conductor, polyethylene-insulated, nonshielded cable that conforms to NEMA WC 70, ANSI/NEMA WC 71/ICEA S-96-659, NEMA WC 74/ICEA S-93-639 and AEIC CS8.

2.2.2.3 Ethylene-Propylene with PVC Jacket

\*\*\*\*\*  
NOTE: Specify multiple-conductor, ethylene-propylene-insulated, PVC-jacketed, nonshielded cable for 2,400-volt phase-to-ground circuits.  
\*\*\*\*\*

Provide multiple-conductor, ethylene-propylene-insulated, PVC-jacketed, nonshielded cable that conforms to NEMA WC 70, ANSI/NEMA WC 71/ICEA S-96-659, NEMA WC 74/ICEA S-93-639 and AEIC CS8.

2.2.3 Single-Conductor Shielded Cables

2.2.3.1 Cross-Linked Polyethylene with PVC Jacket

\*\*\*\*\*  
NOTE: Specify single-conductor, polyethylene-insulated, PVC-jacketed, shielded cable for 6,900- and 13,200/13,800-volt phase-to-phase circuits.  
\*\*\*\*\*

\*\*\*\*\*

Provide single-conductor, polyethylene-insulated, PVC-jacketed, shielded cable that conforms to NEMA WC 70, ANSI/NEMA WC 71/ICEA S-96-659, NEMA WC 74/ICEA S-93-639 and AEIC CS8.

2.2.3.2 Cross-Linked Polyethylene with Interlocked Armor

\*\*\*\*\*

NOTE: Specify single-conductor, polyethylene-insulated, PVC-jacketed, shielded cable with interlocked armor for 6,900- and 13,200/13,800-volt phase-to-phase circuits.

\*\*\*\*\*

Provide single-conductor, polyethylene-insulated, PVC-jacketed, shielded cable with interlocked armor that conforms to NEMA WC 70, ANSI/NEMA WC 71/ICEA S-96-659, NEMA WC 74/ICEA S-93-639 and AEIC CS8.

Apply a close-fitting, interlocked-armor tape of [galvanized steel] [aluminum] over the jacket.

2.2.3.3 Ethylene-Propylene-Rubber-Insulated with PVC Jacket

\*\*\*\*\*

NOTE: Specify single-conductor, ethylene-propylene-rubber-insulated, PVC-jacketed, shielded cable for 6,900- and 13,200/13,800 and 12,470-volt phase-to-phase circuits.

\*\*\*\*\*

Provide single-conductor 15 kV rated cable assemblies that consist of the following: Class B stranded copper conductors, an extruded semiconducting shield over the conductors, 5.6 millimeter 220 mils of ethylene propylene rubber insulation, an extruded or other approved semiconducting shield, a 0.130 millimeter 5-mil minimum copper tape shield wrapped helically with a minimum [12.5] [\_\_\_\_\_] percent overlap and a PVC jacket.

Provide single-conductor, ethylene-propylene-insulated, PVC-jacketed, shielded cable that conforms to NEMA WC 70, ANSI/NEMA WC 71/ICEA S-96-659, NEMA WC 74/ICEA S-93-639 and AEIC CS8.

2.2.4 Single-Conductor Nonshielded Cables

2.2.4.1 Cross-Linked Polyethylene

\*\*\*\*\*

NOTE: Specify single-conductor, cross-linked polyethylene-insulated, nonshielded cable for 2,400-volt phase-to-ground circuits (5,000-volt cable or less).

\*\*\*\*\*

Provide single-conductor, cross-linked polyethylene-insulated, nonshielded cable that conforms to NEMA WC 70, ANSI/NEMA WC 71/ICEA S-96-659, and NEMA WC 74/ICEA S-93-639.

#### 2.2.4.2 Ethylene-Propylene-Rubber-Insulated with PVC Jacket

\*\*\*\*\*  
**NOTE: Specify single-conductor, ethylene-propylene-rubber-insulated, PVC-jacketed, nonshielded cable for 2,400-volt phase-to-ground circuits (5,000-volt cable or less).**  
\*\*\*\*\*

Provide single-conductor, ethylene-propylene-rubber-insulated, PVC-jacketed, nonshielded cable that conforms to [NEMA WC 70](#), [ANSI/NEMA WC 71/ICEA S-96-659](#), and [NEMA WC 74/ICEA S-93-639](#).

#### 2.2.5 Portable Cables

\*\*\*\*\*  
**NOTE: Specify multiple-conductor, butyl-rubber-insulated, neoprene-jacketed, shielded portable cable for 2,400-volt phase-to-phase circuits, 6,900-volt phase-to-phase ungrounded neutral circuits, and 13,200/13,800-volt phase-to-phase circuits.**  
\*\*\*\*\*

Provide SHD multiple-conductor, butyl-rubber-insulated, neoprene-jacketed, shielded portable cable conforming to [NEMA WC 70](#), [ANSI/NEMA WC 71/ICEA S-96-659](#) and [NEMA WC 74/ICEA S-93-639](#).

#### [2.2.6 Insulated Medium Voltage Connectors

Provide connector with a steel reinforced hook-stick eye, grounding eye, test point, and arc-quenching contact material per [IEEE 386](#). Ensure connections are compatible with equipment bushings. Provide connectors as follows:

- a. 200 Ampere loadbreak connector ratings: Voltage: 15kV, 95kV BIL. Short time rating: 10,000 amperes rms, symmetrical for a time duration of 0.17 seconds.
- b. 600 Ampere deadbreak connector ratings: Voltage: 15kV, 95kV BIL. Short time rating: 27,000 ampere rms, symmetrical for a time duration of 4.0 seconds.
- c. Provide connectors with a steel reinforced hook-stick eye, grounding eye, test point, and arc-quenching contact material per [IEEE 386](#). [Provide hot line voltage indicators on all connectors.]

Ensure connections are compatible with equipment bushings.

#### ]2.2.7 Splices

Provide [heat][cold] shrink splice kits which are the product of a single manufacturer. Ensure the power cable splice meets the requirements of [IEEE 404](#) for a [5][15][ ] kV rating, and must be rated by the manufacturer for use on [5][15][ ] kV class cable systems. Ensure splices are rated for continuous operation at [105 degrees C](#) [221 degrees F](#), with an emergency overload temperature rating of [140 degrees C](#) [284 degrees F](#). Ensure the kit is capable of splicing cables with copper[ or aluminum] conductors sized as indicated in the contract drawings or accommodate a

conductor size transition Provide splices specifically designed for the cable and grounding provisions.

[ Provide heat shrink splices which include but are not limited to the following:

- a. Inner heat shrink stress control tube with external end sealant, additional heat shrink tube over inner tube and inner tube end sealant.
- b. Heat shrink outer wraparound sleeve with heat sensitive indications on both the tube and rail/channel area to indicate proper torch heating, stress relief material, mastic, sealant, shielding mesh, and silicone grease.

][Provide splices of a cold shrink design which does not require any additional heat source for installation. The cold shrink splice body must be of a molded design made of silicone rubber with splice jacketing made of EPDM rubber.]

#### 2.2.8 Terminations

Provide Class 1 terminations per IEEE 48.

\*\*\*\*\*  
**NOTE: Coordinate the following paragraph with  
Section 33 71 02 UNDERGROUND ELECTRICAL DISTRIBUTION  
if Section 33 71 02 is used in this project.**  
\*\*\*\*\*

#### 2.2.9 Cable Supports and Fittings

[ Provide cable supports, related fittings, and accessories for use in corrosive underground locations, such as manholes and utility tunnels, with a factory-applied coating of PVC of at least [0.51] [\_\_\_\_\_] millimeter [20] [\_\_\_\_\_] mils thick. Provide PVC coated items that have a uniform thickness and are free of blisters, breaks, and holidays. Provide PVC compound that conforms to ASTM D746.

][Provide cable racks, cable tray supports and related fittings that are UL-listed [standard] [heavy]-duty nonmetallic [glass-reinforced nylon] [polycarbonate].

#### ][2.2.10 Polyethylene Cable Tags

Provide tags of polyethylene that have an average tensile strength of 31 MPa 4500 pounds per square inch, and are 0.9 millimeter 0.035-inch thick, non-corrosive non-conductive. Ensure tags are resistive to acids, alkalis, organic solvents, salt water, and are distortion resistant to 150 degrees C 300 degrees F. Provide a one-piece nylon, self-locking tie at each end of the cable tag. Ensure ties have a minimum loop tensile strength of 780 newtons 175 pounds. Provide cable tags with block letters, numbers, and symbols 25 millimeter 1 inch high on a yellow background. Ensure letters, numbers, and symbols do not fall off or change positions regardless of the cable tags orientation.

#### ]2.2.11 Fireproof Tape

Provide fireproof tape approximately 0.8 millimeter 30 mils thick by 76 millimeters 3 inches wide, consisting of a flexible, unsupported elastomer

that expands in fire to provide a thick char buildup between the flame and the cable. Ensure the tape does not give off a smoke when subjected to flames or support combustion. Also, ensure tape does not deteriorate when subjected to oil, water, gases, salt water, sewage and fungus.

### 2.3 MATERIALS

\*\*\*\*\*

NOTE: If aluminum is to be specified for any of the wire purchased, revise the paragraphs accordingly.

Conductors for wire and cable may be aluminum or copper. Aluminum conductors may be considered for use in accordance with NFPA 70, Article 310.106. When used, aluminum conductor material must be AA-8000 series electrical grade aluminum alloy. The designer must consider several factors when deciding to use aluminum instead of copper including comparisons of electrical properties, mechanical properties, environmental properties specific to the intended installation, reliability, and cost. Specifications for wire and cable may be written to permit either aluminum or copper conductors where aluminum is suitable for the application, suitably reliable, and is determined to be more economical than copper.

Aluminum conductors should be permitted only where cost comparisons show an overall savings and after a careful evaluation of the corrosion problems associated with their use. They should only be allowed where installers are qualified to make reliable connections with them. Proper wire and cable connectors must be suitably rated for installation with the conductor material to which they are applied. Wire and cable connectors used with aluminum conductors must be suitably rated, termination must be prepared correctly, and an antioxidant must be applied when the connector is installed. Costs should be compared to between all pertinent items such as installation, conduit, tray, tunnel and duct banks, lifetime costs of energy losses if significant, and differences in ventilation needs if losses are evaluated. Conductors should have the required current-carrying capacities, the required short circuit capacities, and should be satisfactory with respect to voltage drop. Aluminum conductors should be sized to have equal or less resistance than the alternate copper conductors unless the total cost comparison, including losses, shows a net advantage otherwise. In such cases where the engineering costs to properly compare the use of the two materials will exceed any possible savings to be achieved by aluminum, the arbitrary choice of copper may be the best policy.

\*\*\*\*\*



2.3.1 Conductors

Ensure that conductors conform to the applicable requirements of NEMA WC 70, ANSI/NEMA WC 71/ICEA S-96-659, or NEMA WC 74/ICEA S-93-639.

[Ensure that conductors are [solid][annealed] copper core conforming to ASTM B3 and ASTM B8 and that they are bare, or tin-alloy-coated, according to the type of insulation used.][Ensure that aluminum conductors are Type AA-8000 aluminum conductors. Do not use Type 1350 aluminum conductors.] Do not intermix copper and aluminum conductors in the same raceway.

Provide Class B stranded conductors.

2.3.2 Insulation

Ensure the provided cables are rated for minimum[ 90 degrees C 194 degrees F][ 105 degrees C 221 degrees F] continuous conductor temperature and 130 degrees C 266 degrees F emergency overload.

\*\*\*\*\*  
**NOTE: Cable insulation is designed to withstand the voltage stresses a cable will experience over its expected lifetime. An insulation level defines various insulation thicknesses within a single voltage rating. The two most common levels are 100 percent and 133 percent. Normally, 100 percent insulation level is used on a grounded system and the 133 percent level is normally used on an "ungrounded" system. A 173 percent insulation level also exists and is normally used on an ungrounded system where further fault clearing time is needed.**  
 \*\*\*\*\*

Provide cables with [100][133][173] percent insulation. Ensure insulation thickness is in accordance with the following:

Voltage Rating (kV)	Insulation Level (%)	Typical Insulation Thickness	
		mm	mils
5	100	2.29	90
	137	2.92	115
	173	3.56	140
8	100	2.92	115
	133	3.56	140
	173	4.45	175

Voltage Rating (kV)	Insulation Level (%)	Typical Insulation Thickness	
		mm	mils
15	100	4.45	175
	133	5.59	220
	173	6.6	260
25	100	6.6	260
	133	8.13	320
	173	10.67	420
35	100	8.76	345
	133	10.67	420
	173	14.73	580

### 2.3.3 Cable Identification

Provide cables with printing on the outer jacket showing the cable type, name of the manufacturer, the year in which the cable was manufactured, sequential cable reel length markings and a unique number for identification purposes. Closely group the information on the tape at 1.8 meters 6 foot maximum intervals to permit complete identification.

### 2.3.4 Non-metallic Insulation Shield

Provide extruded insulation shield made of an extruded thermoset material compatible with the insulation and jacket. Ensure insulation shield is applied directly over and bonded to the insulation, and complies with AEIC CS8.

### [2.3.5 Concentric Neutral Shield

Provide [copper][aluminum] wires helically applied over the insulation shield, where the minimum total cross sectional area (of the shield wires) is [1/3 of the core][full core] conductor for the cable. Minimum size of an individual shield wire is 1.6 millimeter No. 14 AWG.

### ]2.3.6 Jacket

Provide [polyvinyl-chloride (PVC)][polyethylene (PE)] jacketed cable extruded over the cable to a minimum thickness of 2 millimeter 80 mils.

### 2.3.7 Interlock Armored Cable

Provide a nonmetallic, corrosion-resistant jacket over interlock-armored cable that is [[thermoplastic black] [colored] [PVC]] [black polyethylene] conforming to [NEMA WC 27500] [NEMA WC 70, ANSI/NEMA WC 71/ICEA S-96-659 and NEMA WC 74/ICEA S-93-639].

## 2.4 TESTS, INSPECTIONS, AND VERIFICATIONS

### 2.4.1 FACTORY TESTING

Submit certified evidence that the cable manufacturer has made factory-conducted tests on each shipping length (reel) of cable. Submit certified copies of test data in accordance with applicable provisions of the referenced standard. Include in tests on each length of cable to include:

- (1) Conductor Resistance
- (2) Accelerated Water Absorption Test
- (3) Water Immersion Test
- (4) Ionization
- (5) High-Voltage
- (6) Partial Discharge Test[

Contracting Officer or designee has the option of witnessing required factory testing at no additional cost. Provide a schedule of manufacturing and testing in advance to permit such witnessing, if requested.]

Submit certified [qualification test reports](#) in accordance with [AEIC CS8](#) made in accordance with the applicable referenced standards. Ensure certified copies of test data show conformance to the requirements of referenced standards and submit for approval prior to shipment of the cable.

Prior to manufacturing, provide data regarding degradation of proposed insulating material and cable performance due to water immersion test as specified in this specification to the Contracting Officer or designee. Indicate in information AC breakdown stress in kV/mm or V/mil versus immersion time. Ensure a complete description and condition under which cable was tested accompanies the test information. Submit an accelerated water absorption test.[]

For cables not to be enclosed in metallic conduit, test for flammability in accordance with [[FED-STD-228](#), Method 5221 [vertical], [spark]][[IEEE 383](#) and [IEEE 1202](#), 20000 watt 70,000 Btu per hour per hour vertical tray flame test].]

## PART 3 EXECUTION

### [3.1 DEMOLITION OR CABLE CUTTING

Notify the Contracting Officer 14 working days prior to an outage for demolition or cable cutting of medium voltage electrical system.

The Government has established a mandatory inspection point prior to Contractor performing any medium voltage cable cuts or demolition. Notify the Contracting Officer 48 hours in advance of this mandatory inspection point.

As part of the mandatory inspection point, positively identify and label

the medium voltage cable to be worked utilizing an electronic cable identifier. Ensure the process of identifying and labeling the cable to be worked is witnessed by the Government. Cable cutting and demolition of any medium voltage cable can occur only after approval by the Contracting Officer.

Cut medium voltage cables and conductors by indirect means using cable cutters specifically designed to be operated remotely only. Cutting of medium voltage cables and conductors by direct means is not permitted.

### ]3.2 INSTALLATION

Install medium-voltage cables in accordance with NFPA 70, NFPA 70E; and IEEE C2.

[ Refer to contract provisions for safety submittals and requirements associated with working in the vicinity of energized cables and equipment. The use of arc-flash and shock prevention equipment and personal protective equipment is mandatory.

] Notify the Contracting Officer 14 working days prior to an outage that requires testing for phasing and phase rotation of medium voltage electrical systems. The [Government][\_\_\_\_\_] will identify and tag the phasing of equipment and provide to the Contractor, in writing, the results of phasing and phase rotation tests. The Contractor is responsible for maintaining the phasing and phase rotation tests, and is responsible for maintaining the phasing, and matching the existing phase rotation and phasing when installing conductors in existing electrical systems.

Install the cables in the following locations:

Exterior:

- a. In underground duct banks
- b. In conduit above and below grade
- c. In manholes
- d. And by direct burial

Inside Buildings:

- a. By open wire method
- b. On insulator hooks
- c. On racks
- d. In wall and ceiling mounted cable trays

Secure cables with heavy-duty cable ties in existing or new trays mounted horizontally, where the cable rests on the tray bottom. Install cable ties at a minimum of [3000] [\_\_\_\_\_] millimeter [10] [\_\_\_\_\_] foot intervals.

Secure cables with [PVC-coated] [metallic] [non-metallic] cable clamps, straps, hangers, or other approved supporting devices to tunnel walls, ceilings, and in new or existing cable trays mounted vertically, where the

tray bottom is in a vertical plane.

When field cuts or other damage occurs to the PVC coating, apply a liquid PVC patch to maintain the integrity of the coating. After the installation is complete, perform an inspection to ensure that the coating has no voids, pinholes, or cuts.

Before installing new armored cable, ensure that cable trays are properly secured and supported. Add new permanent or temporary tray support devices as required to preclude cable tray failure during cable pulling or after cable is installed.

Installed cable or conductors of a primary distribution system will be rejected by the Government when placed:

- a. Openly in cable trays or openly racked along interior walls
- b. In the same raceway or conduit with AC/DC control circuits or AC power circuits operating at less than 600 volts
- c. In a manner allowing the cable to support its own weight

### 3.2.1 Protection During Splicing Operations

Provide a blower to force fresh air into manholes or confined areas where free movement or circulation of air is obstructed. Have waterproof protective coverings available on the work site to protect against moisture while a splice is being made. Use pumps to keep manholes dry during splicing operations. Never make a splice or termination with the interior of a cable exposed to moisture. Moisture-test the conductor insulation paper before the splice is made. Use a manhole ring at least [150] [\_\_\_\_\_] millimeter [6] [\_\_\_\_\_] inches above ground around the manhole entrance to keep surface water from entering the manhole. Before starting the splice, plug unused ducts and stop water seepage through ducts in use.

### 3.2.2 Duct Cleaning

\*\*\*\*\*  
**NOTE: Delete the heading and the following paragraph if the installation of power cables is in ducts and manholes provided under this project. Provisions for duct cleaning are adequately covered in Section 33 71 02 UNDERGROUND ELECTRICAL DISTRIBUTION.**  
\*\*\*\*\*

Thoroughly clean ducts before installation of power cables. Pull a standard flexible mandrel through each duct to loosen particles of earth, sand, or foreign material in the line. Use a mandrel that is not less than [300] [\_\_\_\_\_] millimeter [12] [\_\_\_\_\_] inches long with a diameter 13 millimeter 1/2 inch less than the inside diameter of the duct. Then pull a brush with stiff bristles through each duct to remove the loosened particles. Use a brush with a diameter that is the same as or slightly larger than the diameter of the duct.

### 3.2.3 Pulling Cables in Ducts, Manholes and Utility Tunnels

Submit a [Pulling Plan](#) including calculations of pulling tension and side

wall pressure anticipated, and the maximum allowable pulling tension for each pull. Do not perform any pull until Government reviews and approves the pulling plan.

Pull medium-voltage cables into ducts and utility tunnels with equipment designed for this purpose, including a power-driven winch, cable-feeding flexible tube guide, cable grips, and lubricants. Employ a sufficient number of trained personnel and equipment to ensure correct installation of the cable.

Set up the cable reel at the side of the manhole or tunnel hatch opening and above the duct or hatch level, allowing the cable to enter through the opening without reverse bending. Install a flexible tube guide through the opening in a manner that prevents the cable from rubbing against the edges of structural members.

Ensure that the pulling force for a cable grip on lead-sheathed cable does not exceed [the force calculated in the pulling plan for the] [6700] [\_\_\_\_\_] newton per 650 square millimeter [1,500] [\_\_\_\_\_] pounds per square inch of sheath cross-sectional area. Use a dynamometer in the pulling line to ensure that the pulling force is not exceeded. Ensure that the pulling force for a nonmetallic-sheathed cable does not exceed the smaller of 4400 newton 1,000 pounds or a value computed from the following equation:

$$TM = 0.036 \times N \times CM$$

Where: TM = maximum allowable pulling tension in newton pounds

N = number of conductors in the cable

CM = cross-sectional area of each conductor in square millimeter circular mils

### 3.2.3.1 Allowable Sidewall Pressure

The allowable sidewall pressure is the smaller of 7300 newtons per meter 500 pounds per foot of bend radius or the cable manufacturer's recommended maximum value. Show in the pulling plan submittal the calculations for allowable tension and sidewall pressure as well as the anticipated tension and sidewall pressure for each pull in the project.

Unreel cable from the top of the reel, carefully controlling payout. Attach cable to be pulled through a swivel to the main pulling wire by means of a [pulling eye installed by the factory or approved cable splicer] [suitable cable grip permitted only on cables less than 60 meter 200 feet long and less than 50 millimeter 2 inches in diameter].

Attach pulling eyes to the cable conductors of the 3-1/C circuit to prevent damage to the cable structure. Pull the entire 3-1/C circuit simultaneously.

### 3.2.3.2 Minimum Bending Radius

Minimum bending radius during cable pulling operations is 760 millimeter 30 inches. For permanent cable bending/racking the minimum bending radius is 12 times cable diameter.

### 3.2.3.3 Coating of Cables

Liberally coat cables with a suitable cable-pulling lubricant as it enters the tube guide or duct. Do not use greaser and oil lubricants. Cover nonmetallic sheathed cables with wire-pulling compounds, when required, which have no deleterious effects on the cable. Use rollers, sheaves or tube guides, around which the cable is pulled, conforming to the 760 millimeter 30 inches minimum bending radius of the cable during the pulling operations.

### 3.2.3.4 Pulling Speed

Pull cables into ducts at a speed not to exceed [15] [\_\_\_\_\_] meters per minute 50 feet per minute and not in excess of maximum permissible pulling tension specified by the cable manufacturer. Cable pulling using a vehicle is not be permitted. Stop pulling operations immediately with any indication of binding or obstruction and do not resume until such difficulty is corrected. Provide sufficient slack for free movement of cable due to expansion or contraction.

### 3.2.3.5 Cable Splice Support And Sealing

Firmly support cable splices made up in manholes on cable racks as indicated. Do not pull cable splices in ducts. Overlap cable ends at the ends of a section to provide sufficient undamaged cable for splicing. Overlap cables to be spliced in manholes to the centerline of the proposed joint by not less than [600] [\_\_\_\_\_] millimeters 2 feet.

Immediately seal cut ends of cables cut in the field to prevent entrance of moisture with heat-shrinkable molded cable end caps.

### 3.2.4 Splices and Terminations

Make splices in manholes or tunnels except where cable terminations are specifically indicated. Expedite splicing and terminating of cables in order to minimize exposure and cable deterioration.

Use only equipment and materials recommended by the splice manufacturer including calibrated cutting equipment to ensure consistent cut depths when preparing cable ends for the application of the splice kit. Connect the cable concentric neutral/shield wires across one side of the splice by split bundling the splice neutral wiring and connecting each bundle set to a continuous No. 4 AWG solid bare copper conductor via two compression conductors. Ensure the No. 4 AWG conductor extrudes from the cable splice jacket and connects to the manholes grounding system. Make all connections within the splice utilizing long barrel-type compression connectors and appropriate compression tools with proper size dies to ensure a satisfactory mechanical and electrical joint. Ensure bare connections of concentric neutral/shield wires are either contained within the splice kit or sealed via an additional outer covering, consisting of a heavy wall, heat-shrinkable tubing containing adhesive material (mastic) that melts as heat is applied and the outer tubing shrinks to form a moisture proof environmental seal. Provide outer tubing conforming to ANSI C119.1. Ensure splice meets the requirements of IEEE 404 for a 15 kV rating and is rated by the manufacturer for use on 15 kV class feeder cable systems. Take extra precautions to seal around the exit area of the bare copper jumpers with an additional mastic per the splice manufacturer's recommendations.

Terminate cables in approved cable terminations, rated Class 1 per IEEE 48. Dry terminations with medium voltage pennants, preformed, and hand wrapped stress cones can be used for terminating cables. Provide terminations with adequate means for making external connections to the cable conductors of single-conductor cables (phase and concentric neutral), protecting the cable insulation against moisture, oil, or other contaminants. Take extra precautions in physically protecting and supporting cables, and maintaining the insulation level of the cable.

Ensure that installation includes built-up or prefabricated heat or cold shrink stress-relief cones at the terminals of all shielded cables and at the terminals of single-conductor lead-covered cables rated 15 kV and above, ungrounded.

Field-fabricate cable splices from splicing kits supplied by and in accordance with the cable manufacturer's recommendations for the type, size, and electrical characteristics of the cable specified. Locate cable splices in manholes midway between the cable racks on the walls of the manholes and supported with cable arms at approximately the same elevation as the enclosing duct.

If cable splices in the tunnel are not installed in cable trays, install the cable splices on cable racks or by other approved methods that minimize physical stress on the splice connections. Support splices at approximately the same elevation as the installed cable except where space limitations or existing cable length limitations make this method impractical or impossible.

Support all universal demountable splices in a manner that minimizes physical stress on the splice connections. Support each cable end termination using a pair of saddle supports under the cable end termination or cable with a minimum [300] [ ] millimeter [12] [ ] inches and a maximum [750] [ ] millimeter [30] [ ] inches separation between the supports. Secure the cable end termination and cable to the supports in a manner that prevents movement of termination or cable at the support. Install saddle supports on a galvanized steel framing channel that is anchored to the wall, securely fastened to the cable tray, or installed by other approved methods.

### 3.2.5 Fireproofing

Provide fireproofing (Arc Proofing) for individual cable conductor in manholes, handholes and vaults which carry current at 2200 volts or more.

Tightly wrap strips of fireproofing tape around each cable spirally in half-lapped wrapping. Extend the tape 25 millimeter 1 inch into the ducts. To prevent unraveling, random wrap the fireproofing tape the entire length of the fireproofing with pressure-sensitive glass cloth tape.

### 3.2.6 Cable Tag Installation

Install cable tags in each manhole and at each termination as specified. Install cable tags over the fireproofing and position the tags so that they are clearly visible without disturbing any cabling or wiring in the manholes and equipment.

## 3.3 FIELD QUALITY CONTROL

\*\*\*\*\*



NOTE: If the specified system is identified as critical, configured, or mission-essential, use Section 01 86 26.07 40 RELIABILITY CENTERED ACCEPTANCE FOR ELECTRICAL SYSTEMS to establish predictive and acceptance testing criteria, above and beyond that listed below.

\*\*\*\*\*

Perform PT&I tests and provide submittals as specified in Section 01 86 26.07 40 RELIABILITY CENTERED ACCEPTANCE FOR ELECTRICAL SYSTEMS.

After the installation of power cables has been completed, including splices, joints, and terminations, and before the cable is energized, subject each medium voltage cable to field testing in accordance with the following requirements:

- a. Provide test equipment, labor, and trained technical personnel as necessary to perform the electrical acceptance tests.
- b. Record all tests on an approved medium voltage cable test form and submit completed forms to the Contracting Officer.
- c. Make arrangements to have tests witnessed and approved by the Contracting Officer.
- d. Isolate each power-cable installation completely from extraneous electrical connections at cable splices/terminations and joints. Observe all safety precautions.
- e. Ensure each power cable is first given an insulation resistance test using a meg-ohmmeter with a voltage output of at least 2,500-volts. Apply test for a long enough time to fully charge the cable (no less than one minute). Record readings as indicated on forms provided. The minimum reading is 5000 megohms at an ambient temperature of 20 degrees C 68 degrees F. Correct readings taken at other than 20 degrees C 68 degrees F ambient temperatures accordingly.
- f. Conform testing to NETA ATS, and NFPA 70B.

[ Upon successful completion of the insulation resistance test, subject the cable to a Very Low Frequency (VLF) AC high potential test. Adhere general VLF testing measures, parameters, considerations, and results to the following:

- a. Ensure test voltage duration is continuous duty for 30 minutes (non-interrupted)
- b. Provide the test equipment to test the cable capacity in microfarads.
- c. Provide the test equipment to generate the test voltages required for the 30 minute test duration and adhere to the following table:

<u>VLF Test Voltage for Sinusoidal Waveform</u>		
Cable Rating phase to phase	Acceptance (phase to ground test values)	Acceptance (phase to ground test values)
	(New cable)	(Existing cable spliced to new cable)
(rms voltage, KV)	(peak voltage, KV)	(peak voltage, KV)
[5]	[14]	[10]
[15]	[28]	[22; (EPR TO EPR)]
[15]	[15]	[15; (EPR TO NON-EPR)]

- d. Ensure the sinusoidal test frequency is 0.1 Hertz.
- e. Do not perform test on cable attached to equipment.

\*\*\*\*\*

**NOTE: Include, but do not limit Acceptance test values to peak voltage, frequency, and duration, with respect to the cable rating, and clearly identify each on the test submittal, with pass/fail results identified per cable installation (refer to IEEE 400.2). Notify Contracting Officer or Contracting Officer's Technical Representative 48 hours prior to test start. All testing will be witnessed by the Government.**

\*\*\*\*\*

Ensure Splices/terminations are clean, dry, and tested per **IEEE 48** and **IEEE 400.2**.

] [Upon successful completion of the insulation resistance tests, subject the cable to a direct-current high-potential test for 5 minutes applying test voltages in accordance with **AEIC CS1** and **IEEE 400.2** for paper-impregnated, lead-covered cable; **AEIC CS8** and **IEEE 400.2** for cross-linked, polyethylene-insulated cable; and **AEIC CS8** and **IEEE 400.2** for ethylene propylene rubber-insulated cable.

Record leakage current readings every 30 seconds during the first 2 minutes and every minute thereafter for the remainder of the test. When the leakage current continues to increase after the first minute, immediately terminate the test and take steps to find and correct the fault. When a second test becomes necessary, repeat this test procedure.

Upon satisfactory completion of the high-potential test, give the cable a second insulation resistance test as before.

Provide results of the second insulation resistance test that agree with the first test and that indicate no evidence that the cable has been permanently injured by the high-potential test.

Record test data identifying the cable and location, megohm readings

versus time, leakage current readings versus time, and cable temperature versus time.]

Final acceptance depends upon the satisfactory performance of the cable under test. Do not energize cable until recorded test data has been approved by the Contracting Officer.

Perform [radiographic tests](#) on all potheads at the discretion of the Contracting Officer to determine if voids exist in the pothead. Rework unacceptable terminations at no additional expense to the Government.

#### 3.4 CLOSEOUT ACTIVITIES

Provide manufacturer's instructions showing the recommended sequence and method of installation for [medium-voltage power cables](#).

-- End of Section --