

\*\*\*\*\*  
USACE / NAVFAC / AFCEA UFGS-09225 (October 2003)  
-----  
Preparing Activity: USACE Superseding  
UFGS-09225A (November 1995)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMLR dated 22 December 2004

\*\*\*\*\*

SECTION TABLE OF CONTENTS

DIVISION 09 - FINISHES

SECTION 09225

STUCCO

10/03

PART 1 GENERAL

- 1.1 REFERENCES
- 1.2 SUBMITTALS
- 1.3 DELIVERY AND STORAGE
- 1.4 ENVIRONMENTAL CONDITIONS

PART 2 PRODUCTS

- 2.1 PORTLAND CEMENT
- 2.2 COLORED STUCCO FINISH COAT
- 2.3 LIME
- 2.4 SAND
- 2.5 ACCESSORIES
- 2.6 STEEL FRAMING
- 2.7 METAL LATH
- 2.8 WATER

PART 3 EXECUTION

- 3.1 FRAMING
- 3.2 CONTROL JOINTS
- 3.3 LATH
  - 3.3.1 Steel and Wood Supports
  - 3.3.2 On Concrete and Masonry
  - 3.3.3 Over Metal Lintels and Flashings
  - 3.3.4 Special Shapes, Profiles, and Contours
- 3.4 FURRING
- 3.5 PREPARATION OF SURFACES
- 3.6 PROPORTIONS AND MIXING
- 3.7 STUCCO APPLICATION
  - 3.7.1 Workmanship
  - 3.7.2 Scratch Coat
  - 3.7.3 Brown Coat
  - 3.7.4 Finish Coat

3.7.5 Surface Tolerance  
3.8 CURING AND PROTECTION  
3.9 PATCHING AND POINTING

-- End of Section Table of Contents --

\*\*\*\*\*  
USACE / NAVFAC / AFCEA UFGS-09225 (October 2003)  
-----  
Preparing Activity: USACE Superseding  
UFGS-09225A (November 1995)

## UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated 22 December 2004

\*\*\*\*\*

### SECTION 09225

STUCCO  
10/03

\*\*\*\*\*

NOTE: This section covers requirements for stucco,  
including associated framing and lathing.

Comments and suggestions on this guide specification  
are welcome and should be directed to the technical  
proponent of the specification. A listing of  
technical proponents, including their organization  
designation and telephone number, is on the Internet.

Recommended changes to a UFGS should be submitted as  
a Criteria Change Request (CCR).

Use of electronic communication is encouraged.

Brackets are used in the text to indicate designer  
choices or locations where text must be supplied by  
the designer.

\*\*\*\*\*

## PART 1 GENERAL

\*\*\*\*\*

NOTE: At paragraph SUBMITTALS, SD-04 Samples; for  
large projects, select the wording to require a  
jobsite sample panel.

\*\*\*\*\*

### 1.1 REFERENCES

\*\*\*\*\*

NOTE: Issue (date) of references included in  
project specifications need not be more current than  
provided by the latest guide specification. Use of  
SpecsIntact automated reference checking is  
recommended for projects based on older guide  
specifications.

\*\*\*\*\*

The publications listed below form a part of this specification to the

extent referenced. The publications are referred to within the text by the basic designation only.

ASTM INTERNATIONAL (ASTM)

ASTM A 185	(2002) Steel Welded Wire Reinforcement, Plain, for Concrete
ASTM C 1032	(2004) Woven Wire Plaster Base
ASTM C 1063	(2003) Installation of Lathing and Furring to Receive Interior and Exterior Portland Cement-Based Plaster
ASTM C 150	(2004a) Portland Cement
ASTM C 206	(2003) Finishing Hydrated Lime
ASTM C 841	(2003) Installation of Interior Lathing and Furring
ASTM C 847	(1995; R 2000) Metal Lath
ASTM C 897	(2000) Aggregate for Job-Mixed Portland Cement-Based Plasters
ASTM C 926	(1998a) Application of Portland Cement-Based Plaster
ASTM C 933	(2004) Welded Wire Lath
ASTM D 1784	(2003) Rigid Poly(Vinyl Chloride) (PVC) Compounds and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds

1.2 SUBMITTALS

\*\*\*\*\*

NOTE: Submittals must be limited to those necessary for adequate quality control. The importance of an item in the project should be one of the primary factors in determining if a submittal for the item should be required.

A "G" following a submittal item indicates that the submittal requires Government approval. Some submittals are already marked with a "G". Only delete an existing "G" if the submittal item is not complex and can be reviewed through the Contractor's Quality Control system. Only add a "G" if the submittal is sufficiently important or complex in context of the project.

For submittals requiring Government approval on Army projects, a code of up to three characters within the submittal tags may be used following the "G" designation to indicate the approving authority. Codes for Army projects using the Resident Management System (RMS) are: "AE" for

Architect-Engineer; "DO" for District Office (Engineering Division or other organization in the District Office); "AO" for Area Office; "RO" for Resident Office; and "PO" for Project Office. Codes following the "G" typically are not used for Navy projects.

Submittal items not designated with a "G" are considered as being for information only for Army projects and for Contractor Quality Control approval for Navy projects.

\*\*\*\*\*

Government approval is required for submittals with a "G" designation; submittals not having a "G" designation are [for Contractor Quality Control approval.] [for information only. When used, a designation following the "G" designation identifies the office that will review the submittal for the Government.] The following shall be submitted in accordance with Section 01330 SUBMITTAL PROCEDURES:

#### SD-02 Shop Drawings

##### Lathing and Stucco

Drawings showing details of construction for reinforcement, furring, and grounds; including detailed description of the proposed job-mix proportions for base and finish coats; including identification of thickness of coats and locations where each mix and coating thickness will be used.

#### SD-03 Product Data

##### Materials

Manufacturers installation instructions for stucco materials.

#### SD-04 Samples

##### Colored Stucco Finish Coat

Samples including both a fabricated portion of unit of work and color samples.

[One 300 mm 12 inch square stucco panel showing finish texture and color and exposed reinforcement at the edges, one 300 mm 12 inch square of reinforcement, and a 300 mm 12 inch length of each accessory proposed, prior to proceeding with stucco work.]

[A sample panel of stucco, constructed at the jobsite, and located as directed, to demonstrate installation procedures, texture and color, prior to proceeding with any stucco work. Panel size shall be a minimum of 1200 x 2400 mm 4 feet wide x 8 feet high; shall contain each type accessory proposed for use and shall be constructed in the vertical position. Sample panel shall have exposed reinforcement at the edges. Each phase of installation such as framing, scratch coat, brown coat, finish coat and curing procedures shall be demonstrated in the construction of the panel. One 300 mm 12 inch square of reinforcement and one 300 mm 12 inch length of each accessory

proposed for use, shall be submitted prior to constructing the sample panel.]

### 1.3 DELIVERY AND STORAGE

Packaged materials shall be delivered to the site in the original packages and containers with labels intact and seals unbroken. Cementitious materials shall be kept dry and stored off the ground under cover away from damp surfaces until ready to be used. Aggregate shall be covered to prevent the absorption or loss of moisture.

### 1.4 ENVIRONMENTAL CONDITIONS

Stucco shall not be applied when the ambient temperature is 4 degrees C 40 degrees F or lower, or when a drop in temperature below 4 degrees C 40 degrees F is expected within 48 hours after application.

## PART 2 PRODUCTS

### 2.1 PORTLAND CEMENT

\*\*\*\*\*  
NOTE: Where colored or white stucco finish is required, the gray portland cement will be omitted. Select type of cement to provide the required characteristics. Type I cement should normally be specified when stucco requires no special characteristics. Type II cement should be specified when stucco will be exposed to moderate sulphate (alkali) action. Type III cement should be specified when high early strength is needed.  
\*\*\*\*\*

Portland cement shall conform to ASTM C 150, [gray portland cement Type [I] [II] [III].] [white portland cement, Type [I] [II] [III].]

### 2.2 COLORED STUCCO FINISH COAT

Colored stucco finish coat shall be a mill mixed product using white portland cement and requiring only the addition of and mixing with water for application. Color shall be [in accordance with Section 09915COLOR SCHEDULE] [\_\_\_\_\_].

### 2.3 LIME

Lime shall conform to ASTM C 206, Type S.

### 2.4 SAND

Sand aggregate for job-mixed base coat and job-mixed finish coat stucco shall conform to ASTM C 897.

### 2.5 ACCESSORIES

\*\*\*\*\*  
NOTE: Custom aluminum radiuses, and custom miters and intersections with welded corners or taped backs are available. Aluminum shapes with clear anodized, color anodized, or baked enamel finishes may be used  
\*\*\*\*\*

where required for aesthetic purposes. Aluminum shapes are more costly than standard steel or PVC shapes.

\*\*\*\*\*

Accessories shall be [roll formed galvanized steel, or rigid polyvinyl chloride (PVC)] [\_\_\_\_], except that cornerite and striplath shall be formed from steel sheets with manufacturer's standard galvanized coating. Vinyl members shall be in accordance with ASTM D 1784. Welded wire corner reinforcements shall be zinc coated, galvanized 1.4 mm (17 gauge) 17 gauge steel wire conforming to ASTM A 185. Furring shall include hangers, bolts, inserts, clips, fastenings, and attachments of number, size, and design to develop the full strength of the members.

## 2.6 STEEL FRAMING

\*\*\*\*\*

NOTE: Stud sizes and framing dimensions and details will be indicated on the drawings. Framing will be designed for a maximum deflection of L/240 studs only assembly or a maximum deflection of L/360 for completed assembly, based on wind load design requirements in TM 5-809-1.

\*\*\*\*\*

Steel framing shall be as shown and shall be manufacturers standard products with shop applied protective coating.

## 2.7 METAL LATH

Metal lath shall conform to ASTM C 847, types and weights in accordance with the various spacing shown in ASTM C 841. Lath for vertical application on steel and wood framing supports shall be expanded metal or welded or woven wire and shall have paper backing with a minimum vapor permeance of 287.2 ng per Pa per second per square meter (5 perms). 5 perms. Woven wire lath shall be a maximum 38 x 38 mm 1-1/2 x 1-1/2 inch mesh wire of not less than 1.37 mm 0.0540 inch nominal diameter and shall conform to ASTM C 1032. Welded wire lath shall conform to ASTM C 933, with openings not to exceed 50 x 50 mm. 2 x 2 inches. Expanded metal or wire lath shall be fabricated in a manner to provide not less than 6 mm 1/4 inch keying between wire and paper backing and keying shall be obtained by a uniform series of slots in a perforated face paper woven between the wires.

## 2.8 WATER

Water shall be clean, fresh, potable, and free from amounts of oils, acids, alkalis and organic matter that would be injurious to the stucco.

## PART 3 EXECUTION

### 3.1 FRAMING

Framing shall be installed as indicated.

### 3.2 CONTROL JOINTS

\*\*\*\*\*

NOTE: Control joints will be shown on the drawings. Control joints shall divide stucco into areas of

not more than 13 square meters (144 square feet)  
with no dimension between control joints greater  
than 5.4 meters (18 feet). The length to width  
ratio of the area bounded by the control joints will  
not exceed 25 to 63 mm (1 to 2-1/2 inches).

\*\*\*\*\*

Control joints shall be located as indicated on the drawings.  
Prefabricated control joint members shall be installed prior to the  
application of the stucco. Control joints shall be cleared of all stucco  
within the control area after stucco application and prior to final stucco  
set.

### 3.3 LATH

\*\*\*\*\*

NOTE: Drawings will clearly indicate where metal  
lath is required. Metal lath will be used over  
metal supports and wood supports. Metal  
reinforcement with water-resistant paper is  
recommended in all steel frame construction and  
suspended ceilings. The use of metal reinforcement  
over concrete and masonry will be in accordance with  
local practice based upon satisfactory experience.  
Paper backed lath may be applied to interior  
concrete and masonry when adequate and uniform bond  
cannot be obtained otherwise, and when the lath will  
be protected from moisture.

\*\*\*\*\*

Lath shall be installed in accordance with ASTM C 841 or ASTM C 1063 except  
as otherwise specified. Metal and wire lath shall be applied straight,  
without buckles and with joints staggered. End laps of metal lath shall be  
not less than 25 mm. 1 inch. When paper-backed lath is used, the paper  
shall be split from the lath at all lap areas to provide a paper to paper  
and lath to lath lap. Horizontal joints shall be shiplapped. Lath shall  
be interrupted at all control joints.

#### 3.3.1 Steel and Wood Supports

Metal lath without integral backing over vertical open or solid wood and  
steel backing frame construction shall be applied only after a backing of  
shiplapped waterproofed building paper or other approved material has been  
applied to the area to receive the stucco. Lath shall be secured to the  
wood frames with nails or staples spaced not over 150 mm 6 inches on  
centers along each support; and where sheets of lath are lapped, fasteners  
shall be driven so as to hold both lapped edges securely in place. Lath  
shall be secured to steel frames in accordance with ASTM C 841 or ASTM C  
1063, as applicable.

#### 3.3.2 On Concrete and Masonry

Lath shall be fastened every 200 mm 8 inches vertically and every 400 mm 16  
inches horizontally. Where wood supports adjoin masonry or concrete in the  
same direction, casing bead, control joints, or reinforcement shall be  
provided as indicated.



### 3.3.3 Over Metal Lintels and Flashings

Lath over metal lintels shall be extended vertically over the angles to a height of not less than 150 mm 6 inches and horizontally across the underside of the lintels and shall be secured in an approved manner. Lath over metal flashings shall lap the flashings not less than 50 mm 2 inches and shall be extended vertically for a height of not less than 150 mm. 6 inches.

### 3.3.4 Special Shapes, Profiles, and Contours

Special shapes, profiles, and contours shall be formed with wood, metal or aluminum furring and reinforcing.

## 3.4 FURRING

Furring shall be installed to true lines and surfaces and shall be rigidly supported and secured in place.

## 3.5 PREPARATION OF SURFACES

Preparation of surfaces for application of stucco to solid bases such as stone, masonry or concrete shall conform to the applicable requirements of ASTM C 926.

## 3.6 PROPORTIONS AND MIXING

Proportions and mixing for job-mixed base coat and finish coat shall conform to the applicable requirements of ASTM C 926. Mixing of mill-mixed finish coat shall be in accordance with the manufacturer's directions.

## 3.7 STUCCO APPLICATION

Stucco shall be applied in three coats to a thickness of not less than 25 mm 1 inch as measured from the back plane of metal reinforcement, exclusive of ribs or dimples or from the face of solid backing or support, with or without metal reinforcement, to the finished stucco surface, including moderate texture variations. Stucco application shall conform to the applicable requirements of ASTM C 926 and the following:

### 3.7.1 Workmanship

Items or features of the work in connection with or adjoining the stucco shall be in place, plumb, straight, and true prior to beginning the stucco work. Metal and wire lath, where required, shall be in place and positioned to provide a good key at back of lath. Where lath is applied over copper, the copper shall be given a heavy coat of bituminous paint. Masonry surfaces to receive stucco shall be evenly dampened immediately prior to application of stucco. Each stucco coat shall be applied continuously in one general direction, without allowing mortar to dry at edges. Where it is impossible to work the full dimension of a wall surface in a continuous operation, jointing shall be made at a break, opening, or other natural division of the surface. Edges to be joined shall be dampened slightly to produce a smooth confluence. Exterior corners of stucco shall be slightly rounded. Stucco on soffit surfaces shall be pitched forward to form a drip.

### 3.7.2 Scratch Coat

Scratch coat shall be applied not less than 9 mm 3/8 inch thick under sufficient pressure to form good keys and to completely embed the reinforcement. Before the scratch coat has set, it shall be lightly scratched in one direction and vertical surfaces shall be scratched in the horizontal direction only. The scratch coat shall be fog cured for a minimum of 72 hours.

### 3.7.3 Brown Coat

The scratch coat shall be dampened evenly to obtain uniform suction before the brown coat is applied. There shall be no visible water on the surface when the brown coat is applied. The brown coat shall be applied to the scratch coat with sufficient pressure to force the stucco into the scratches and shall be brought to a plumb, true, even plane with rod or straightedge. When set sufficiently, the brown coat shall be uniformly floated with a dry float to promote densification of the coat and to provide a surface receptive to bonding of the finish coat. Brown coat shall be fog cured for a minimum of 72 hours.

### 3.7.4 Finish Coat

Surfaces of the brown coat shall be dampened not more than 1 hour before the finish coat is to be applied to a uniform wetness with no free-standing water on the surface. The finish coat shall have a [smooth trowel] [float] [trowel-textured] [rough-textured] [spray-textured] [exposed aggregate] finish and shall conform to the approved sample. The finish coat shall be fog cured for a minimum of 48 hours. Care shall be taken to prevent staining.

### 3.7.5 Surface Tolerance

When a 3 m 10 foot straightedge is placed at any location on the finished surface of the stucco, excluding rough-textured finish, the surface shall not vary more than 3 mm 1/8 inch from the straightedge.

## 3.8 CURING AND PROTECTION

Fog curing shall be accomplished by applying a fine mist of water to the stucco. Care shall be exercised during fog curing to avoid erosion damage to the stucco surfaces. A solid stream of water shall not be used. Frequency of fogging shall be not less than three times daily. When directed the Contractor shall protect the stucco from the direct rays of the sun during severe drying conditions using canvas, cloth or other approved sheet material.

## 3.9 PATCHING AND POINTING

Loose, cracked, damaged or defective work shall be replaced or patched as directed. Patching shall match existing work in texture and color and shall be finished flush.

-- End of Section --