
USACE / NAVFAC / AFCEC / NASA UFGS-09 65 66 (August 2010)

Preparing Activity: USACE Superseding
UFGS-09 65 66 (May 2009)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated January 2016

SECTION TABLE OF CONTENTS

DIVISION 09 - FINISHES

SECTION 09 65 66

RESILIENT ATHLETIC FLOORING

08/10

PART 1 GENERAL

- 1.1 REFERENCES
- 1.2 SUBMITTALS
- 1.3 QUALITY ASSURANCE
 - 1.3.1 Adhesive Application
 - 1.3.2 Flooring Material
 - 1.3.3 Sustainable Design Certification
- 1.4 DELIVERY, STORAGE, AND HANDLING
- 1.5 WARRANTY
- 1.6 EXTRA MATERIALS
 - 1.6.1 Floor Tiles
 - 1.6.2 Carpeting

PART 2 PRODUCTS

- 2.1 INDOOR-OUTDOOR CARPETING TYPE [A] [_____]
- 2.2 RUBBER COMPOSITION TILE TYPE [A] [_____]
- 2.3 RUBBER POURED-IN-PLACE FLOORING TYPE [A] [_____]
- 2.4 SHEET RUBBER COMPOSITION FLOORING TYPE [A] [_____]
- 2.5 SHEET VINYL COMPOSITION FLOORING TYPE [A] [_____]
- 2.6 URETHANE POURED-IN-PLACE FLOORING TYPE [A] [_____]
- 2.7 RESILIENT MAT UNDERLAY
- 2.8 ADHESIVES
- 2.9 CRACK FILLER/LEVELER FOR CONCRETE SURFACES
- 2.10 EDGING STRIPS
- 2.11 PRIMER
- 2.12 GAME LINE MATERIAL
- 2.13 WALL BASE
- 2.14 SEALANTS
- 2.15 MANUFACTURERS COLOR

PART 3 EXECUTION

- 3.1 PREPARATION
- 3.2 MOISTURE TEST

- 3.3 INSTALLATION
 - 3.3.1 General Requirements
 - 3.3.2 Molded Rubber Base
 - 3.3.3 Indoor-Outdoor Carpeting
 - 3.3.4 Sheet Vinyl Composition Flooring
 - 3.3.4.1 Seams
 - 3.3.4.2 Hot-welded Seams
 - 3.3.5 Sheet Rubber Composition Flooring
 - 3.3.6 Rubber Composition Tile Flooring
 - 3.3.6.1 Application With Adhesive
 - 3.3.6.2 Application Without Adhesive
 - 3.3.7 Rubber Poured-in-Place Flooring
 - 3.3.8 Urethane Poured-in-Place Flooring
 - 3.3.9 Resilient Mat Underlay
 - 3.3.10 Line Marking and Finishing
- 3.4 PROTECTION

-- End of Section Table of Contents --

USACE / NAVFAC / AFCEC / NASA UFGS-09 65 66 (August 2010)

Preparing Activity: USACE Superseding
UFGS-09 65 66 (May 2009)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated January 2016

SECTION 09 65 66

RESILIENT ATHLETIC FLOORING 08/10

NOTE: This guide specification covers the requirements for resilient athletic flooring.

Adhere to UFC 1-300-02 Unified Facilities Guide Specifications (UFGS) Format Standard when editing this guide specification or preparing new project specification sections. Edit this guide specification for project specific requirements by adding, deleting, or revising text. For bracketed items, choose applicable items(s) or insert appropriate information.

Remove information and requirements not required in respective project, whether or not brackets are present.

Comments, suggestions and recommended changes for this guide specification are welcome and should be submitted as a Criteria Change Request (CCR).

PART 1 GENERAL

NOTE: Systems specified in this guide specification are recommended for indoor athletic rooms e.g., weight rooms, running tracks, recreational areas, aerobic centers, multi-purpose gym floors, etc. Hardwood flooring is preferable for basketball courts, handball, and racquetball courts. Rubber-base floorings can be used in outdoor installations like wet bars, running tracks, tennis courts, and swimming pool walks.

1.1 REFERENCES

NOTE: This paragraph is used to list the publications cited in the text of the guide

specification. The publications are referred to in the text by basic designation only and listed in this paragraph by organization, designation, date, and title.

Use the Reference Wizard's Check Reference feature when you add a RID outside of the Section's Reference Article to automatically place the reference in the Reference Article. Also use the Reference Wizard's Check Reference feature to update the issue dates.

References not used in the text will automatically be deleted from this section of the project specification when you choose to reconcile references in the publish print process.

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

ASTM INTERNATIONAL (ASTM)

ASTM C920	(2014a) Standard Specification for Elastomeric Joint Sealants
ASTM D1054	(2002; R 2007) Rubber Property - Resilience Using a Rebound Pendulum
ASTM D1894	(2014) Static and Kinetic Coefficients of Friction of Plastic Film and Sheet
ASTM D2240	(2005; R 2010) Standard Test Method for Rubber Property - Durometer Hardness
ASTM D2632	(2014) Rubber Property-Resilience by Vertical Rebound
ASTM D395	(2014) Standard Test Methods for Rubber Property - Compression Set
ASTM D412	(2006a; R 2013) Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers - Tension
ASTM D624	(2000; R 2012) Tear Strength of Conventional Vulcanized Rubber and Thermoplastic Elastomers
ASTM F1303	(2004; R 2014) Sheet Vinyl Floor Covering with Backing
ASTM G21	(2015) Determining Resistance of Synthetic Polymeric Materials to Fungi

SCIENTIFIC CERTIFICATION SYSTEMS (SCS)

SCS	Scientific Certification Systems
-----	----------------------------------

(SCS)Indoor Advantage

UL ENVIRONMENT (ULE)

ULE Greenguard

UL Greenguard Certification Program

1.2 SUBMITTALS

NOTE: Review submittal description (SD) definitions in Section 01 33 00 SUBMITTAL PROCEDURES and edit the following list to reflect only the submittals required for the project.

The Guide Specification technical editors have designated those items that require Government approval, due to their complexity or criticality, with a "G." Generally, other submittal items can be reviewed by the Contractor's Quality Control System. Only add a "G" to an item, if the submittal is sufficiently important or complex in context of the project.

For submittals requiring Government approval on Army projects, a code of up to three characters within the submittal tags may be used following the "G" designation to indicate the approving authority. Codes for Army projects using the Resident Management System (RMS) are: "AE" for Architect-Engineer; "DO" for District Office (Engineering Division or other organization in the District Office); "AO" for Area Office; "RO" for Resident Office; and "PO" for Project Office. Codes following the "G" typically are not used for Navy, Air Force, and NASA projects.

An "S" following a submittal item indicates that the submittal is required for the Sustainability Notebook to fulfill federally mandated sustainable requirements in accordance with Section 01 33 29 SUSTAINABILITY REPORTING.

Choose the first bracketed item for Navy, Air Force and NASA projects, or choose the second bracketed item for Army projects.

Government approval is required for submittals with a "G" designation; submittals not having a "G" designation are for [Contractor Quality Control approval.] [information only. When used, a designation following the "G" designation identifies the office that will review the submittal for the Government.] Submittals with an "S" are for inclusion in the Sustainability Notebook, in conformance to Section 01 33 29 SUSTAINABILITY REPORTING. Submit the following in accordance with Section 01 33 00 SUBMITTAL PROCEDURES:

SD-02 Shop Drawings

Approved Detail Drawings; G[, [_____]]

SD-03 Product Data

Installation
Certification

SD-04 Samples

Flooring

SD-07 Certificates

Flooring

1.3 QUALITY ASSURANCE

1.3.1 Adhesive Application

Adhesive applied and poured-in-place flooring shall be installed by an experienced floor applicator approved by the manufacturer.

1.3.2 Flooring Material

Submit three samples minimum 225 x 275 mm 9 x 11 inches of each color of flooring material required and manufacturer's certificates stating that the resilient athletic flooring materials conform to the specified requirements. Labels or markings affixed to manufacturer's products attesting that products meet requirements specified herein will be accepted in lieu of certificates.

1.3.3 Sustainable Design Certification

NOTE: Products meeting the Gold standard will also meet the basic standard. Require Gold when the facility will be used by people sensitive to air quality conditions, such as child development centers and medical facilities.

Product shall be third party certified in accordance with ULE Greenguard[Gold], SCS Scientific Certification Systems Indoor Advantage[Gold]or equal. Certification shall be performed annually and shall be current.

1.4 DELIVERY, STORAGE, AND HANDLING

Deliver Materials in manufacturer's original unopened containers with labels intact. Materials shall not be delivered to the installation area or installed before all work that may damage the materials or the finished floor, such as overhead work, is completed. Store materials in a clean, dry area. Materials in storage shall be maintained at temperatures recommended by the manufacturer. Protection boards shall be stored flat and off the ground.

1.5 WARRANTY

Provide manufacturer's standard performance guarantees or warranties that extend beyond a one year period.

1.6 EXTRA MATERIALS

1.6.1 Floor Tiles

Furnish spare tiles of each color at the rate of [_____] [5] tiles for each 1000 tiles installed. Tiles shall be from the same lot as those installed.

1.6.2 Carpeting

Extra material from same dye lot consisting of full width continuous broadloom shall be provided for maintenance. A minimum of [_____] percent of total square meters square yards of each carpet type, pattern, and color shall be provided.

PART 2 PRODUCTS

NOTE: If more than one type of resilient flooring is required, a separate paragraph for that type floor will be used. Each flooring type will be designated with a letter or number symbol. Use the same symbols to key flooring types to locations listed or shown on the drawings.

Floor types will be specified for a specific use such as, carpet for pool areas, multi-use areas, and pro shops, or rubber tile flooring for weight rooms, etc. Edit specification as required to meet project needs and omit text not applicable.

2.1 INDOOR-OUTDOOR CARPETING TYPE [A] [_____]

NOTE: Carpeting shall be specially designed for indoor or indoor-outdoor environments as required, e.g., weight rooms, outdoor playground areas, indoor/outdoor pool areas, and pro shops. Edit as required to meet project requirements.

Carpet-type flooring shall be spike proof [[ribbed] [berber] pattern consisting of a top layer of rugged [polypropylene] [or] [nylon] fibers combined with an inorganic cut-resistant [non-skid] [_____] [wet areas artificial turf pattern consisting of a top layer of rugged polypropylene fibers combined with an inorganic cut-resistant [porous rubber knob][foam] [_____] backing. Minimum total thickness shall be [10] [_____] mm [0.375] [_____] inches. Finished surface pile yarn weight (face weight) shall be minimum [_____] kg/square meter ounces/square yard. Test results for resistance to soil bacteria or fungi shall show no sustained growth or discoloration after 21 days when tested in accordance with ASTM G21.

2.2 RUBBER COMPOSITION TILE TYPE [A] [_____]

Rubber tiles shall be [interlocked] [_____] [600 x 600] [_____] mm [24 x 24] [_____] inches square, of solid first quality rubber, uniformly resilient material designed to be applied [with] [without] adhesive. Tiles shall be approximately [13] [_____] mm [1/2] [_____] inch thick, shall be [smooth] [traction] [_____] texture, and shall be [reversible]

[non-reversible]. Flooring shall be able to withstand [75 percent compression for 22 hours at 70 degrees C 158 degrees F] [_____] without residual deformation when tested in accordance with ASTM D395. Flooring shall have a durometer hardness Shore-A of 50-60 when tested in accordance with ASTM D2240.

2.3 RUBBER POURED-IN-PLACE FLOORING TYPE [A] [_____]

The resilient poured-in-place rubber surface shall be composed of chloroprene rubber, chloroprene rubber sponge, aggregate, setting powders, and a top finish composed of acrylic resins. Flooring shall be able to withstand 50 percent compression for 72 hours at 22 degrees C 72 degrees F with a residual deformation of less than 10 percent when tested in accordance with ASTM D395. Flooring shall have a minimum compression modulus at 10 percent of 690 kPa 100 psi, a minimum elongation of 250 percent and a minimum tensile strength of 3800 kPa 550 psi plus or minus 34 kPa 5 psi when tested in accordance with ASTM D412. Flooring shall have a durometer hardness Shore-A of 55-60 when tested in accordance with ASTM D2240 and a minimum tear resistance of 10.5 kN/m 60 lbf/inch when tested in accordance with ASTM D624.

2.4 SHEET RUBBER COMPOSITION FLOORING TYPE [A] [_____]

Sheet rubber flooring shall be prefabricated, homogeneous, natural and synthetic rubbers, and shall be minimum [5] [_____] mm [3/16] [_____] inch thick, and shall have [smooth gymnasium] [textured all-purpose] finish. Flooring shall be roll type not less than 1500 [_____] mm 60 [_____] inches wide. Flooring shall have a minimum tensile stress at 100 percent elongation of 1500 kPa 220 psi and a minimum ultimate elongation of 250 percent when tested in accordance with ASTM D412. Flooring shall be able to withstand 50 percent compression for 72 hours at 22 degrees C 72 degrees F with a residual deformation of less than 10 percent when tested in accordance with ASTM D395. Flooring shall provide a 55 plus or minus 5 percent rebound when tested in accordance with ASTM D1054.

2.5 SHEET VINYL COMPOSITION FLOORING TYPE [A] [_____]

Sheet vinyl flooring shall consist of a solid polyvinyl chloride material which shall conform to the chemical resistance requirements of ASTM F1303. Flooring shall be not less than 1200 mm 48 inches wide and shall have a minimum thickness of [3] [_____] mm [1/8] [_____] inch. Floor surface shall be [smooth] [stipple] [track embossed] texture. Flooring shall have a minimum coefficient of friction of 0.75 when tested in accordance with ASTM D1894. Flooring shall have an average thickness loss of 0.2 mm 8.0 mils plus or minus 0.025 mm 1 mil. Rebound resilience of flooring shall be greater than 12 percent and less than 30 percent when tested in accordance with ASTM D2632. [An optional compatible top coating shall be provided by the sheet vinyl flooring manufacturer.]

2.6 URETHANE POURED-IN-PLACE FLOORING TYPE [A] [_____]

NOTE: Urethane resilient flooring may be installed on a variety of substrates and in a variety of thicknesses from 3 to 25 mm 1/8 to 1 inch. Coordinate with manufacturer's literature. Edit specification as required.

The resilient poured-in-place urethane surface shall be composed of a seamless pigmented monolithic material. Flooring shall be minimum [3] [_____] mm [1/8] [_____] inch thick and shall have [smooth gymnasium] [textured all-purpose] [textured track] finish. Flooring shall have a durometer hardness Shore-A of 55-60 when tested in accordance with ASTM D2240. Flooring shall have a minimum ultimate elongation of 250 percent when tested in accordance with ASTM D412 and shall have a density of 1.25.

2.7 RESILIENT MAT UNDERLAY

NOTE: Resilient mat underlay may be used under a two-component polyurethane wear coat system, sheet rubber surfacing system, or a vinyl sheet surfacing system. Deletion or specification and thickness of mat underlay will be determined by the athletic flooring requirements. Coordinate with manufacturer's literature.

Resilient mat underlay shall be prefabricated granulated indoor/outdoor rubber mat bound with polyurethane for shock absorption. Mat thickness shall be [_____] mm inches.

2.8 ADHESIVES

Adhesive shall be as recommended by the flooring manufacturer and correspond to the specified flooring product and to the substrate.

2.9 CRACK FILLER/LEVELER FOR CONCRETE SURFACES

Crack filler/leveler for concrete floor surfaces shall be as recommended by flooring manufacturer.

2.10 EDGING STRIPS

Strips shall be of the same material and design as recommended by flooring manufacturer.

2.11 PRIMER

Concrete primer shall be as recommended by flooring manufacturer and correspond to the specified flooring product and to the substrate.

2.12 GAME LINE MATERIAL

Game line material shall as recommended by the flooring manufacturer and correspond to the specified flooring product.

2.13 WALL BASE

Base shall be [rubber] [vinyl], Type [straight] [coved] style. Base shall be 100 mm 4 inches high and minimum 2 mm 0.080 inch thick.

2.14 SEALANTS

Sealants shall be in accordance with Section 07 92 00 JOINT SEALANTS.

2.15 MANUFACTURERS COLOR

Color shall be [in accordance with Section 09 06 90 SCHEDULES FOR PAINTING AND COATING] [_____].

PART 3 EXECUTION

NOTE: Expansion joints under resilient athletic flooring should be avoided to the maximum extent possible by placing the joints at the perimeter of the floor area. For large areas such as gymnasiums, shrinkage compensating concrete may be advisable.

3.1 PREPARATION

Concrete surfaces shall be completely cured and dry. No curing agents, sealers, or hardeners shall be used to aid in the curing of the concrete slab. Surfaces shall be free of paint spots, and other foreign materials. Surfaces shall be ground down or leveled with an approved leveling compound to a tolerance of plus or minus 3 mm 1/8 inch within a 3 meters 10 foot radius. Cracks, construction joints, or damaged portions of floor shall be filled with crack filler for concrete surfaces. Expansion joints shall be filled and sealed in accordance with the approved installation instructions of the manufacturer. All sealants shall be in accordance with ASTM C920. Expansion joints shall not be filled with a material that will make them inoperable.

3.2 MOISTURE TEST

The suitability of the concrete subfloor for receiving the resilient flooring with regard to moisture content shall be determined by a moisture test as recommended by the flooring manufacturer.

3.3 INSTALLATION

3.3.1 General Requirements

Installation shall be in accordance with the approved installation instructions. Tile or sheet flooring shall be rolled with a medium-sized roller in both directions to release entrapped air. Submit manufacturer's descriptive data and catalog cuts indicating materials of construction and physical characteristics. Installation, cleaning and maintenance instructions shall be included.

3.3.2 Molded Rubber Base

Base shall be installed in accordance with the approved installation instructions of the manufacturer of the base.

3.3.3 Indoor-Outdoor Carpeting

Application of flooring shall be as recommended by the manufacturer.

3.3.4 Sheet Vinyl Composition Flooring

Concrete slab shall be primed in accordance with approved installation instructions. Flooring shall be installed as recommended by the

manufacturer.

3.3.4.1 Seams

End seams shall be cut and placed as recommended by the manufacturer.
Seams shall be weighted as required.

3.3.4.2 Hot-welded Seams

Butted sheets shall be grooved to a depth of approximately two thirds of their total thickness using an electrical or hand grooving tool. Grooved seams shall be thermowelded using a hot air welding tool and a PVC welding thread. After seam has cooled to room temperature, the excess shall be trimmed off to provide a flush joint.

3.3.5 Sheet Rubber Composition Flooring

Sheet flooring shall be dry cut and layed out flat a minimum of 24 hours prior to adhering to the substrate. End seams shall be single cut. Edge seams shall be cut through overlapping sheets, then snapped into place to ensure tight seams. Seams shall be weighted as required.

3.3.6 Rubber Composition Tile Flooring

**NOTE: Tile flooring can be installed with adhesive
or without adhesive using a mechanical locking
technique. Edit to comply with the type flooring
specified.**

3.3.6.1 Application With Adhesive

Tiles shall be layed on adhesive surface in pattern according to approved detail drawings. Joints of tiles shall be even and tight. Tiles shall be cut to fit tightly against the wall. Submit drawings showing game lines, location of anchor plate assemblies, floor outlets, and under-floor conduit or raceways.

3.3.6.2 Application Without Adhesive

Tiles shall be joined together using interlocking ears or other mechanical locking techniques. The ears shall interlock into the adjoining tile 40 mm 1-1/2 inches and shall provide at least five interlocks for each 600 mm 24 inch edge. Where required, a beveled transfer border shall be supplied to interlock with the flooring tiles. The borders shall be 150 mm 6 inches wide and 600 mm 24 inches long and the same thickness as the matching tiles.

3.3.7 Rubber Poured-in-Place Flooring

Concrete slab shall be primed with primer recommended by manufacturer in a thin film covering approximately 10 square meters/L 400 square feet per gallon. Chloroprene rubber shall be poured onto subfloor and troweled to a smooth and uniform layer of the required thickness. A grout chloroprene rubber coat shall be applied to fill possible voids in surface. After the chloroprene rubber is completely dry, a pigmented finish shall be applied with a spray and roller.

3.3.8 Urethane Poured-in-Place Flooring

Concrete slab shall be primed with primer recommended by the manufacturer. Rate of application shall be in accordance with approved installation instructions and shall be allowed to dry odor free. Concrete construction joints shall be covered with 50 mm 2 inch wide PVC duct tape. Resin shall be applied in a minimum of 2 lifts. Pigmented and textured coatings shall be applied in accordance with manufacturer's recommendations.

3.3.9 Resilient Mat Underlay

The resilient mat underlay shall be unrolled and allowed to relax prior to cutting or fitting. Mat shall be installed in accordance with manufacturers instructions.

3.3.10 Line Marking and Finishing

After installation is complete, the floor surface shall be cleaned in accordance with installation instructions. Line marking shall be layed out, masked, and painted according to approved detail drawings and approved installation instructions. Finishing shall be in accordance with the manufacturer's recommendations.

3.4 PROTECTION

The installed flooring shall be protected from soiling and damage with heavy reinforced, nonstaining kraft paper, plywood, or hardboard sheets as required. Edges of kraft paper protection shall be lapped and secured to provide a continuous cover. Protective covering shall be removed when directed by the Contracting Officer.

-- End of Section --