

\*\*\*\*\*  
USACE / NAVFAC / AFCEC / NASA UFGS-09 66 16 (August 2016)  
-----  
Preparing Activity: USACE Superseded  
UFGS-09 66 16 (August 2010)

## UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated January 2017

\*\*\*\*\*

### SECTION TABLE OF CONTENTS

#### DIVISION 09 - FINISHES

#### SECTION 09 66 16

#### TERRAZZO FLOOR TILE

08/16

#### PART 1 GENERAL

- 1.1 REFERENCES
- 1.2 SUBMITTALS
- 1.3 QUALITY ASSURANCE
- 1.4 CERTIFICATIONS
  - 1.4.1 Indoor Air Quality Certifications
    - 1.4.1.1 Adhesives and Sealants
- 1.5 DELIVERY, STORAGE, AND HANDLING
- 1.6 SITE CONDITIONS
- 1.7 WARRANTY

#### PART 2 PRODUCTS

- 2.1 PRODUCT SUSTAINABILITY CRITERIA
  - 2.1.1 Recycled Content for Terrazzo Floor Tile Materials
  - 2.1.2 Reduce Volatile Organic Compounds (VOC) (LOW-EMITTING MATERIALS) for Products
- 2.2 STANDARD PRODUCTS
- 2.3 TERRAZZO TILE
- 2.4 ADHESIVE
- 2.5 TERRAZZO BASE
- 2.6 TERRAZZO STRIPS
- 2.7 METAL EDGE STRIPS
- 2.8 COLOR

#### PART 3 EXECUTION

- 3.1 GENERAL
- 3.2 EXAMINATION
- 3.3 SUBSTRATE PREPARATION
- 3.4 MOISTURE TEST
- 3.5 INSTALLATION
  - 3.5.1 Tile
  - 3.5.2 Metal Edge Strips
  - 3.5.3 Terrazzo Base/Strips

- 3.6 CLEANING
- 3.7 PROTECTION

-- End of Section Table of Contents --

\*\*\*\*\*  
USACE / NAVFAC / AFCEC / NASA UFGS-09 66 16 (August 2016)  
-----  
Preparing Activity: USACE Superseded  
UFGS-09 66 16 (August 2010)

## UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated January 2017

\*\*\*\*\*

### SECTION 09 66 16

#### TERRAZZO FLOOR TILE 08/16

\*\*\*\*\*

NOTE: This guide specification covers the requirements for cast marble or granite terrazzo tile of various sizes and thicknesses).

Adhere to UFC 1-300-02 Unified Facilities Guide Specifications (UFGS) Format Standard when editing this guide specification or preparing new project specification sections. Edit this guide specification for project specific requirements by adding, deleting, or revising text. For bracketed items, choose applicable items(s) or insert appropriate information.

Remove information and requirements not required in respective project, whether or not brackets are present.

Comments, suggestions and recommended changes for this guide specification are welcome and should be submitted as a Criteria Change Request (CCR).

\*\*\*\*\*

## PART 1 GENERAL

### 1.1 REFERENCES

\*\*\*\*\*

NOTE: This paragraph is used to list the publications cited in the text of the guide specification. The publications are referred to in the text by basic designation only and listed in this paragraph by organization, designation, date, and title.

Use the Reference Wizard's Check Reference feature when you add a Reference Identifier (RID) outside of the Section's Reference Article to automatically place the reference in the Reference Article. Also use the Reference Wizard's Check Reference feature to update the issue dates.

References not used in the text will automatically  
be deleted from this section of the project  
specification when you choose to reconcile  
references in the publish print process.

\*\*\*\*\*

The publications listed below form a part of this specification to the  
extent referenced. The publications are referred to within the text by the  
basic designation only.

ASTM INTERNATIONAL (ASTM)

ASTM C109/C109M	(2016a) Standard Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or (50-mm) Cube Specimens)
ASTM C501	(1984; R 2015) Relative Resistance to Wear of Unglazed Ceramic Tile by the Taber Abraser
ASTM C97/C97M	(2015) Absorption and Bulk Specific Gravity of Dimension Stone
ASTM D2047	(2011) Static Coefficient of Friction of Polish-Coated Floor Surfaces as Measured by the James Machine
ASTM E648	(2014c) Standard Test Method for Critical Radiant Flux of Floor-Covering Systems Using a Radiant Heat Energy Source
ASTM E84	(2016) Standard Test Method for Surface Burning Characteristics of Building Materials

CALIFORNIA DEPARTMENT OF PUBLIC HEALTH (CDPH)

CDPH SECTION 01350	(2004; Add 2004-01) Standard Practice for the Testing Of Volatile Organic Emissions from Various Sources Using Small-Scale Environmental Chambers
--------------------	------------------------------------------------------------------------------------------------------------------------------------------------------------

SOUTH COAST AIR QUALITY MANAGEMENT DISTRICT (SCAQMD)

SCAQMD Rule 1168	(1989; R 2005) Adhesive and Sealant Applications
------------------	-----------------------------------------------------

1.2 SUBMITTALS

\*\*\*\*\*

NOTE: Review submittal description (SD) definitions  
in Section 01 33 00 SUBMITTAL PROCEDURES and edit  
the following list to reflect only the submittals  
required for the project.

The Guide Specification technical editors have  
designated those items that require Government

approval, due to their complexity or criticality, with a "G." Generally, other submittal items can be reviewed by the Contractor's Quality Control System. Only add a "G" to an item, if the submittal is sufficiently important or complex in context of the project.

For submittals requiring Government approval on Army projects, a code of up to three characters within the submittal tags may be used following the "G" designation to indicate the approving authority. Codes for Army projects using the Resident Management System (RMS) are: "AE" for Architect-Engineer; "DO" for District Office (Engineering Division or other organization in the District Office); "AO" for Area Office; "RO" for Resident Office; and "PO" for Project Office. Codes following the "G" typically are not used for Navy, Air Force, and NASA projects.

Use the "S" classification only in SD-11 Closeout Submittals. The "S" following a submittal item indicates that the submittal is required for the Sustainability Notebook to fulfill federally mandated sustainable requirements in accordance with Section 01 33 29 SUSTAINABILITY REPORTING.

Choose the first bracketed item for Navy, Air Force and NASA projects, or choose the second bracketed item for Army projects.

\*\*\*\*\*

Government approval is required for submittals with a "G" designation; submittals not having a "G" designation are for [Contractor Quality Control approval.] [information only. When used, a designation following the "G" designation identifies the office that will review the submittal for the Government.] Submittals with an "S" are for inclusion in the Sustainability Notebook, in conformance to Section 01 33 29 SUSTAINABILITY REPORTING. Submit the following in accordance with Section 01 33 00 SUBMITTAL PROCEDURES:

SD-02 Shop Drawings

Terrazzo Tile; G[, [\_\_\_\_]]

SD-03 Product Data

Terrazzo Tile

Adhesive

Installation

SD-04 Samples

Terrazzo Tile

Terrazzo Base

Metal Edge Strips

SD-10 Operation and Maintenance Data

Manufacturer's Maintenance Instructions; G[, [\_\_\_\_\_]]

SD-11 Closeout Submittals

Recycled Content for Terrazzo Tile; S

Indoor Air Quality for Adhesive; S

Warranty

### 1.3 QUALITY ASSURANCE

Installer must possess, to the satisfaction of the Contracting Officer, the technical qualifications, experience, trained personnel, and facilities to properly install the specified items.

#### [1.4 CERTIFICATIONS

\*\*\*\*\*  
**NOTE: Include the following section where these  
products are used on the interior of the building  
(defined as inside of the weatherproofing system).**  
\*\*\*\*\*

##### 1.4.1 Indoor Air Quality Certifications

Submit required indoor air quality certifications in one submittal package.

##### 1.4.1.1 Adhesives and Sealants

Adhesive products used on the interior of the building (defined as inside of the weatherproofing system) must meet either emissions requirements of CDPH SECTION 01350 (limit requirements for either office or classroom spaces regardless of space type) or VOC content requirements of SCAQMD Rule 1168. Provide current product certification documentation from certification body.

#### ]1.5 DELIVERY, STORAGE, AND HANDLING

Deliver materials to the jobsite in the manufacturer's original unopened containers marked with the manufacturer's brand name, color, and pattern. Store materials delivered and placed in storage protected from damage, weather, humidity and temperature variation, dirt and dust, or other contaminants. Temperature of storage area must not be lower than 10 degrees C 50 degrees F or higher than 32 degrees C 90 degrees F.

### 1.6 SITE CONDITIONS

Do not install tiles until other work that could cause damage to the finished flooring has been completed. Maintain a temperature of not less than 21 degrees C 70 degrees F in all areas where tile is to be installed for a period of not less than [48] [\_\_\_\_\_] hours before, during and after laying of tiles. Bring tiles into installation areas and allow to condition at not less than 21 degrees C 70 degrees F for a period of [48] [\_\_\_\_\_] hours prior to installation. After installation of tiles, maintain

a minimum temperature of 13 degrees C 55 degrees F.

## 1.7 WARRANTY

Provide manufacturer's standard performance guarantees or warranties that extend beyond a one year period.

## PART 2 PRODUCTS

### 2.1 PRODUCT SUSTAINABILITY CRITERIA

For products in this section, where applicable and to extent allowed by performance criteria, provide and document the following:

#### [2.1.1 Recycled Content for Terrazzo Floor Tile Materials

\*\*\*\*\*  
**NOTE: Use materials with recycled content, calculated on the basis of post-industrial and post-consumer percentage content where appropriate for use. Designer must verify suitability, availability within the region, cost effectiveness and adequate competition (including verification of bracketed percentages included in this guide specification) before specifying product recycled content requirements.**  
\*\*\*\*\*

Recycled content is identified for some products in this section; provide documentation in accordance with Section 01 33 29 SUSTAINABILITY REPORTING paragraph RECYCLED CONTENT. Other products listed in this section may be available with recycled content; identify those products that meet project requirements for recycled content, and provide documentation in accordance with Section 01 33 29 SUSTAINABILITY REPORTING paragraph RECYCLED CONTENT.

#### ]2.1.2 Reduce Volatile Organic Compounds (VOC) (LOW-EMITTING MATERIALS) for Products

Reduced VOC content is identified for some products in this section; provide documentation in accordance with Section 01 33 29 SUSTAINABILITY REPORTING paragraph REDUCE VOLATILE ORGANIC COMPOUNDS (VOC) (LOW-EMITTING MATERIALS). Other products listed in this section may be available with reduced VOC content; identify those products that meet project requirements for reduced VOC content, and provide documentation in accordance with Section 01 33 29 SUSTAINABILITY REPORTING paragraph REDUCE VOLATILE ORGANIC COMPOUNDS (VOC) (LOW-EMITTING MATERIALS).

### 2.2 STANDARD PRODUCTS

Provide materials which are the standard products of a manufacturer regularly engaged in the manufacture of the material and that essentially duplicate products that have been in satisfactory use at least 2 years prior to bid opening.

### 2.3 TERRAZZO TILE

\*\*\*\*\*  
**NOTE: Designer will select the chip requirements and also determine whether flexible or rigid resin**

is required, or give the Contractor the options.  
The source of the aggregate will directly impact the  
look of the tile.

Coordinate with manufacturer's data of terrazzo tile  
when determining the patterns, styles, sizes and  
thicknesses of tiles.

\*\*\*\*\*

\*\*\*\*\*

NOTE: Use materials with recycled content,  
calculated on the basis of post-industrial and  
post-consumer percentage content where appropriate  
for use. Designer must verify suitability,  
availability within the region, cost effectiveness  
and adequate competition (including verification of  
bracketed percentages included in this guide  
specification) before specifying product recycled  
content requirements.

Research shows the product is commonly available  
with the minimum recycled content percentages shown  
below. Based on research, insert desired minimum  
percentages into the empty set of brackets.

\*\*\*\*\*

provide terrazzo tile of the indicated colors and consisting of [marble]  
[or] [granite] chips embedded in a [flexible] [or] [rigid] thermoset resin  
matrix. Submit drawings indicating pattern, size, style, and color of  
tiles and two 150 by 150 mm 6 by 6 inch minimum samples of each color and  
pattern of terrazzo tile to be used. Tiles must be [5] [\_\_\_\_\_] mm [3/16]  
[\_\_\_\_\_] inch thick and nominal [300 by 300] [\_\_\_\_\_] mm [12 by 12] [\_\_\_\_\_] inches.  
Provide tiles with a [polished] [polished and [honed] [textured]]  
[honed] [textured] finish with uniform color distribution of chips. [Grade  
marble chips to [16] [6] mm [5/8] [1/4] inch maximum size.] [Granite chips  
must be manufacturer's standard gradation.] Provide tile with the following  
properties:

TERRAZZO TILE PROPERTIES		
PROPERTY	TEST METHOD	VALUE
Compressive Strength	ASTM C109/C109M	20 MPa 3000 psi minimum
Water Absorption	ASTM C97/C97M	0.7 percent maximum
Abrasive Wear	ASTM C501	Index 28
Coefficient of Friction	ASTM D2047	0.5 wet
Flame Spread	ASTM E84	Class A
Critical Radiant Flux	ASTM E648	Class I

Provide Terrazzo Tile with [50][100][\_\_\_\_\_] percent recycled aggregate.  
Provide data identifying percentage of recycled content for terrazzo tile.]

## 2.4 ADHESIVE

Adhesive must be flooring manufacturer's standard product or a product recommended by the manufacturer. Submit documentation from manufacturer indicating that the materials conform to the specified requirements and flooring manufacturer's approval of underlayment, adhesive, and cleaners. Provide certification of indoor air quality for adhesive.

## 2.5 TERRAZZO BASE

Provide terrazzo base of colors as indicated, meeting the requirements of paragraph TERRAZZO TILE and being a manufacturer's standard product. Base/strips shall be [10] [19] mm thick by [\_\_\_\_\_] mm wide by [\_\_\_\_\_] mm long [3/8] [3/4] inch thick by [\_\_\_\_\_] inch wide by [\_\_\_\_\_] inch long. Base/strips shall have [polished] [honed] [textured] finish. Submit two 100 mm 4 inch long samples of each type and color of trim pieces.

## 2.6 TERRAZZO STRIPS

Provide terrazzo strips of colors as indicated, meeting the requirements of paragraph TERRAZZO TILE and being a manufacturer's standard product. Strips must be [\_\_\_\_\_] mm high by [\_\_\_\_\_] mm wide by [\_\_\_\_\_] mm long [3/8] [3/4] inch high by [\_\_\_\_\_] inch wide by [\_\_\_\_\_] inch long. Strips must have [polished] [honed] [textured] finish. Submit two 100 mm 4 inch long samples of each type and color of trim pieces.

## 2.7 METAL EDGE STRIPS

Metal edge strips must be extruded aluminum, butt type, approximately 40 mm 1-1/2 inches wide with thickness to set top surface flush with top of tile and with bevel at exposed edge. Edge strips must have countersunk holes near each end and spaced not more than 200 mm 8 inches on center for securement. Submit one 150 mm 6 inch long sample of metal edge strip

## 2.8 COLOR

Color must be [as indicated] [in accordance with Section 09 06 00 SCHEDULES FOR FINISHES] [\_\_\_\_\_].

# PART 3 EXECUTION

## 3.1 GENERAL

Install flooring and base on floor surfaces and walls where indicated. Except as required for installation of new tile, keep traffic new tile for at least [24] [\_\_\_\_\_] hours after installation.

## 3.2 EXAMINATION

After becoming familiar with details of the work, verify dimensions in the field, and advise the Contracting Officer of any discrepancy before performing the work.

## 3.3 SUBSTRATE PREPARATION

Fill holes and cracks with mortar. Floors must be free of curing compounds, grease, dirt, loose particles and other foreign matter that would prevent adhesion. Chip and grind smooth projecting irregularities.

Fill depressions and level uneven surfaces. Rinse subfloors and allow to dry prior to applying adhesive.

#### 3.4 MOISTURE TEST

After concrete floor surfaces have been cleaned, spread small patches of adhesive in several locations in each room or area to receive tile and allowed to dry overnight. If the adhesive can be peeled easily from the floor surfaces, the surface is not sufficiently dry. Repeat the steps until the adhesive adheres properly. Do not apply tiles until adhesive adheres tightly to the floor.

#### 3.5 INSTALLATION

Submit the manufacturer's printed installation instructions for the conditions indicated.

##### 3.5.1 Tile

Install tile in accordance with the manufacturer's approved installation instructions, except as specified herein. Lay tile symmetrical about center lines of rooms or areas. Joints must be tight, inconspicuous as possible, and in alignment. Cut tile to fit snugly at pipes and other vertical surfaces. Seal joints at pipes with adhesive. Remove spots or smears of adhesive immediately. Entire surface of finished tile floor must be smooth, straight, and free from bleeding adhesive, buckles, waves, or projecting tile edges upon completion. Bleeding of adhesive on finished floors is cause for rejection by the Contracting Officer. Remove and replace damaged or rejected tiles.

##### 3.5.2 Metal Edge Strips

Secure edge strips with No. 10 aluminum alloy, counter-sunk, flathead machine screws with expansion sleeves. Provide exposed edges of tile with one-piece metal edge strips.

##### 3.5.3 Terrazzo Base/Strips

Terrazzo base/strips must be continuous and adhesively applied. Joints must be tight and inconspicuous in same manner as floor tile.

#### 3.6 CLEANING

Upon completion of the installation and after adhesive has cured, flooring shall be thoroughly cleaned in accordance with the manufacturer's recommendations.

#### 3.7 PROTECTION

Cover and protect the terrazzo tile work from damage until completion of the work of all other trades. Remove and replace defects which develop, such as loose, broken, or curled tiles. Submit [six] [\_\_\_\_\_] copies of the Manufacturer's Maintenance Instructions.

-- End of Section --