
USACE / NAVFAC / AFCEA / NASA UFGS-09 97 13.28 (April 2006)

Preparing Activity: NAVFAC

Replacing without change
UFGS-09974 (September 2000)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated 1 April 2006

SECTION TABLE OF CONTENTS

DIVISION 09 - FINISHES

SECTION 09 97 13.28

PROTECTION OF BURIED STEEL PIPING AND STEEL BULKHEAD TIE RODS

04/06

PART 1 GENERAL

- 1.1 REFERENCES
- 1.2 DEFINITIONS
 - 1.2.1 Coating
 - 1.2.2 Coating System
 - 1.2.3 Tape
 - 1.2.4 Tape Coating System
- 1.3 SUBMITTALS

PART 2 PRODUCTS

- 2.1 MATERIALS
 - 2.1.1 Tape Coating System (TCS)
 - 2.1.2 Adhesive Thermoplastic Resin Coating System (ATRCs)
 - 2.1.3 Thermosetting Epoxy Coating System (TECS)
 - 2.1.4 Polyethylene-Butyl Adhesive Coating System (PBACS)
 - 2.1.5 Mastics
 - 2.1.6 Rock Shield

PART 3 EXECUTION

- 3.1 INSTALLATION
 - 3.1.1 TCS
 - 3.1.1.1 Surface Preparation
 - 3.1.1.2 Application
 - 3.1.2 Joints, and Other Irregular Surfaces For ATRCS
 - 3.1.2.1 Damaged Areas
 - 3.1.3 TECS
 - 3.1.3.1 Joints
 - 3.1.3.2 Damaged Areas
 - 3.1.4 Joints and Other Irregular Surfaces For PBACS
 - 3.1.4.1 Damaged Areas
- 3.2 FIELD QUALITY CONTROL
 - 3.2.1 Field Inspection
 - 3.2.2 Field Test

-- End of Section Table of Contents --

PART 1 GENERAL

1.1 REFERENCES

NOTE: This paragraph is used to list the publications cited in the text of the guide specification. The publications are referred to in the text by basic designation only and listed in this paragraph by organization, designation, date, and title.

Use the Reference Wizard's Check Reference feature when you add a RID outside of the Section's Reference Article to automatically place the reference in the Reference Article. Also use the Reference Wizard's Check Reference feature to update the issue dates.

References not used in the text will automatically be deleted from this section of the project specification when you choose to reconcile references in the publish print process.

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

AMERICAN WATER WORKS ASSOCIATION(AWWA)

- | | |
|-----------|--|
| AWWA C209 | (2000) Cold-Applied Tape Coatings for the Exterior of Special Sections, Connections and Fitting for Steel Water Pipe |
| AWWA C213 | (2001) Fusion-Bonded Epoxy Coating for the Interior and Exterior of Steel Water Pipelines |
| AWWA C214 | (2000) Tape Coating Systems for the Exterior of Steel Water Pipelines |

NACE INTERNATIONAL (NACE)

- | | |
|-------------|--|
| NACE RP0274 | (2004) High Voltage Electrical Inspection of Pipeline Coatings |
|-------------|--|

U.S. DEPARTMENT OF DEFENSE (DOD)

- | | |
|-----------|--|
| MIL-I-631 | (Rev D; Am. 6) Insulation, Electrical, Synthetic-Resin Composition, Nonrigid |
|-----------|--|

U.S. GENERAL SERVICES ADMINISTRATION (GSA)

- | | |
|------------|--|
| FS L-C-530 | (Rev C) Coating, Pipe, Thermoplastic Resin |
|------------|--|

1.2 DEFINITIONS

1.2.1 Coating

A continuous, uniformly thick layer formed on a surface by the mechanical application of a liquid, mastic, powdered, or extruded film material. Some types of application require elevated temperatures.

1.2.2 Coating System

One or more coatings applied to a properly prepared steel surface. If only one coating, that coating is applied directly to the steel surface; if more than one coating, each coating is applied in one operation over the previously applied and cured coating. For some applications, the first coating is a primer. Coatings of a particular system function together as a collective entity to protect the steel surface from corrosion. Coating system may be either liquid or tape applied.

1.2.3 Tape

Prefabricated laminate of plastic film backing with a homogeneous sealant layer or a pressure-sensitive adhesive layer produced in sheets, pads, or rolls wound on hollow cores. Tape applications do not require elevated temperatures.

1.2.4 Tape Coating System

One or more layers of tape applied cold over a properly prepared and primed steel surface. Tape on the primed surface protects the steel surface from corrosion.

1.3 SUBMITTALS

NOTE: Review submittal description (SD) definitions in Section 01 33 00 SUBMITTAL PROCEDURES and edit the following list to reflect only the submittals required for the project. Submittals should be kept to the minimum required for adequate quality control.

A "G" following a submittal item indicates that the submittal requires Government approval. Some submittals are already marked with a "G". Only delete an existing "G" if the submittal item is not complex and can be reviewed through the Contractor's Quality Control system. Only add a "G" if the submittal is sufficiently important or complex in context of the project.

For submittals requiring Government approval on Army projects, a code of up to three characters within the submittal tags may be used following the "G" designation to indicate the approving authority. Codes for Army projects using the Resident Management System (RMS) are: "AE" for Architect-Engineer; "DO" for District Office (Engineering Division or other organization in the District Office); "AO" for Area Office; "RO" for Resident Office; and "PO" for Project Office. Codes

following the "G" typically are not used for Navy,
Air Force, and NASA projects.

Choose the first bracketed item for Navy, Air Force
and NASA projects, or choose the second bracketed
item for Army projects.

Government approval is required for submittals with a "G" designation;
submittals not having a "G" designation are [for Contractor Quality Control
approval.][for information only. When used, a designation following the
"G" designation identifies the office that will review the submittal for
the Government.] The following shall be submitted in accordance with
Section 01 33 00 SUBMITTAL PROCEDURES:

SD-03 Product Data

Factory-applied coating system

Field-applied epoxy coating system

Thermosetting epoxy coating system

Polyethylene-Butyl Adhesive Coating System

Adhesive Thermoplastic Resin Coating System

Tape Coating System

Electrical-flaw detector

[Mastics]

[Rock shield]

[SD-06 Test Reports

Inspector's certificate

Submit for each inspection and test.

Field-applied epoxy coating]

SD-08 Manufacturer's Instructions

Field-applied epoxy coating system

Thermosetting epoxy coating system

Electrical-flaw detector

[Mastics]

[Rock Shield]

PART 2 PRODUCTS

2.1 MATERIALS

2.1.1 Tape Coating System (TCS)

NOTE: Use of M.L.W. or M.L.L.W. should be based upon the usage by a particular Activity. Selection may be based on the datum for each Activity contained in Table 1-4, "Tide Data for Naval Activities"; of DM-26.1 "Harbor and Coastal Facilities." If the design does not include tie rods, delete those portions of the first sentences that refer to tie rods, M.L.W., and M.L.L.W.

NOTE: Factory-applied coating with field machine-applied coatings at joints and damaged areas is the preferred method. If the work is a small retrofit or repair, factory applied coatings may be too restrictive. Irregular surfaces such as tees, valve bodies, and flanges are done by hand.

NOTE: The thicknesses of inner and combined tape are designed for moderately, and severely corrosive soil environments. For lightly corrosive soil environment use thickness specified for moderately corrosive soil environment.

NOTE: Tape applied at a temperature below 10 degrees C 50 degrees F should be suitable for cold weather application down to -12 degrees C 10 degrees F. Delete if application is going to be above 10 degrees C 50 degrees F.

Prefabricated tape with adhesive primer [for bulkhead tie rods and turnbuckles] [and] [for use on [pipe,] couplings, damaged areas and fittings]. The tape wrapping system shall conform to AWWA C209 and to MIL-I-631, Class I for fungus resistance, except that the fungus rating shall lie between zero and one for all specimens. The overall thickness of the tape wrap protection shall be not less than [0.75] [1.12] [_____] mm [30] [45] [_____] mils. [The tape system shall be suitable to be applied at temperatures below 10 degrees C 50 degrees F and above -12 degrees C 10 degrees F.]

2.1.2 Adhesive Thermoplastic Resin Coating System (ATRCs)

Steel pipe factory-applied coating system conforming to FS L-C-530 and coating manufacturer's instructions shall consist of a continuously extruded polyethylene coating [, capable of withstanding operating temperatures up to 88 degrees C 190 degrees F,] applied on an adhesive undercoat.

2.1.3 Thermosetting Epoxy Coating System (TECS)

NOTE: Use only epoxy coatings where petroleum fuels
are expected.

Factory-applied steel pipe system conforming to AWWA C213. Provide
field-applied epoxy coating in accordance with manufacturer's
recommendations and AWWA C213.

2.1.4 Polyethylene-Butyl Adhesive Coating System (PBACS)

Factory-applied steel pipe system of extruded butyl adhesive compound, 0.18
mm 7 mils minimum thickness, covered with overlapping layers of extruded
polyethylene wrapping, one mm 38 mils minimum thickness, in accordance with
AWWA C214.

[2.1.5 Mastics

NOTE: Mastic coatings are brush applied. Mastics
are used on irregular surfaces such as bolted
flanges and valve bodies where the tape will not
directly contact exposed surfaces. Show surfaces
that will require mastic coatings on drawings.
Delete if surfaces are smooth and round.

Apply a coating of manufacturer approved mastic protection to irregular
surfaces. Mastic shall be compatible with coating system. [Apply the tape
system over mastic.] Mastic layer thickness shall conform to coating
manufacturer's recommendation.

] [2.1.6 Rock Shield

NOTE: Rock shields are used where coarse rock
backfill or rocky soil conditions may damage the
tape coating.

Provide rock shield over completed coating system as recommended by coating
manufacturer.

] PART 3 EXECUTION

3.1 INSTALLATION

3.1.1 TCS

3.1.1.1 Surface Preparation

Surfaces shall be clean and dry. Wire brush weld beads, and remove weld
spatters. Remove heavy rust or mill scale with wire brush.

3.1.1.2 Application

Remove paper from Kraft paper-protected material before placing in final position. Reinforce coating at sling points with roofing felt or other approved heavy shielding material, or handle with nylon or canvas slings. Apply polyvinylchloride-butyl rubber laminated tape or pressure-sensitive organic plastic tape and its adhesive primer by single machine operation.

- a. Pipe: Spirally wrap straight runs in one layer, lapping the tape as applied. Overlap shall conform to recommendations of the tape manufacturer. When an outerwrap is used, overlap of outerwrap shall bridge joints of the tape. Apply at each end of straight runs a double wrap of one full width of tape at right angles to the axis in such a manner so as to seal ends of spiral wrapping.
- b. Pipe Joints and Couplings and Damaged Areas of Coatings: Clean joint areas which are to be taped, of burrs and rust. Smooth down or cut away damaged coating when not firmly bonded to pipe. Spirally wrap with a two-layer wrapping system, overlapping coating surface at least 75 mm 3 inches. Initially stretch tape sufficiently to conform to the surface to which it is applied, using one layer half-lapped for tape 50 mm 2 inches or less in width or one layer lapped at least 25 mm one inch for tape more than 50 mm 2 inches wide. Apply a second layer, lapped as above, with tension as tape comes off roll, and press to conform to shape of component. For other irregular surfaces such as bolted flanges valve bodies where tape coating system containing mastics is to be provided, apply with brush.
- c. Tie Rods and Tie Rod Fittings: Spirally wrap with a two-layer coating system. Apply tape to tie rods by lapping each layer of tape using a half-lap for tape 50 mm 2 inches or less in width or at least a 25 mm one inch lap for tape more than 50 mm 2 inches wide. For tie rod fittings, initially stretch tape sufficiently to conform to the surface to which it is applied, using one layer half-lapped for tape 50 mm 2 inches or less in width or one layer lapped at least 25 mm one inch for tape more than 50 mm 2 inches wide. Apply a second layer, lapped as before, with a tension as tape comes off the roll, and press to conform to the shape of component.

3.1.2 Joints, and Other Irregular Surfaces For ATRCS

Prepare surface as described in paragraph entitled "TCS." Wrap tape as specified in paragraph entitled "TCS"; except, apply the tape half-lapped, and prime extruded polyethylene coating and adhesive undercoat surfaces to be tape wrapped with a compatible primer as recommended by the tape manufacturer and approved by the extruded polyethylene coating applicator for use on the polyethylene coating.

3.1.2.1 Damaged Areas

Repair damaged areas of the extruded polyethylene coating by tape wrapping as specified under the paragraph, entitled "Tape Coating System" except press residual material from the extruded polyethylene coating into the break, or trim off. Prime areas to be taped prior to applying half-lapped tape.

3.1.3 TECS

NOTE: Use only epoxy coatings where petroleum products are expected.

Install in accordance with the manufacturer's instructions and [AWWA C213](#).

3.1.3.1 Joints

Clean both sides of weld area by wire brushing, and remove dust, moisture, and other contaminants. Apply primer recommended by coating manufacturer after cleaning of joints.

3.1.3.2 Damaged Areas

Remove damaged coating by abrading, filing, or wire brushing. Clean area to be repaired free of dust, moisture, and other contaminants. Cover with a primer and a coating recommended by coating manufacturer. Apply coating over cleaned surface, and extend approximately [75 mm 3 inches](#) beyond damaged area.

3.1.4 Joints and Other Irregular Surfaces For PBACS

Clean both sides of weld area by wire brushing, and remove dust, moisture, and other contaminants. Apply primer recommended by tape manufacturer and acceptable to coating manufacturer on cleaned area. Apply tape spirally with a 50-percent overlap in accordance with the tape manufacturer's instructions.

3.1.4.1 Damaged Areas

Remove rough or protruding polyethylene from damaged area by abrading, filing, or cutting the material. Clean area to be repaired free of dust, moisture, and other contaminants. Cover with tape recommended by coating manufacturer and primer recommended by tape manufacturer. Apply primer over cleaned surface, and extend approximately [75 mm 3 inches](#) beyond damaged area. Apply tape over primer, and extend [25 mm one inch](#) beyond damaged area. Apply additional primer over tape patch. Spirally wrap additional tape around pipe with a 50-percent overlap to cover tape patch, and extend a minimum of [50 mm 2 inches](#) beyond the edge of the patch.

3.2 FIELD QUALITY CONTROL

NOTE: Require a certified inspector where the scope and cost of the project warrants. When editing Section 01 45 00.00 20 QUALITY CONTROL, ensure that the qualification of inspector required below is coordinated.

Conform to [AWWA C214](#) [and [AWWA C213](#)]. [Inspection shall be performed by a National Association of Corrosion Engineers (NACE) certified inspector].

3.2.1 Field Inspection

Examine material surface preparation and application procedures performed in

the field.

3.2.2 Field Test

Test the protective system for holes, voids, cracks, and other visually undetectable damage that may occur during handling and installation in accordance with NACE Standard [NACE RP0274](#). In critical applications no holidays will be permitted. In non critical applications up to [10 holidays per meter](#) [3 holidays per linear feet](#) of the pipe may be accepted. Test with an approved [electrical-flaw detector](#) in accordance with the detector manufacturer's printed instructions. Prepare [inspector's certificate](#) for each inspection and test. Repair areas where arcing occurs and retest.

-- End of Section --