
USACE / NAVFAC / AFCEC

UFGS-03 70 00 (February 2010)

Change 2 - 08/20

Preparing Activity: USACE

Superseding

UFGS-03 70 00 (April 2006)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated April 2025

SECTION TABLE OF CONTENTS

DIVISION 03 - CONCRETE

SECTION 03 70 00

MASS CONCRETE

02/10, CHG 2: 08/20

PART 1 GENERAL

1.1 UNIT PRICES

1.1.1 Concrete for [_____]

1.1.1.1 Payment

1.1.1.2 Measurement

1.1.1.3 Unit of Measure

1.1.2 Concrete in Blockouts

1.1.2.1 Payment

1.1.2.2 Measurement

1.1.2.3 Unit of Measure

1.1.3 Portland Cement

1.1.3.1 Payment

1.1.3.2 Measurement

1.1.3.3 Unit of Measure

1.1.4 Pozzolan (Except Silica Fume)

1.1.4.1 Payment

1.1.4.2 Measurement

1.1.4.3 Unit of Measure

1.1.5 Ground Granulated Blast-Furnace Slag

1.1.5.1 Payment

1.1.5.2 Measurement

1.1.5.3 Unit of Measure

1.1.6 Water-Reducing Admixture (WRA)

1.1.6.1 Payment

1.1.6.2 Measurement

1.1.6.3 Unit of Measure

1.1.7 High-Range Water-Reducing Admixture (HRWR)

1.1.7.1 Payment

1.1.7.2 Measurement

1.1.7.3 Unit of Measure

1.1.8 Silica Fume, Dry

1.1.8.1 Payment

1.1.8.2 Measurement

- 1.1.8.3 Unit of Measure
- 1.1.9 Silica Fume, Slurry
 - 1.1.9.1 Payment
 - 1.1.9.2 Measurement
 - 1.1.9.3 Unit of Measure
- 1.2 REFERENCES
- 1.3 SUBMITTALS
- 1.4 QUALITY ASSURANCE
 - 1.4.1 Government Preconstruction Testing
 - 1.4.1.1 Aggregate Sources
 - 1.4.1.2 Cementitious Materials, Admixtures, and Curing Materials
 - 1.4.1.3 Materials for Mixture-Proportioning Studies
 - 1.4.2 Construction Testing by the Government
 - 1.4.2.1 General
 - 1.4.2.2 Testing Aggregates
 - 1.4.2.3 Cementitious Materials
 - 1.4.2.4 Cement from Prequalified Sources
 - 1.4.2.5 Pozzolan from Prequalified Sources
 - 1.4.2.6 Cement from Nonprequalified Sources
 - 1.4.2.7 Pozzolan from Nonprequalified Sources
 - 1.4.2.8 Ground Granulated Blast-Furnace Slag
 - 1.4.2.9 Chemical Admixtures
- 1.5 DELIVERY, STORAGE, AND HANDLING
 - 1.5.1 Cementitious Materials
 - 1.5.1.1 Transportation
 - 1.5.1.2 Storage
 - 1.5.1.3 Separation of Materials
 - 1.5.2 Aggregates Storage

PART 2 PRODUCTS

- 2.1 SYSTEM DESCRIPTION
 - 2.1.1 Proportioning Responsibility
 - 2.1.2 Design Requirements
 - 2.1.3 Air Content
 - 2.1.4 Slump
 - 2.1.5 Construction Tolerances
 - 2.1.6 Tabulations and Definitions
- 2.2 MATERIALS
 - 2.2.1 Cementitious Materials
 - 2.2.1.1 Portland Cement
 - 2.2.1.2 Pozzolan Other than Silica Fume
 - 2.2.1.3 Ground Granulated Blast-Furnace Slag
 - 2.2.1.4 Silica Fume
 - 2.2.1.5 Temperature of Cementitious Materials
 - 2.2.2 Admixtures
 - 2.2.2.1 Air-Entraining Admixtures
 - 2.2.2.2 [Accelerating Admixture
 - 2.2.2.3 Retarding Admixture
 - 2.2.2.4 Water-Reducing Admixture
 - 2.2.2.5 High-Range Water-Reducing Admixture (HRWRA)
 - 2.2.2.6 Expansive Admixture
 - 2.2.3 Curing Materials
 - 2.2.3.1 Sheet Materials
 - 2.2.3.2 Membrane-Forming Curing Compound
 - 2.2.3.3 Burlap
 - 2.2.4 Water
 - 2.2.5 Aggregates
 - 2.2.5.1 Aggregate Composition

- 2.2.5.2 Quality of Aggregates
- 2.2.5.3 Grading
 - 2.2.5.3.1 Fine Aggregate
 - 2.2.5.3.2 Coarse Aggregate
- 2.2.5.4 Particle Shape
- 2.2.5.5 Nominal Maximum-Size of Aggregate
- 2.2.5.6 Moisture Content
- 2.2.5.7 Commercial Concrete Aggregate Sources
- 2.2.5.8 Government Furnished Concrete Aggregate Source
 - 2.2.5.8.1 Location
 - 2.2.5.8.2 Explorations
- 2.2.6 Nonshrink Grout
- 2.2.7 Packaged Dry Repair Materials
- 2.2.8 Bonding Agents
 - 2.2.8.1 Latex Bonding Agent
 - 2.2.8.2 Epoxy Resin
- 2.2.9 Surface Retarder
- 2.3 PLANT AND EQUIPMENT
 - 2.3.1 Batch Plant
 - 2.3.2 Location
 - 2.3.3 Bins and Silos
 - 2.3.4 Batching Equipment
 - 2.3.4.1 Batchers
 - 2.3.4.2 Water Batcher
 - 2.3.4.3 Admixture Dispensers
 - 2.3.4.4 Moisture Control
 - 2.3.4.5 Scales
 - 2.3.4.6 Operation and Accuracy
 - 2.3.4.7 Interlocks
 - 2.3.4.8 Recorder
 - 2.3.4.9 Batch Counters
 - 2.3.4.10 Rescreening Plant
 - 2.3.4.11 Washing Plant
 - 2.3.4.12 Trial Operation
 - 2.3.4.13 Protection
 - 2.3.5 Laboratory Areas
 - 2.3.6 Plant Layout Drawings
 - 2.3.7 Mixers
 - 2.3.7.1 Stationary Mixer Uniformity Requirements
 - 2.3.7.2 Truck Mixers
 - 2.3.8 Sampling Facilities
 - 2.3.9 Coarse Aggregate
 - 2.3.10 Transporting Equipment
 - 2.3.10.1 Buckets
 - 2.3.10.2 Trucks
 - 2.3.10.3 Chutes
 - 2.3.10.4 Belt Conveyors
 - 2.3.10.5 Pump Placement

PART 3 EXECUTION

- 3.1 PREPARATION FOR PLACING
 - 3.1.1 Vibrators
 - 3.1.2 Embedded Items
 - 3.1.3 Concrete on Earth Foundations
 - 3.1.4 Concrete on Rock Foundations
 - 3.1.5 Construction Joint Treatment
 - 3.1.5.1 Joint Preparation
 - 3.1.5.2 Air-Water Cutting

- 3.1.5.3 High-Pressure Water Jet
 - 3.1.5.4 Wet Sandblasting
 - 3.1.5.5 Waste Water Disposal
- 3.2 TRANSPORTING AND PLACING
 - 3.2.1 Transporting
 - 3.2.1.1 Transporting by Bucket
 - 3.2.1.2 Transporting by Pump
 - 3.2.1.3 Transporting by Belt Conveyor
 - 3.2.2 Placing
 - 3.2.2.1 Time Interval Between Mixing and Placing
 - 3.2.2.2 Hot-Weather Placing
 - 3.2.2.3 Cold Weather Placing
 - 3.2.2.4 Special Temperature-Controlled Concrete
 - 3.2.2.5 Concrete Lifts
 - 3.2.2.6 Consolidation
 - 3.2.2.7 Placing Concrete in Unformed Curved Sections
 - 3.2.2.8 Placing Concrete Underwater
- 3.3 FINISHING
 - 3.3.1 Unformed Surfaces
 - 3.3.1.1 Float Finish
 - 3.3.1.2 Trowel Finish
 - 3.3.1.3 Broom Finish
 - 3.3.1.4 Abrasive Aggregate Finish
 - 3.3.1.5 High Velocity Finishes
 - 3.3.2 Formed Surface Repair
 - 3.3.2.1 Classes A, A-HV, & B Finishes
 - 3.3.2.2 Class C Finish
 - 3.3.2.3 Class D Finish
 - 3.3.2.4 Material and Procedure for Repairs
 - 3.3.3 Grout-Cleaned Finish
- 3.4 CURING AND PROTECTION
 - 3.4.1 Curing Time
 - 3.4.2 Moist Curing
 - 3.4.3 Membrane Curing
 - 3.4.3.1 Pigmented Curing Compound
 - 3.4.3.2 Nonpigmented Curing Compound
 - 3.4.3.3 Application
 - 3.4.4 Sheet Curing
 - 3.4.5 Sealed Insulation Curing
 - 3.4.6 Protection
 - 3.4.7 Cold Weather-Protection
- 3.5 BASE PLATES AND BEARING PLATES
 - 3.5.1 Setting of Plates
 - 3.5.2 Nonshrink Grout
 - 3.5.2.1 Mixing and Placing
 - 3.5.2.2 Treatment of Exposed Surfaces
 - 3.5.2.3 Curing
- 3.6 BLOCK-OUT CONCRETE
 - 3.6.1 Composition and Proportions
 - 3.6.2 Placing Block-out Concrete
- 3.7 TESTS AND INSPECTIONS
 - 3.7.1 General
 - 3.7.2 Testing and Inspection Requirements
 - 3.7.2.1 Fine Aggregate
 - 3.7.2.1.1 Grading
 - 3.7.2.1.2 Fineness Modulus Control Chart
 - 3.7.2.1.3 Corrective Action for Fine Aggregate Grading
 - 3.7.2.1.4 Moisture Content Testing
 - 3.7.2.1.5 Moisture Content Corrective Action

- 3.7.2.2 Coarse Aggregate
 - 3.7.2.2.1 Grading
 - 3.7.2.2.2 Corrective Action for Grading
 - 3.7.2.2.3 Coarse Aggregate Moisture Content
 - 3.7.2.2.4 Coarse Aggregate Moisture Corrective Action
 - 3.7.2.2.5 Particle Shape Testing
 - 3.7.2.2.6 Particle Shape Corrective Action
 - 3.7.2.2.7 Material Finer than the 75- μ m No. 200 Sieve
 - 3.7.2.2.8 Corrective Action for Material Finer than the 75- μ m No. 200 Sieve
- 3.7.2.3 Quality of Aggregates
 - 3.7.2.3.1 Frequency of Quality Tests
 - 3.7.2.3.2 Corrective Action for Aggregate Quality
- 3.7.2.4 Scales
 - 3.7.2.4.1 Weighing Accuracy
 - 3.7.2.4.2 Batching and Recording Accuracy
 - 3.7.2.4.3 Scales Corrective Action
- 3.7.2.5 Batch-Plant Control
- 3.7.2.6 Concrete
 - 3.7.2.6.1 Air Content
 - 3.7.2.6.2 Air Content Corrective Action
 - 3.7.2.6.3 Slump Testing
 - 3.7.2.6.4 Slump Corrective Action
 - 3.7.2.6.5 Compression Test Cylinders
- 3.7.2.7 Inspection Before Placing
- 3.7.2.8 Concrete Placement
 - 3.7.2.8.1 Placing Inspection
 - 3.7.2.8.2 Placing Corrective Action
- 3.7.2.9 Vibrators
 - 3.7.2.9.1 Vibrator Testing and Use
 - 3.7.2.9.2 Vibrator Corrective Action
- 3.7.2.10 Curing
 - 3.7.2.10.1 Moist Curing Inspections
 - 3.7.2.10.2 Moist Curing Corrective Action
 - 3.7.2.10.3 Membrane Curing Inspection
 - 3.7.2.10.4 Membrane Curing Corrective Action
 - 3.7.2.10.5 Sheet Curing Inspection
 - 3.7.2.10.6 Sheet Curing Corrective Action
- 3.7.2.11 Cold Weather Protection and Sealed Insulation Curing
- 3.7.2.12 Cold Weather Protection Corrective Action
- 3.7.2.13 Mixer Uniformity
 - 3.7.2.13.1 Stationary Mixers
 - 3.7.2.13.2 Truck Mixers
- 3.7.2.14 Mixer Uniformity Corrective Action
- 3.7.3 Reports

-- End of Section Table of Contents --

USACE / NAVFAC / AFCEC UFGS-03 70 00 (February 2010)
Change 2 - 08/20

Preparing Activity: USACE Superseding
UFGS-03 70 00 (April 2006)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated April 2025

SECTION 03 70 00

MASS CONCRETE
02/10, CHG 2: 08/20

NOTE: This guide specification covers the requirements for large projects containing mass concrete or mass and structural concrete, and major projects where the government retains the responsibility for concrete mixture proportioning. This section was originally developed for USACE Civil Works projects.

Adhere to UFC 1-300-02 Unified Facilities Guide Specifications (UFGS) Format Standard when editing this guide specification or preparing new project specification sections. Edit this guide specification for project specific requirements by adding, deleting, or revising text. For bracketed items, choose applicable item(s) or insert appropriate information.

Remove information and requirements not required in respective project, whether or not brackets are present.

Comments, suggestions and recommended changes for this guide specification are welcome and should be submitted as a Criteria Change Request (CCR).

PART 1 GENERAL

NOTE: The content of this specification is such that guidance given in EM 1110-2-2000, "Standard Practice for Concrete" is applicable.

1.1 UNIT PRICES

NOTE: If Section 01 20 00 PRICE AND PAYMENT PROCEDURES is included in the project

specifications, this paragraph title (UNIT PRICES) should be deleted from this section and the remaining appropriately edited subparagraphs below should be inserted into Section 01 20 00.

Consult the concrete materials design memorandum to choose the appropriate cementitious materials and admixtures for measurement and payment.

When silica fume is used in the project, the Specifier should include both bid items, "Silica Fume, Dry" and "Silica Fume, Slurry", to give the Contractor the option of supplying the material in dry form or in slurry form.

1.1.1 Concrete for [_____]

NOTE: Repeat this bid item and its respective subparagraphs for each bid item of concrete, renumbering the bid items appropriately.

1.1.1.1 Payment

Payment will be made for costs associated with completing the concrete work for concrete placed in the [_____]. However, these costs will not include the cost of the cement, pozzolan, [slag,] reinforcement, [water-reducing admixture,] [high range water reducer,] [silica fume,] and embedded parts that are specified to be paid for separately. No payment will be made for concrete, as such, that is placed in structures of which payment is made as a lump sum.

1.1.1.2 Measurement

Concrete will be measurement for payment based upon the actual volume of concrete within the pay lines of the structures as indicated on the drawings. Measure concrete placed against the sides of any excavation without the use of intervening forms only within the pay lines of the structure. Do not make deductions for rounded or beveled edges, space occupied by metal work, electrical conduits or reinforcing steel, nor for voids or embedded items that are either less than 0.14 cubic meters 5 cubic feet in volume or 0.09 square meter 1 square foot in cross section.

1.1.1.3 Unit of Measure

Unit of measure: cubic meters yards.

[1.1.2 Concrete in Blockouts

[1.1.2.1 Payment

Payment will be made for costs associated with concrete placed in the blockouts.

] [1.1.2.2 Measurement

Concrete will be measurement for payment based upon the actual volume of

concrete placed in the blockouts as indicated on the drawings.

][1.1.2.3 Unit of Measure

Unit of measure: cubic meters yards.

]1.1.3 Portland Cement

NOTE: List all other cementitious materials (except pozzolan), such as portland-pozzolan cement, slag cement, or portland blast-furnace cement, separately similar to this bid item, and the bid items renumbered appropriately.

1.1.3.1 Payment

Payment will be made for costs associated with Portland cement, which includes the cost of required unloading, hauling, handling, and storage at the site, of all portland cement used in the work.

1.1.3.2 Measurement

Portland cement will be measured for payment based upon the number of tons of portland cement used unless specifically excepted, wasted, or used for the convenience of the Contractor. The quantity to be paid for will be determined by multiplying the approved batch weight in kg/cubic meter pounds/cubic yard of portland cement in each type of concrete used by the number of cubic meters yards of concrete types placed within the pay lines of the structure, as determined in accordance with the concrete bid items, and dividing by 1000 2,000.

1.1.3.3 Unit of Measure

Unit of measure: tons (metric) (2000 lb).

1.1.4 Pozzolan (Except Silica Fume)

1.1.4.1 Payment

Payment will be made for costs associated with pozzolan, which includes the cost of required unloading, hauling, handling, and storage at the site, of all pozzolan used in the concrete bid items.

1.1.4.2 Measurement

Pozzolan, except silica fume, will be measured for payment based upon the number of cubic meters feet solid volume of pozzolan used unless specifically excepted, wasted, or used for the convenience of the Contractor. The quantity to be paid for will be determined by multiplying the approved batch weight in kg/cubic meter pounds/cubic yard of pozzolan in each type of concrete used by the number of cubic meters yards of concrete of the types placed within the pay lines of the structure, as determined in accordance with the concrete bid items, and dividing by the product of the average specific gravity of the pozzolan multiplied by 1000 kg/cubic meter 62.4 pounds/cubic foot. The average specific gravity is the average of the test results for all material accepted during the period covered by the payment.

1.1.4.3 Unit of Measure

Unit of measure: cubic meters feet solid volume.

1.1.5 Ground Granulated Blast-Furnace Slag

1.1.5.1 Payment

Payment will be made for costs associated with ground granulated blast-furnace slag, which includes the cost of required unloading, hauling, handling, and storage at the site, of all ground granulated blast-furnace slag used in the concrete bid items.

1.1.5.2 Measurement

Ground granulated blast-furnace slag will be measured for payment based upon the number of tons of ground granulated blast-furnace slag used excluding the amount specifically excepted, wasted, or used for the convenience of the Contractor. The quantity to be paid for will be determined by multiplying the approved batch weight in kg/cubic meter pounds/cubic yard of ground granulated blast-furnace slag in each type of concrete used by the number of cubic meters yards of concrete types placed within the pay lines of the structure, as determined in accordance with the concrete bid items, and dividing by 1000 2,000.

1.1.5.3 Unit of Measure

Unit of measure: tons (metric) (2000 lb).

1.1.6 Water-Reducing Admixture (WRA)

1.1.6.1 Payment

[Payment will be made for costs associated with water-reducing admixture (WRA) at the applicable contract unit price per cubic meter yard of concrete containing water-reducing admixture.] [Payment will be made for costs associated with water-reducing admixture (WRA) at the applicable contract unit cost of concrete containing water-reducing admixture for:

a. "Bid Item [_____]a., first [_____] cubic meters yards."

b. "Bid Item [_____]b., all over [_____] cubic meters yards."

1.1.6.2 Measurement

Water-reducing admixture (WRA) will be measured for payment based upon the actual volume of concrete containing the admixture and within the pay lines of the structures, as determined in accordance with the concrete bid items.

1.1.6.3 Unit of Measure

Unit of measure: cubic meters yards.

1.1.7 High-Range Water-Reducing Admixture (HRWR)

1.1.7.1 Payment

[Payment will be made for costs associated with high-range water-reducing admixture (HRWR) at the applicable contract unit price per cubic meter yard of concrete containing water-reducing admixture.] [Payment will be made for costs associated with high-range water-reducing admixture (HRWR) at the applicable contract unit cost of concrete containing water-reducing admixture for:

- a. "Bid Item [_____]a., first [_____] cubic meters yards."
- b. "Bid Item [_____]b., all over [_____] cubic meters yards."

1.1.7.2 Measurement

High-Range water-reducing admixture (HRWR) will be measured for payment based upon the actual volume of concrete containing the admixture and within the pay lines of the structures, as determined in accordance with the concrete bid items.

1.1.7.3 Unit of Measure

Unit of measure: cubic meters yards.

1.1.8 Silica Fume, Dry

1.1.8.1 Payment

Payment will be made for costs associated with silica fume, dry, which includes price batching and recording equipment for dry silica fume used in the concrete bid items. Payment will be made at the contract price per kilogram hundredweight of dry silica fume for:

- a. "Bid Item [_____]a., first [_____] kilograms hundredweight."
- b. "Bid Item [_____]b., all over [_____] kilograms hundredweight."

1.1.8.2 Measurement

Silica fume, dry, will be measured for payment based upon the number of kilograms hundredweight of silica fume used in the concrete, excluding the amount wasted or used for the convenience of the Contractor. The quantity to be paid for will be determined by multiplying the weight in kilograms pounds of silica fume per cubic meter yard by the number of cubic meters yards of silica fume concrete placed within the pay lines of the structure as determined in accordance with the concrete bid items., divided by 100.

1.1.8.3 Unit of Measure

Unit of measure: kilograms hundredweight (100 pounds).

1.1.9 Silica Fume, Slurry

1.1.9.1 Payment

Payment will be made for costs associated with silica fume, slurry, which includes the cost of silica fume, slurry; providing admixtures such as

HRWR admixtures that are a component of the slurry; and furnishing storage, batching, and recording equipment for silica fume, slurry, used in the concrete bid items. Payment for silica fume, slurry, will be made at the contract price per hundredweight of dry silica fume for:

- a. "Bid Item [_____]a., first [_____] kilograms hundredweight."
- b. "Bid Item [_____]b., all over [_____] kilograms hundredweight."

][1.1.9.2 Measurement

Silica fume, slurry, will be measured for payment based upon the number of kilograms hundredweight of silica fume used in the concrete, excluding the amount wasted or used for the convenience of the Contractor. The quantity to be paid for will be determined by multiplying the weight in kilograms pounds of silica fume per cubic meter yard by the number of cubic meters yards of silica fume concrete placed within the pay lines of the structure as determined in accordance with the concrete bid items , divided by 100. The dry weight will be determined by supplier's certificate.

][1.1.9.3 Unit of Measure

Unit of measure: kilograms hundredweight (100 pounds).

][1.2 REFERENCES

NOTE: This paragraph is used to list the publications cited in the text of the guide specification. The publications are referred to in the text by basic designation only and listed in this paragraph by organization, designation, date, and title.

Use the Reference Wizard's Check Reference feature when you add a Reference Identifier (RID) outside of the Section's Reference Article to automatically place the reference in the Reference Article. Also use the Reference Wizard's Check Reference feature to update the issue dates.

References not used in the text will automatically be deleted from this section of the project specification when you choose to reconcile references in the publish print process.

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

AMERICAN ASSOCIATION OF STATE HIGHWAY AND TRANSPORTATION OFFICIALS
(AASHTO)

AASHTO M 182

(2005; R 2021) Standard Specification for
Burlap Cloth Made from Jute or Kenaf and
Cotton Mats

AMERICAN CONCRETE INSTITUTE (ACI)

ACI 117	(2010; R 2015) Specifications for Tolerances for Concrete Construction and Materials and Commentary
ACI 214R	(2011) Evaluation of Strength Test Results of Concrete
ACI 305R	(2020) Guide to Hot Weather Concreting

ASTM INTERNATIONAL (ASTM)

ASTM C31/C31M	(2025a) Standard Practice for Making and Curing Concrete Test Specimens in the Field
ASTM C39/C39M	(2024) Standard Test Method for Compressive Strength of Cylindrical Concrete Specimens
ASTM C40/C40M	(2020) Standard Test Method for Organic Impurities in Fine Aggregates for Concrete
ASTM C87/C87M	(2023) Standard Test Method for Effect of Organic Impurities in Fine Aggregate on Strength of Mortar
ASTM C94/C94M	(2024d) Standard Specification for Ready-Mixed Concrete
ASTM C117	(2023) Standard Test Method for Materials Finer than 75-um (No. 200) Sieve in Mineral Aggregates by Washing
ASTM C123/C123M	(2023) Standard Test Method for Lightweight Particles in Aggregate
ASTM C127	(2024) Standard Test Method for Density, Relative Density (Specific Gravity), and Absorption of Coarse Aggregate
ASTM C128	(2022) Standard Test Method for Density, Relative Density (Specific Gravity), and Absorption of Fine Aggregate
ASTM C131/C131M	(2020) Standard Test Method for Resistance to Degradation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine
ASTM C136/C136M	(2019) Standard Test Method for Sieve Analysis of Fine and Coarse Aggregates
ASTM C142/C142M	(2017; R 2023) Standard Test Method for Clay Lumps and Friable Particles in Aggregates
ASTM C143/C143M	(2020) Standard Test Method for Slump of Hydraulic-Cement Concrete

ASTM C150/C150M	(2024) Standard Specification for Portland Cement
ASTM C171	(2020) Standard Specification for Sheet Materials for Curing Concrete
ASTM C172/C172M	(2017) Standard Practice for Sampling Freshly Mixed Concrete
ASTM C231/C231M	(2024) Standard Test Method for Air Content of Freshly Mixed Concrete by the Pressure Method
ASTM C260/C260M	(2024) Standard Specification for Air-Entraining Admixtures for Concrete
ASTM C295/C295M	(2019) Standard Guide for Petrographic Examination of Aggregates for Concrete
ASTM C309	(2019) Standard Specification for Liquid Membrane-Forming Compounds for Curing Concrete
ASTM C441/C441M	(2017) Standard Test Method for Effectiveness of Pozzolans or Ground Blast-Furnace Slag in Preventing Excessive Expansion of Concrete Due to the Alkali-Silica Reaction
ASTM C494/C494M	(2024) Standard Specification for Chemical Admixtures for Concrete
ASTM C535	(2016; R 2024) Standard Test Method for Resistance to Degradation of Large-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine
ASTM C566	(2013) Standard Test Method for Total Evaporable Moisture Content of Aggregate by Drying
ASTM C618	(2023; E 2023) Standard Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
ASTM C666/C666M	(2015) Resistance of Concrete to Rapid Freezing and Thawing
ASTM C881/C881M	(2020a) Standard Specification for Epoxy-Resin-Base Bonding Systems for Concrete
ASTM C928/C928M	(2020a) Standard Specification for Packaged, Dry, Rapid-Hardening Cementitious Materials for Concrete Repairs
ASTM C937	(2023) Grout Fluidifier for Preplaced-Aggregate Concrete

ASTM C989/C989M	(2024) Standard Specification for Slag Cement for Use in Concrete and Mortars
ASTM C1059/C1059M	(2024) Standard Specification for Latex Agents for Bonding Fresh to Hardened Concrete
ASTM C1064/C1064M	(2023) Standard Test Method for Temperature of Freshly Mixed Hydraulic-Cement Concrete
ASTM C1077	(2024) Standard Practice for Agencies Testing Concrete and Concrete Aggregates for Use in Construction and Criteria for Testing Agency Evaluation
ASTM C1107/C1107M	(2020) Standard Specification for Packaged Dry, Hydraulic-Cement Grout (Nonshrink)
ASTM C1240	(2020) Standard Specification for Silica Fume Used in Cementitious Mixtures
ASTM C1260	(2023) Standard Test Method for Potential Alkali Reactivity of Aggregates (Mortar-Bar Method)
ASTM C1567	(2023) Standard Test Method for Potential Alkali-Silica Reactivity of Combinations of Cementitious Materials and Aggregate (Accelerated Mortar-Bar Method)
ASTM D4791	(2019) Flat Particles, Elongated Particles, or Flat and Elongated Particles in Coarse Aggregate
ASTM E11	(2024) Standard Specification for Woven Wire Test Sieve Cloth and Test Sieves

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST)

NIST HB 44	(2018) Specifications, Tolerances, and Other Technical Requirements for Weighing and Measuring Devices
------------	--

NATIONAL READY MIXED CONCRETE ASSOCIATION (NRMCA)

NRMCA CPMB 100	(2000; R 2006) Concrete Plant Standards
----------------	---

U.S. ARMY CORPS OF ENGINEERS (USACE)

COE CRD-C 55	(1992) Test Method for Within-Batch Uniformity of Freshly Mixed Concrete
COE CRD-C 94	(1995) Corps of Engineers Specification for Surface Retarders
COE CRD-C 100	(1975) Method of Sampling Concrete Aggregate and Aggregate Sources, and

	Selection of Material for Testing
COE CRD-C 104	(1980) Method of Calculation of the Fineness Modulus of Aggregate
COE CRD-C 114	(1997) Test Method for Soundness of Aggregates by Freezing and Thawing of Concrete Specimens
COE CRD-C 130	(2001) Standard Recommended Practice for Estimating Scratch Hardness of Coarse Aggregate Particles
COE CRD-C 143	(1962) Specifications for Meters for Automatic Indication of Moisture in Fine Aggregate
COE CRD-C 144	(1992) Standard Test Method for Resistance of Rock to Freezing and Thawing
COE CRD-C 400	(1963) Requirements for Water for Use in Mixing or Curing Concrete
COE CRD-C 521	(1981) Standard Test Method for Frequency and Amplitude of Vibrators for Concrete

1.3 SUBMITTALS

NOTE: Review submittal description (SD) definitions in Section 01 33 00 SUBMITTAL PROCEDURES and edit the following list, and corresponding submittal items in the text, to reflect only the submittals required for the project. The Guide Specification technical editors have classified those items that require Government approval, due to their complexity or criticality, with a "G." Generally, other submittal items can be reviewed by the Contractor's Quality Control System. Only add a "G" to an item, if the submittal is sufficiently important or complex in context of the project.

For Army projects, fill in the empty brackets following the "G" classification, with a code of up to three characters to indicate the approving authority. Codes for Army projects using the Resident Management System (RMS) are: "AE" for Architect-Engineer; "DO" for District Office (Engineering Division or other organization in the District Office); "AO" for Area Office; "RO" for Resident Office; and "PO" for Project Office. Codes following the "G" typically are not used for Navy and Air Force projects.

The "S" classification indicates submittals required as proof of compliance for sustainability Guiding Principles Validation or Third Party Certification and as described in Section 01 33 00 SUBMITTAL PROCEDURES.

Government approval is required for submittals with a "G" or "S" classification. Submittals not having a "G" or "S" classification are for Contractor Quality Control approval. Submittals not having a "G" or "S" classification are for information only. When used, a code following the "G" classification identifies the office that will review the submittal for the Government. Submit the following in accordance with Section 01 33 00 SUBMITTAL PROCEDURES:

SD-02 Shop Drawings

Concrete Lifts; G, [_____]

Equipment; G, [_____]

SD-03 Product Data

Batch Plant; G, [_____]

Mixers

Construction Joint Treatment; G, [_____]

Curing and Protection; G, [_____]

Cold-Weather Protection; G, [_____]

Hot-weather Placing; G, [_____]

Special Temperature-Controlled Concrete; G, [_____]

SD-07 Certificates

Sheet Curing

Nonshrink Grout; G, [_____]

Bonding Agents

Expansive Admixture

1.4 QUALITY ASSURANCE

1.4.1 Government Preconstruction Testing

NOTE: Contact the Engineer Research and Development Center, 3909 Halls Ferry Road, Vicksburg, Mississippi 39180-6199, ATTN: CEERD-SC for guidance in filling in the blanks.

1.4.1.1 Aggregate Sources

The aggregate sources listed in paragraph COMMERCIAL CONCRETE AGGREGATE SOURCES, have been tested, and at the time testing was performed, these sources were capable of producing materials of the quality and quantity required for this project provided suitable processing is performed.

Deliver samples from any source selected consisting of no less than [_____] kg pounds of each size of coarse aggregate and [_____] kg pounds of fine aggregate, taken under the supervision of the Contracting Officer in accordance with COE CRD-C 100, to [_____] within 15 days after notice to proceed. Sampling and shipment of samples is the Contractor's expense. [_____] days will be required to complete evaluation of the aggregates. Testing will be performed by the Government in accordance with the applicable COE CRD-C or ASTM test methods. Tests to which aggregate may be subjected are listed in paragraph AGGREGATES. The material from the proposed source must meet the quality requirements of this paragraph to be used for the project. The Government test data and other information on aggregate quality of those sources listed in paragraph COMMERCIAL CONCRETE AGGREGATE SOURCES, and are available for review in the District Office. Quality assurance testing of aggregates by the Government does not relieve the Contractor of quality control requirements.

1.4.1.2 Cementitious Materials, Admixtures, and Curing Materials

Notify the Contracting Officer of the source, brand name, type, and quantity of all materials (other than aggregates) to be used in the manufacture and curing of the concrete at least 60 days in advance of submitting samples for mixture proportioning studies. Assist the Contracting Officer in obtaining samples of each material. Sampling and testing as determined appropriate will be performed by and at the expense of the Government. If cement or pozzolan are to be obtained from more than one source, state the estimated amount of cement or pozzolan to be obtained from each source and the proposed schedule of shipments in the notification. When pozzolan other than fly ash is used, it must be from one source.

1.4.1.3 Materials for Mixture-Proportioning Studies

NOTE: Contact the Engineer Research and Development Center, 3909 Halls Ferry Road, Vicksburg, Mississippi 39180-6199, ATTN: CEERD-SC to fill in the blanks. At the end of the following table, insert other cementitious materials, including silica fume, as appropriate.

At least [_____] days in advance of the time when placing of concrete is expected to begin, deliver samples of representative materials proposed for this project and meeting all the requirements of this specification to [_____] by the Contractor at its expense. Take samples of aggregates under the supervision of the Contracting Officer in accordance with COE CRD-C 100, accompanied by test reports indicating conformance with grading and quality requirements hereinafter specified. Provide samples of materials other than aggregates that are representative of those proposed for the project and submit accompanied by manufacturer's test reports indicating compliance with applicable specified requirements. Quantities of materials required are as follows:

MATERIAL	QUANTITY
150 mm 6 inch nominal maximum-size coarse aggregate	[_____] kg pounds
75 mm 3 inch nominal maximum-size coarse aggregate	[_____] kg pounds
37.5 mm 1-1/2 inch nominal maximum-size coarse aggregate	[_____] kg pounds
19 mm 3/4 inch nominal maximum-size coarse aggregate	[_____] kg pounds
Fine aggregate	[_____] kg pounds
Cement	[_____] kg pounds
Pozzolans	[_____] cubic m feet
Air-entraining admixture	[_____] L quarts
Other admixtures (each)	[_____] L gallons

Mixture-proportioning studies will be made by the Government.

1.4.2 Construction Testing by the Government

1.4.2.1 General

The Government will sample and test cementitious materials, admixtures, aggregates, and concrete during construction as considered appropriate to determine compliance with the specifications. Provide facilities and labor as may be necessary for procurement of representative test samples. Samples of aggregates will be obtained at the point of batching in accordance with COE CRD-C 100. Slump and air content will be determined in accordance with ASTM C143/C143M and ASTM C231/C231M, respectively, except the point of sampling will be as directed. Compression test specimens will be made and laboratory cured in accordance with ASTM C31/C31M and will be tested in accordance with ASTM C39/C39M.

1.4.2.2 Testing Aggregates

Testing performed by the Government will not relieve the Contractor of its responsibility for testing as appropriate for quality control. During construction, aggregates will be sampled for acceptance testing as delivered to the mixer to determine compliance with specification provisions. Provide necessary facilities and labor for the ready procurement of representative samples under Contracting Officer supervision. The Government will test such samples at its expense using appropriate COE CRD-C and ASTM methods.

1.4.2.3 Cementitious Materials

Furnish cement or pozzolan or both from a prequalified source or, if not, it (they) will be sampled at the mill, shipping point, or site of the work by the Contracting Office. A list of prequalified cement sources and prequalified pozzolan sources is available from the Director, U.S. Army Corps of Engineers, Engineer Research and Development Center - Structures

Laboratory, 3909 Halls Ferry Road, Vicksburg, MS 39180-6199, ATTN: CEERD-SC. If tests prove that a material which has been delivered is unsatisfactory, promptly remove it from the site of the work. Cementitious materials that have not been used within 6 months after being tested will be retested by the Government at the expense of the Contractor when directed.

1.4.2.4 Cement from Prequalified Sources

Deliver and use cement directly from a mill of a producer designated as a prequalified source for the type of cement being used. Samples of cement for quality-assurance testing will be taken at the project site or cement-producing plant by the Contracting Officer for testing at the expense of the Government. Furnish a copy of the mill tests from the cement manufacturer to the Contracting Officer for each lot.

1.4.2.5 Pozzolan from Prequalified Sources

Deliver and use pozzolan directly from a producer designated as a prequalified source. Samples of pozzolan for check testing will be taken at the project site by the Contracting Officer for testing at the expense of the Government. Furnish a copy of the test results from the pozzolan manufacturer to the Contracting Officer for each lot.

1.4.2.6 Cement from Nonprequalified Sources

NOTE: The Contractor's expense rate for excess testing of cement and pozzolan by the Government can be obtained from the Structures Laboratory, U.S. Army Engineer Waterways Experiment Station (CEWES-SC-MP), 3909 Halls Ferry Road, Vicksburg, MS 39180-6199.

Cement, if not from a prequalified source, will be sampled and tested by or under the supervision of the Contracting Officer and at Government expense. Do not use cement until notice has been given by the Contracting Officer that test results are satisfactory. In the event of failure, the cement may be resampled and tested at the request of the Contractor and at the Contractor's expense. When the point of sampling is other than at the site of the work, the fill gate or gates of the sampled bin will be sealed and kept sealed until shipment from the bin has been completed. The fill gate or gates of conveyances used in shipment will be sealed by or under the supervision of the Contracting Officer. Conveyances will not be accepted at the site of the work unless received with all seals intact. If tested cement is rehandled at transfer points, the extra cost of inspection will be at the Contractor's expense. The cost of testing cement excess to project requirements will also be at the Contractor's expense and will be deducted from payments due the Contractor at a rate of [_____] dollars per test.

1.4.2.7 Pozzolan from Nonprequalified Sources

Pozzolan, if not from a prequalified source, will be sampled at the source or at the site of the work and will be stored in sealed bins pending completion of acceptance tests. Pozzolan may be resampled at the site when determined necessary. All sampling and testing will be performed by and at the expense of the Government. Release for shipment and approval

for use will be based on compliance with seven day lime-pozzolan strength requirements and other physical, chemical, and uniformity requirements for which tests can be completed by the time the seven day lime-pozzolan strength test is completed. Release for shipment and approval for use on this basis will be contingent on continuing compliance with the other requirements of the specifications. If test results of a bin fail, the contents may be resampled and tested at the Contractor's expense. The Government will supervise or perform the unsealing and resealing of bins and shipping conveyances. If tested pozzolan is rehandled at transfer points, the extra cost of inspection will be at the Contractor's expense. The cost of testing excess pozzolan in excess of project requirements will be at the Contractor's expense at a rate of [_____] dollars per test. The amount will be deducted from payment to the Contractor.

[1.4.2.8 Ground Granulated Blast-Furnace Slag

NOTE: If any other cementitious materials, including silica fume, are to be allowed, an additional paragraph should be added similar to this paragraph, with the name of the cementitious material substituted for "Ground Granulated Blast-Furnace Slag".

Ground granulated blast-furnace slag will be sampled and tests at the mill or shipping point by and at the expense of the Government to determine that the material meets the requirements of the specification under which it is furnished. Do not use ground granulated blast-furnace slag until notice of acceptance has been given by the Contracting Officer. Ground granulated blast-furnace slag will be subject to check testing from samples obtained at the project site, as scheduled, and such sampling will be by or under the supervision of the Contracting Officer and at Government expense. Remove material not meeting specifications promptly from the site of work.

]1.4.2.9 Chemical Admixtures

Provide satisfactory facilities for ready procurement of test samples. All sampling and testing of a chemical admixture will be by and at the expense of the Government. Tests will be conducted using samples of materials proposed for the project.

1.5 DELIVERY, STORAGE, AND HANDLING

1.5.1 Cementitious Materials

1.5.1.1 Transportation

When bulk cement, pozzolan, dry silica fume, or ground granulated blast-furnace slag is not unloaded from primary carriers directly into weather-tight hoppers at the batching plant, accomplish transportation from the railhead, mill, or intermediate storage to the batching plant in weather-tight trucks, conveyors, or other means that will protect the material from exposure to moisture. Transportation facilities for dry bulk silica fume must be approved in advance.

1.5.1.2 Storage

Furnish cementitious materials in bulk except that cement used for finishing and patching may be packaged, and silica fume may be packaged or in slurry form. Immediately upon receipt at the site of the work, store all cementitious materials in separate dry, weather-tight, and properly ventilated structures. All storage facilities must permit easy access for inspection and identification. Maintain sufficient materials in storage to complete any lift of concrete started. In order that cement may not become unduly aged after delivery, use any cement that has been stored at the site for 60 days or more before using cement of lesser age. Do not use silica fume in slurry form that has been in storage at the project site for longer than recommended by the manufacturer or that has been subjected to freezing in the work and remove from the site.

1.5.1.3 Separation of Materials

Provide separate facilities for unloading, transporting, and handling each cementitious material. Provide separate appropriate storage facilities for each type of cement and each source of pozzolan, dry bulk silica fume, or slag. Plainly mark the contents of each storage facility marked with a large permanent sign posted near the loading port.

1.5.2 Aggregates Storage

Store fine aggregate and each size of coarse aggregate in separate size groups adjacent to the batch plant and in such a manner as to prevent the intermingling of size groups or the inclusion of foreign materials in the concrete. Maintain sufficient fine and coarse aggregate at the site at all times to permit continuous placement and completion of any lift of concrete started.

PART 2 PRODUCTS

2.1 SYSTEM DESCRIPTION

Provide concrete composed of cementitious materials, water, fine and coarse aggregates, and admixtures. Use cementitious materials that are [portland cement], [portland cement in combination with pozzolan], [portland cement in combination with [____]], [portland blast-furnace slag cement] [portland cement in combination with ground granulated blast-furnace slag] [portland cement in combination with silica fume] [portland-pozzolan cement]. Use an air-entraining admixture [or an air-entraining admixture plus] [a retarding admixture], [a WRA], [a HRWRA], [or an accelerating admixture]. A retarding admixture may be used at the request of the Contractor when approved. Do not use chemical admixtures other than those listed above.

2.1.1 Proportioning Responsibility

**NOTE: The last optional sentence should be used if
slow strength gain cementitious materials are to be
used.**

The concrete mixtures will be proportioned by the Contracting Officer. [Preliminary mixture-proportioning studies or thermal studies which include mixture proportions are available for review in the District

Office.] [Some mixtures, especially those containing higher amounts of pozzolans, may have slow strength gain which may impact form design and form removal time.]

2.1.2 Design Requirements

**NOTE: See the concrete materials design memorandum
to select the optional cementitious materials.**

The proportions of all material entering into each concrete mixture will be furnished to the Contractor. The proportions will be changed by the Contracting Officer as necessary. Make adjustments to the batch weights of aggregates and water as necessary to compensate for free moisture in the aggregates. Adjust the quantity of air-entrainment admixture to maintain the specified air content.

2.1.3 Air Content

Determine the air content by volume by **ASTM C231/C231M**. When the nominal maximum size of coarse aggregate is **37.5 mm 1-1/2 inches** or larger, the air content of the sample measured in accordance with **ASTM C231/C231M** must be **5-1/2 ± 1-1/2 percent**. When the nominal maximum-size coarse aggregate is **19 mm 3/4 inch**, the air content must be **6 ± 1 percent**. The specified air content must be present in the concrete when the concrete has been placed in the forms.

2.1.4 Slump

Determine slump in accordance with **ASTM C143/C143M** of **50 mm 2 inches ± 25 mm 1 inch** for massive features and between **25 and 100 mm 1 and 4 inches** for all others except where placement by pump is approved, in which case the slump must be **114 mm 4-1/2 ± 38 mm 1-1/2 inches**. In addition, the range of each set of two consecutive tests for each mixture must be no more than **50 mm 2 inches**. The above specified slump is that required at the forms.

2.1.5 Construction Tolerances

Make level and grade tolerance measurements of slabs as soon as possible after finishing. When forms or shoring are used, make the measurements prior to removal. Tolerances are not cumulative. The most restrictive tolerance controls. Do not allow tolerances to extend the structure beyond legal boundaries. Except as specified otherwise, plus tolerance increases the amount or dimension to which it applies, or raises a level alignment and minus tolerance decreases the amount or dimension to which it applied, or lowers a level alignment. A tolerance without sign means plus or minus. Where only one signed tolerance is specified, there is no limit in the other direction. Finish unformed finished surfaces subject to high-velocity flow (**12 m/s**) (**40 fps**) to meet the tolerances for A-HV surfaces specified in Table, "TOLERANCES FOR FINISHED FORMED CONCRETE SURFACES".

2.1.6 Tabulations and Definitions

**NOTE: Delete any of the following tables that are
not applicable. Most projects will require several**

tables to cover all parts of the structure.

The definitions of the terms used in the following tabulations are used as defined and used in ACI 117. Make level and grade tolerance measurements of slabs as soon as possible after finishing.

TOLERANCES FOR FOUNDATIONS		
(1)	Lateral alignment	
	As cast to the center of gravity as specified; 0.02 times width of footing in direction of misplacement but not more than	50 mm 2 inches
	Supporting masonry construction	13 mm 1/2 inch
(2)	Level alignment	
	Top of footings supporting masonry	13 mm 1/2 inch
	Top of other footings	+13 mm, -50 mm +1/2 inch, -2 inch
(3)	Cross-sectional dimensions	
	Horizontal dimensions of formed members	+50 mm, -13 mm +2 in., -1/2 in.
	Horizontal dimensions of unformed members cast against soil	
	600 mm 2 feet or less	+75 mm, -13 mm +3 in., -1/2 in.
	Greater than 600 mm 2 feet but less than 1800 mm 6 feet	+150 mm, -13 mm +6 in., -1/2 in.
	Over 1800 mm 6 feet	+300 mm, -13 mm +12 in., -1/2 in.
	Vertical dimension (thickness)	-5 percent
(4)	Relative alignment	
	Slope of footing side and top surfaces with respect to the specified plan	25 mm/3000 mm 1 in./10 ft

TOLERANCES FOR CAST-IN-PLACE REINFORCED CONCRETE FOR BUILDINGS		
(1)	Vertical alignment	
	For heights 30 m 100 feet	
	Lines, surfaces, and arrises	25 mm 1 inch
	Outside corner of exposed corner columns and control joint grooves in concrete exposed to view	13 mm 1/2 inch
	For heights greater than 30 m 100 ft	
	Lines, surfaces, and arrises, 1/1,000 times the height at any point but not more than	150 mm 6 inches
	Outside corner of exposed corner columns and control joint grooves in concrete, 1/2,000 times the height at any point but not more than	75 mm 3 inches
(2)	Lateral alignment	
	Members	25 mm 1 inch
	In slabs, centerline location of openings 12 in. or smaller and edge location of larger openings	13 mm 1/2 inch
	Sawcuts, joints, and weakened plane embedment in slabs	19 mm 3/4 inch
(3)	Level alignment	
	Top of slabs	
	Elevation of slabs-on-grade	19 mm 3/4 inch
	Elevation of top surfaces of formed slabs before removal of supporting shores	19 mm 3/4 inch
	Elevation of formed surfaces before removal of shores	19 mm 3/4 inch
	Lintels, sills, parapets, horizontal grooves, and other lines exposed to view	13 mm 1/2 inch
(4)	Cross-sectional dimensions	
	Members, such as columns, beams, piers, walls (thickness only) and slabs (thickness only)	
	300 mm 12 inches dimension or less	+10, -6 mm +3/8, -1/4 inch
	More than 300 mm 12 inches but not over 900 mm 3 feet dimension	+13, -10 mm +1/2, -3/8 inch
	Over 900 mm 3 feet dimension	+25, -19 mm +1, -3/4 inch

TOLERANCES FOR CAST-IN-PLACE REINFORCED CONCRETE FOR BUILDINGS		
(5)	Relative alignment	
	Stairs	
		Different in height between adjacent risers
		3 mm1/8 inch
		Different in width between adjacent treads
		6 mm1/4 inch
	Grooves	
		Specified width 50 mm 2 inches or less
		3 mm1/8 inch
		Specified width more than 50 mm 2 inches but not more than 300 mm 12 inches
		6 mm1/4 inch
	Sawcuts, joints, and weakened plane on slab	
		Lateral, gradual
		19 mm in 3000 mm3/4 inch in 10 feet
		Lateral, abrupt
		0 mm inch
(6)	Openings through members	
	Cross-sectional size of opening	+25 mm, -6 mm +1, -1/4 inch
	Location of centerline of opening	13 mm1/2 inch
TOLERANCE FOR FINISHED FORMED CONCRETE SURFACES		
(1)	Vertical alignment: Formed surfaces slope with respect to the specified plane	
	Vertical alignment of outside corner of exposed corner columns and control joint grooves in concrete exposed to view	7 mm in 3000 mm 1/4 in. in 10 ft
	All other conditions	10 mm in 3000 mm 3/8 in. in 10 ft

TOLERANCE FOR FINISHED FORMED CONCRETE SURFACES		
(2)	Abrupt variation: The offset between concrete surfaces under adjacent pieces of formwork for the following classes of surface: (For Class A-HV, positive means raise of elevation in the direction of waterflow, negative means drop of elevation in the direction of waterflow)	
	Class A-HV, in the direction of waterflow	+0, -3 mm -1/8 inch
	*Class A-HV, perpendicular to the direction of waterflow	3 mm1/8 inch
	Class A	3 mm1/8 inch
	Class B	6 mm1/4 inch
	Class C	6 mm1/4 inch
	Class D	25 mm1 inch
(3)	Gradual variation: Surface finish tolerances as measured by placing a freestanding (unleveled), 1.5 m 5 foot straightedge for plane surface or curved template for curved surface anywhere on the surface and allowing it to rest upon two high spots within 72 hr after concrete placement. The gap at any point between the straightedge or template and the surface must not exceed:	
	*Class A (including Class A-HV)	3 mm1/8 inch
	Class B	6 mm1/4 inch
	Class C	13 mm1/2 inch
	Class D	25 mm1 inch
*Includes any high-velocity flow surface.		
TOLERANCES FOR CAST-IN-PLACE, VERTICALLY SLIPFORMED BUILDING ELEMENTS		
(1)	Translation and rotation from a fixed point at the base of the structure:	
	For heights 30 m 100 feet or less	50 mm2 inches
	For heights greater than 30 m 100 feet, 1/600 times the height but not more than	205 mm8 inches
(2)	Lateral alignment	
	Between adjacent elements	50 mm2 inches
(3)	Cross-sectional dimensions	
	Wall thickness	+19 mm, -10 mm +3/4 inch, -3/8 inch

TOLERANCES FOR CAST-IN-PLACE, VERTICALLY SLIPFORMED BUILDING ELEMENTS			
(4)	Relative alignment		
	Formed surface slope with respect to the specified plane		19 mm in 3000 mm 3/4 in. in 10 ft
TOLERANCES FOR MASS CONCRETE STRUCTURES OTHER THAN BUILDINGS			
(1)	Vertical alignment		
	Visible surfaces		30 mm1-1/4 inch
	Concealed surfaces		65 mm2-1/2 inches
	Side walls for radial gates and similar watertight joints		5 mm3/16 inch
(2)	Lateral alignment		
	Visible surfaces		30 mm1-1/4 inch
	Concealed surfaces		65 mm2-1/2 inches
(3)	Level alignment		
	Visible flatwork and formed surfaces		13 mm1/2 inch
	Concealed flatwork and formed surfaces		25 mm1 inch
	Sills for radial gates and similar watertight joints		5 mm3/16 inch
(4)	Relative alignment: Formed surface slope with respect to the specified plane		
	Slopes in lateral and level alignments		
		Visible surfaces	7 mm in 3000 mm 1/4 in. in 10 ft
		Concealed surfaces	13 mm in 3000 mm 1/2 in. in 10 ft
	Slopes in vertical alignment		
		Visible surfaces	13 mm in 3000 mm 1/2 in. in 10 ft
		Concealed surfaces	25 mm in 3000 mm 1 in. in 10 ft

TOLERANCES FOR CANAL LINING		
(1)	Lateral alignment	
	Alignment of tangents	50 mm 2 inches
	Alignment of curves	100 mm 4 inches
	Width of section at any height	$0.0025W + 25 \text{ mm}$ 1 inch
(2)	Level alignment	
	Profile grade	25 mm 1 inch
	Surface of invert	6 mm 1/4 inch
	Surface of side slope	13 mm 1/2 inch
	Height of lining	$0.005H + 25 \text{ mm}$ 1 inch
(3)	Cross-sectional dimensions	
	Thickness of lining cross section: percent of specified thickness provided average thickness is maintained as determined by daily batch volumes	10
TOLERANCES FOR TUNNEL LININGS, CONDUITS, AND FILLING AND EMPTYING CULVERTS		
(1)	Lateral alignment	
	Centerline alignment	
	Water conveying tunnels, conduits, and culverts	13 mm 1/2 inch
	Other	25 mm 1 inch
	Inside dimensions	0.005 times inside dimension
(2)	Level alignment	
	Profile grade	
	Water conveying tunnels, conduits, and culverts	13 mm 1/2 inch
	Other	25 mm 1 inch
	Surface of invert	6 mm 1/4 inch
	Surface of side slope	13 mm 1/2 inch

(3)	Cross-sectional dimension	
	Thickness at any point	
	Tunnel and culvert lining	-0 mm inch
	Conduits	+5 percent thickness but not less than 13 mm 1/2 inch
		-2.5 percent thickness but not less than 6 mm 1/4 inch

2.2 MATERIALS

2.2.1 Cementitious Materials

NOTE: See the appropriate concrete aggregates design memorandum or thermal study to select the proper requirements for cementitious materials options, pozzolan, and silica fume.

2.2.1.1 Portland Cement

Provide portland cement conforming to **ASTM C150/C150M**, Type [____], [low-alkali when used with aggregates listed to require it in paragraph COMMERCIAL CONCRETE AGGREGATE SOURCES below, or when directed if a nonlisted source is permitted.] [including the heat of hydration requirement at 7 days] [including false-set requirement]. [In lieu of low-alkali cement, the Contractor may use a combination of portland cement that does not meet the low-alkali requirement with a pozzolan or slag provided the following requirement is met. The expansion of the proposed combination must be equal to or less than the expansion of a low-alkali cement meeting the requirements of this paragraph when tested in general conformance with **ASTM C441/C441M**. Run expansion tests concurrently at an independent laboratory that is nationally recognized to perform such tests. The Government reserves the right to confirm the test results and to adjust the percentage of pozzolan or slag in the combination to suit other requirements.] [Provide white portland cement meeting these requirements except that it may be Type I, Type II, or Type III [low alkali].] [Type III may be used only in specific areas of the structure, when approved in writing.]

[2.2.1.2 Pozzolan Other than Silica Fume

Provide pozzolan other than silica fume conforming to **ASTM C618**, Class C or F, including low alkali [multiple factor,] [drying shrinkage,] [uniformity,] [and [moderate] [severe] sulfate resistance requirements] of Table 2A. Uniformity Requirements (for entrained air) must apply to all fly ash. [Table 1A., Supplementary Optional Chemical Requirement for Maximum Alkalies, applies when used with aggregates listed to require low-alkali cement].

]2.2.1.3 Ground Granulated Blast-Furnace Slag

Provide ground granulated blast-furnace slag conforming to ASTM C989/C989M, Grade [_____].

]2.2.1.4 Silica Fume

NOTE: Include optional Table 2 in ASTM C1240 when used with aggregates listed to require low-alkali cement. Other requirements in Table 4 may be specified if necessary. Refer EM 1110-2-2000 for guidance.

Silica fume may be furnished as a dry, densified material or as a slurry. Silica fume, unprocessed, or before processing into a slurry or a densified material, must conform to ASTM C1240 with [Table 2 and] the Specific Surface Area and Uniformity Requirements in Table 4 invoked. Provide the services of a manufacturer's technical representative, experienced in mixture proportioning, placement procedures, and curing of concrete containing silica fume. The manufacturer's representative must be available for consultation by both the Contractor and the Contracting officer during mixture proportioning, planning, and production of silica-fume concrete and onsite immediately prior to and during at least the first placement of concrete containing silica fume, and at other times if directed.

]2.2.1.5 Temperature of Cementitious Materials

The temperature of the cementitious materials as delivered to the site must not exceed 65 degrees C 150 degrees F.

2.2.2 Admixtures

All chemical admixtures furnished as liquids must be in a solution of suitable viscosity for field use as determined by the Contracting Officer.

2.2.2.1 Air-Entraining Admixtures

Provide air-entraining admixture conforming to ASTM C260/C260M and consistently entrain air in the specified ranges under field conditions.

2.2.2.2 [Accelerating Admixture

Do not use calcium chloride. Use accelerators that meet the requirements of ASTM C494/C494M, Type C [(or Type E)].

]2.2.2.3 Retarding Admixture

NOTE: A retarding admixture should not be used where high early strength is desirable so that form stripping may proceed expeditiously. Before listing items consult the concrete materials design memorandum to determine areas where retarders may be necessary.

Provide retarding admixture meeting the requirements of [ASTM C494/C494M](#), Type B, or D, except that the 6-month and 1-year compressive strength tests are waived. The admixture may be added to the concrete mixture only when approved[, except for the following structural items where a retarding admixture are not to be used: [_____]]. Do not use Type D as the reason to reduce the cementitious material content unless used in mixture proportioning studies.

]2.2.2.4 Water-Reducing Admixture

Provide a water-reducing admixture meeting the requirements of [ASTM C494/C494M](#), Type A [or D], except that the 6-month and 1-year compressive strength tests are waived. The admixture may be added to the concrete mixture only when its use is approved or directed and after mixture proportioning studies.

]2.2.2.5 High-Range Water-Reducing Admixture (HRWRA)

Use high-range water-reducing admixture that meets the requirements of [ASTM C494/C494M](#), Type F [or G], except the 6-month and 1-year strength requirements are waived.[The admixture may be used only after mixture proportioning studies and when approved.] [Provide the services of a manufacturer's technical representative experienced in mixture proportioning and placement procedures of concrete containing HRWRA. The technical representative must be available for consultation during mixture proportioning and on-site for the first placement of concrete containing HRWRA.]

]2.2.2.6 Expansive Admixture

**NOTE: Delete this paragraph and paragraph BLOCK-OUT
CONCRETE in Part 3 if block-out concrete is not used.**

Submit manufacturer's descriptive literature and certification for fluidifier to be used as expansive admixture in block-out concrete, 60 days prior to its use. Use expansive admixture in block-out concrete conforming to [ASTM C937](#).

]2.2.3 Curing Materials

[2.2.3.1 Sheet Materials

Provide [sheet curing](#) materials conforming to [ASTM C171](#), type optional, except do not use polyethylene sheet. Submit a manufacturer's certificate certifying that the materials comply with the requirements of [ASTM C171](#), if sheet curing is used.

]2.2.3.2 Membrane-Forming Curing Compound

Provide membrane-forming curing compound conforming to [ASTM C309](#), Type 1D or 2, except a styrene acrylate or chlorinated rubber compound meeting [ASTM C309](#), Class B, requirements may be used for surfaces that are to be painted or are to receive subsequent coatings, or floors that are to receive adhesive applications of resilient flooring. Select curing compound selected that is compatible with any subsequent paint, roofing, coating, or flooring specified.

2.2.3.3 Burlap

Provide burlap for curing purposes conforming to AASHTO M 182.

2.2.4 Water

Use water for washing aggregates and for mixing and curing concrete that is free from injurious amounts of oil, acid, salt, alkali, organic matter, or other deleterious substances and in compliance with COE CRD-C 400.

2.2.5 Aggregates

NOTE: See the concrete materials design memorandum to select the aggregate composition options.

This note may be disregarded for regions where Alkali-Silica Reactivity (ASR) is not a concern. Some aggregate sources may exhibit an ASR potential. ASR is a potentially deleterious reaction between alkalis present in concrete and some siliceous aggregates, reference EM 1110-2-2000 paragraph 2-3b(6) and appendix D. Use of cementitious materials meeting the low alkali requirement may be effective in some applications, and insufficient in others. In regions where imposing the low alkali requirement has not been effective in controlling ASR, additional effort for evaluation and mitigation may be required. In which case, the alternate procedures to proportion cementitious materials to meet the low alkali requirement in paragraph PORTLAND CEMENT should not be used with the following requirements. Where ASR is known or suspected to pose a concern for concrete durability, it is recommended that aggregates proposed for use in concrete be evaluated to determine ASR potential and an effective mitigation. EM 1110-2-2000, provides recommendations for evaluating and mitigating ASR in concrete mixtures.

Section 32 13 14.13 CONCRETE PAVING FOR AIRFIELDS AND OTHER HEAVY DUTY PAVEMENTS, paragraph ALKALI-SILICA REACTIVITY, provides a specification method for the Contractor to evaluate and mitigate ASR in concrete mixtures. The expansion limits specified in Section 32 13 14.13 are requirements for pavements and exterior slab construction. For structural concrete applications the measured expansion must be less than 0.10 percent. It may not be economical or practical to specify different test limit requirements for use on the same project. In which case the lower limit required by the application should be used.

The designer may use the specification method in UFGS Section 32 13 14.13 by incorporating the relevant paragraphs into this specification, or may use the following requirements (retain either the

0.10 or the 0.08 percent expansion limits as appropriate) included in the set of brackets highlighted thus "[.]".

2.2.5.1 Aggregate Composition

[Provide fine aggregate consisting of natural sand, manufactured sand, or a combination of natural and manufactured sands. Provide coarse aggregate consisting of gravel, crushed gravel, crushed stone, air-cooled blast-furnace slag, or a combination thereof.] "[Test and evaluate fine and coarse aggregates proposed for use in concrete for alkali-aggregate reactivity in accordance with ASTM C1260. Evaluate fine and coarse aggregates separately and in combination, which matches the Contractor's proposed mix design proportioning. All results of the separate and combination testing must have a measured expansion less than 0.10 (0.08) percent at 16 days after casting. Should the test data indicate an expansion of 0.10 (0.08) percent or greater, reject the aggregate(s) or perform additional testing using ASTM C1260 and ASTM C1567. Perform additional testing using ASTM C1260 and ASTM C1567 using the low alkali portland cement in combination with ground granulated blast furnace (GGBF) slag, or Class F fly ash. Use GGBF slag in the range of 40 to 50 percent of the total cementitious material by mass. Use Class F fly ash in the range of 25 to 40 percent of the total cementitious material by mass.]"

2.2.5.2 Quality of Aggregates

NOTES: The tests selected should be those which are applicable to the concrete to be used in the project. These tests may include those in the following list in addition to others not listed. See EM 1110-2-2000 for schedule of tests.

A list of properties and test values are unique to each project and should be taken from the concrete materials design memorandum. Delete the quality tests not required in the design memorandum.

Use petrographic examination to identify deleterious substances in aggregates. List deleterious substances individually with respective limits.

Deliver aggregates to the mixer meeting the following requirements:

TEST LIMITS			
PROPERTY	FINE AGGREGATE	COARSE AGGREGATE	TESTS
Specific Gravity	[_____]	[_____]	ASTM C127 ASTM C128

TEST LIMITS			
PROPERTY	FINE AGGREGATE	COARSE AGGREGATE	TESTS
Absorption	[_____]	[_____]	ASTM C127 ASTM C128
Durability Factor using Procedure A	[_____]	[_____]	COE CRD-C 114 ASTM C666/C666M
Clay Lumps and Friable Particles	[_____]	[_____]	ASTM C142/C142M
Material Finer than 75 μ No. 200 Sieve	[_____]	[_____]	ASTM C117
Organic Impurities	Not Darker than No. 3, Not less than 95 percent		ASTM C40/C40M ASTM C87/C87M
L.A. Abrasion	[_____]	[_____]	ASTM C131/C131M ASTM C535
Soft Particles	[_____]	[_____]	COE CRD-C 130
Petrographic Examination	List unwanted deleterious materials and their limits	[_____]	ASTM C295/C295M
Chert, less than 2.40 specific gravity	[_____]	[_____]	ASTM C123/C123M
[Coal and Lignite, less than 2.00 specific gravity]	[_____]	[_____]	ASTM C123/C123M

2.2.5.3 Grading

NOTES: The Designer should invoke the optional requirement limiting the amount of material passing the 75- μ m No. 200 sieve when manufactured sand is specified and may invoke the option when natural sand is specified. If the limitation is invoked here, it must be listed for fine aggregate in paragraph AGGREGATES above.

See the concrete materials design memorandum for the approved gradings. Delete gradings not required.

2.2.5.3.1 Fine Aggregate

Deliver fine aggregate to the mixers with a grading such that the individual percent retained on any sieve does not vary more than 3 percent from the percent retained on that sieve in a fixed grading selected by the Contractor with the approval of the Contracting Officer. The fixed

grading may be selected at the start of concrete placement and based upon 30 days fine aggregate production or selected after the first 30 days of concrete placement. The minimum individual percent retained on the 2.36 mm (No. 8) sieve must be 5 percent and on all smaller sieves[, except the 75 μ m (No. 200),] must be 10 percent. In addition to the grading limits, the fine aggregate, as delivered to the mixer, must have a fineness modulus of no less than 2.25 nor more than 2.85. Also control the grading of the fine aggregate so that the fineness moduli groups (average of the current test and the previous two tests) of the fine aggregate as delivered to the mixer do not vary more than 0.10 from the target fineness modulus of the fixed grading selected by the Contractor and approved by the Contracting Officer. The range of each group must not exceed 0.20. Determine the fineness modulus in accordance with COE CRD-C 104. At the option of the Contractor, fine aggregate may be separated into two or more sizes or classifications, but control the uniformity of grading of the separate sizes so that they may be combined throughout the job in fixed proportions established during the first 30 days of concrete placement. The selected fixed grading must be within the following limits, except any individual test result may be outside these limits if within the allowable 3 percent variation from the selected grading.

SIEVE DESIGNATION U.S. STANDARD SQUARE MESH	PERMISSIBLE LIMITS PERCENT BY MASS, PASSING
9.5 mm 3/8 inch	100
4.75 mm No. 4	95 - 100
2.36 mm No. 8	80 - 95
1.18 mm No. 16	60 - 80
600 μ m No. 30	35 - 60
300 μ m No. 50	15 - 30
150 μ m No. 100	5 - 10
75 μ m No. 200	0 - 5

2.2.5.3.2 Coarse Aggregate

Rescreen coarse aggregate just prior to delivery to the concrete batch plant bins. The grading of the coarse aggregate within the separate size groups must conform to the following requirements as delivered to the mixer.

PERCENT BY MASS PASSING INDIVIDUAL SIEVES				
U.S. STANDARD SIEVE SIZE	4.75 mm No. 4 to 19.0 mm 3/4 inch	19.0 mm 3/4 inch to 37.5 mm 1-1/2 inch	37.5 mm 1-1/2 inch to 75 mm 3 inch	75 mm 3 inch to 150 mm 6 inch
175 mm 7 inch				100
150 mm 6 inch				90 - 100
100 mm 4 inch			100	20 - 55
75 mm 3 inch			90 - 100	0 - 15
50 mm 2 inch		100	20 - 55	0 - 5
37.5 mm 1-1/2 inch		90 - 100	0 - 10	
25 mm 1 inch	100	20 - 45	0 - 5	
19.0 mm 3/4 inch	90 - 100	0 - 10		
9.5 mm 3/8 inch	20 - 55	0 - 5		
4.75 mm No. 4	0 - 10			
2.36 mm No. 8	0 - 5			

2.2.5.4 Particle Shape

The quantity of flat and elongated particles in the separate size groups of coarse aggregate, as determined by [ASTM D4791](#), using a value of 3 for width-thickness ratio and length-width ratio must not exceed 25 percent in any size group.

2.2.5.5 Nominal Maximum-Size of Aggregate

Use nominal maximum-size of coarse aggregate in the various parts of the work in accordance with the following tabulation except as directed. The NMSA may be changed for sections requiring a special quality of concrete as directed.

FEATURES	NOMINAL MAXIMUM-SIZE AGGREGATE
Sections 190 mm 7-1/2 inches or less in width or slabs 100 mm 4 inches or less in thickness or any section with a clear distance between reinforcement less than 55 mm 2-1/4 inches	19 mm 3/4 inch
Sections over 190 mm 7-1/2 inches or slabs at least 100 mm 4 inch in thickness. However, do not use this size in any section in which the clear distance between reinforcement is less than 55 mm 2-1/4 inch	40 mm 1-1/2 inch

FEATURES	NOMINAL MAXIMUM-SIZE AGGREGATE
Unreinforced sections over 300 mm 12 inches in width and reinforced sections over 450 mm 18 inches in width or slabs 255 mm 10 inches or greater in thickness. However, do not use this size in any section in which the clear distance between reinforcing bars is less than 115 mm 4-1/2 inches	75 mm 3 inches
Massive sections exceeding 1.8 m 6 feet in width and slabs 600 mm 24 inches in thickness, in which the clear distance between reinforcing bars is at least 225 mm 9 inches	150 mm 6 inches

2.2.5.6 Moisture Content

Do not place fine aggregate in bins at the batch plant until it is in a stable state of moisture content. Reach a stable moisture content when the variation in the percent of total moisture tested in accordance with ASTM C566 and when sampled at the same location will not be more than 0.5 percent during 1 hour of the 2 hours prior to placing the material in the batch plant bins and the variation in moisture content when sampled at the same location must not be more than 2.0 percent during the last 8 hour period that the aggregate remains in the stockpile. Deliver coarse aggregate to the mixers with the least amount of free moisture and the least variation in free moisture practicable under the job conditions. Under no conditions deliver coarse aggregate to the mixer "dripping wet".

[2.2.5.7 Commercial Concrete Aggregate Sources

NOTE: The list of sources and required tests will be taken from the concrete materials design memorandum.

Concrete aggregates may be furnished from any source capable of meeting the quality requirements stated in paragraph AGGREGATES above. The following sources were evaluated during the design phase of the project in [_____] and were found at that time capable of meeting the quality requirements when suitably processed. No guarantee is given or implied that any of the following listed sources are currently capable of producing aggregates that meet the required quality stated above. A Design Memorandum containing the results of the Government investigation and test results is available for review in the [_____] District Office. Contact [_____] at [_____] to arrange for review of the memorandum. Consider test results and conclusions valid only for the sample tested and do not take as an indication of the quality of all material from a source nor for the amount of processing required.

- a. List of Sources
- b.

FINE AGGREGATE		COARSE AGGREGATE	
F1	[_____] [1/]	C1	[_____] [1/]
F2	[_____] [1/]	C2	[_____] [1/]
F3	[_____] [1/]	C3	[_____] [1/]
[1/ Low-alkali cement or the approved alternate must be used with these sources.]			

NOTE: The concrete materials design memorandum will list those sources requiring low-alkali cement, which must be noted herein.

- c. Selection of Source - After the award of the contract, designate in writing only one source or combination of sources from which the Contractor proposes to furnish aggregates. If the Contractor proposes to furnish aggregates from a source or sources not listed in subparagraph "a.", LIST OF SOURCES, above, designate only a single source or single combination of sources for aggregates. Regardless of the source selected, provide samples for quality-assurance testing as required by paragraphs GOVERNMENT PRECONSTRUCTION TESTING and MATERIALS FOR MIXTURE-PROPORTIONING STUDIES IN part 1. If a source for coarse or fine aggregate so designated by the Contractor does not meet the quality requirements stated above, do not submit for approval other sources but furnish the coarse or fine aggregate, as the case may be, from one or a combination of the sources listed at no additional cost to the Government.

12.2.5.8 Government Furnished Concrete Aggregate Source

NOTE: The Specification Writer should ascertain that restoration of the pit or quarry site is specified under other sections.

2.2.5.8.1 Location

The deposits are [owned] [controlled] by the Government and are made available to the Contractor free of charge for production of aggregate required under this contract. Within the designated area, a supply of material is available from which concrete aggregate meeting the requirement of these specifications can be produced with suitable processing. The Government guarantees that a sufficient amount of material of suitable quality for production of all of the concrete aggregate required is available within the deposit and that concrete aggregates of suitable quality can be produced with a properly designed and operated plant [without hand-picking or similar operations]. However, the amount of work involved or the amount of unsatisfactory materials required to be wasted to produce a sufficient quantity of suitable concrete aggregate is the responsibility of the Contractor, and the Government will not be held liable for costs resulting from such work or waste. Produce the concrete aggregate from the following sites as shown:

	QUARRY SITE	BAR	TERRACE	COORDINATES	DIST. AND DIRECTION
G1	[_____]	[_____]	[_____]	[_____]	[_____]
G2	[_____]	[_____]	[_____]	[_____]	[_____]
G3	[_____]	[_____]	[_____]	[_____]	[_____]

[2.2.5.8.2 Explorations

The deposits listed have been explored by the Government to determine the character and extent of the materials available. The locations of the explorations are shown in the contract drawings. The logs of the exploratory holes are also shown in the drawings. Samples of materials secured are available for inspection at [_____]. The results of explorations are furnished for information only. These data are the result of limited explorations and tests conducted by and for the Government and are accurate to the extent of the scope of the investigations conducted. The Government will not be responsible for any deduction, interpretation, or conclusion drawn therefrom by the Contractor.

]2.2.6 Nonshrink Grout

**NOTE: Grade of nonshrink grout will be specified
based on the application, exposure conditions, and
manufacturer's recommendation.**

Use nonshrink grout for use in setting base plates and machinery conforming to **ASTM C1107/C1107M**, Grade [_____], and is a commercial formulation suitable for the application proposed. Submit descriptive literature of the grout proposed for use containing certified laboratory test results showing that it meets **ASTM C1107/C1107M** 60 days prior to its use together with a certificate from the manufacturer stating that the grout is suitable for the application or exposure for which it is being considered. In addition, a detailed plan for review, showing equipment and procedures for use in mixing and placing the grout.

2.2.7 Packaged Dry Repair Materials

Provide packaged dry rapid-hardening cementitious materials for concrete repairs that is a commercial formulation conforming to **ASTM C928/C928M** requiring only the addition of water.

2.2.8 Bonding Agents

Submit descriptive literature and certification in advance of their use. Bonding agents must meet the following requirements:

2.2.8.1 Latex Bonding Agent

Provide latex agents for bonding fresh to hardened concrete conforming to **ASTM C1059/C1059M**, Type II.

2.2.8.2 Epoxy Resin

Provide epoxy resins for use in repairs conforming to ASTM C881/C881M, Type V, Grade I or II.

2.2.9 Surface Retarder

Provide surface retarder conforming to COE CRD-C 94.

2.3 PLANT AND EQUIPMENT

NOTE: See the concrete materials design memorandum
or EM 1110-2-2000 for the plant size requirements.

Provide batching, mixing, conveying, and placing systems with a capacity of at least [_____] cubic meters yards per hour. Submit the methods and description of the equipment proposed for transporting, handling, and depositing the concrete for review, 60 days before concrete placement begins. Include site drawings or sketches with locations of equipment and placement site.

2.3.1 Batch Plant

NOTE: See EM 1110-2-2000, and the concrete
materials design memorandum for selection of
automatic or semiautomatic plant.

Submit details and data on the concrete plant, within 60 days prior to assembly, to the Contracting Officer for conformance review with the requirements of paragraph PLANT AND EQUIPMENT. Batch plant must meet the following requirements:

2.3.2 Location

The concrete plant [will] [may] be located at the site of the work in the general area indicated on the drawings, [or may be located offsite].

2.3.3 Bins and Silos

Provide separate bins, compartments, or silos for each size or classification of aggregate and for each of the cementitious materials. Provide compartments of ample size and constructed so that the various materials will be maintained separately under all working conditions. Separate all compartments containing bulk cement, pozzolan, ground granulated blast-furnace slag, or silica fume from each other by a free-draining air space. Clearly mark all filling ports with a permanent sign stating the contents.

2.3.4 Batching Equipment

2.3.4.1 Batchers

Weigh aggregate in separate weigh batchers with individual scales. Weigh each bulk cement and/or other cementitious materials on a separate scale in a separate weigh batcher. Measure water by weight or by volume. If

measured by weight, do not weigh cumulatively with another ingredient. Measure ice separately by weight. Batch admixtures separately and batch by weight or by volume in accordance with the manufacturer's recommendations.

2.3.4.2 Water Batcher

Provide a suitable water-measuring and batching device that will be capable of measuring and batching the mixing water within the specified tolerances for each batch. Use mechanism for delivering water to the mixers that is free from leakage when the valves are closed. Interlock the filling and discharge valves for the water batcher so that the discharge valve cannot be opened before the filling valve is fully closed. When a water meter is used, provide a suitable strainer ahead of the metering device.

2.3.4.3 Admixture Dispensers

Provide a separate batcher or dispenser for each admixture. Equip each plant with the necessary calibration devices that will permit convenient checking of the accuracy of the dispensed volume of the particular admixture. Use batching or dispensing devices capable of repetitively controlling the batching of the admixtures to the accuracy specified. Use piping for liquid admixtures that are free from leaks and properly valved to prevent backflow or siphoning. Include a device or devices that will detect and indicate the presence or absence of the admixture or provide a means of visually observing the admixture in the process of being batched or discharged in the dispensing system. Ensure each system is capable of ready adjustment to permit varying the quantity of admixture to be batched. Interlock each dispenser with the batching and discharge operations so that each admixture is added separately to the batch in solution in a separate portion of the mixing water or in fine aggregate in a manner to ensure uniform distribution of the admixtures throughout the batch during the required mixing period. Store and handle admixtures in accordance with the manufacturers recommendations.

2.3.4.4 Moisture Control

Provide plant which is capable of ready adjustment to compensate for the varying moisture content of the aggregates and to change the weights of the materials being batched. Provide a moisture meter complying with the provisions of [COE CRD-C 143](#) for measurement of moisture in the fine aggregate. Arrange the sensing element so that the measurement is made near the batcher charging gate of the fine aggregate bin or in the fine aggregate batcher.

2.3.4.5 Scales

Provide facilities for the accurate measurement and control of each of the materials entering each batch of concrete. Use weighing equipment and controls conforming to the applicable requirements of [NIST HB 44](#), except that the accuracy must be within 0.2 percent of the scale capacity. Provide standard test weights and any other auxiliary equipment required for checking the operating performance of each scale or other measuring device. Make tests at the frequency required in paragraph TESTS AND INSPECTIONS in PART 3, and in the presence of a Government quality assurance representative. Include a visible indicator for each weighing unit that indicates the scale load at all stages of the weighing operation and shows the scale in balance at zero load. Arrange weighing equipment

so that the concrete plant operator can observe the indicators.

2.3.4.6 Operation and Accuracy

[Start weighing operation of each material automatically when actuated by a single starter switch and end automatically when the designated amount of each material has been reached. These requirements can be met by providing an automatic batching system as defined in [NRMCA CPMB 100.](#)]

[Start weighing operation of each material automatically when actuated by one or more starter switches and end when the designated amount of each material has been reached. These requirements can be met by providing a semiautomatic or automatic batching system as defined by [NRMCA CPMB 100.](#)]

Provide equipment to permit the selection of [_____] preset mixes each by the movement of not more than two switches or other control devices.

Cumulative weighing will not be permitted. Construct and arrange weigh batchers so that the sequence and timing of batcher discharge gates can be controlled to produce a ribboning and mixing of the aggregates, water, admixtures, and cementitious materials as the materials pass through the charging hopper into the mixer. Include provisions to facilitate the inspection of all operations at all times. Deliver materials from the batching equipment within the following limits of accuracy:

MATERIAL	PERCENT
Cementitious materials	± 1
Water	± 1
Aggregate smaller than 37.5 mm 1-1/2 inch size	± 2
Aggregate larger than 37.5 mm 1-1/2 inch size	± 3
Chemical admixtures	± 3

2.3.4.7 Interlocks

Interlock batchers and mixers so that:

- The charging device of each batcher cannot be actuated until all scales have returned to zero balance within ± 0.2 percent of the scale capacity and each volumetric device has reset to start or has signaled empty.
- The charging device of each batcher cannot be actuated if the discharge device is open.
- The discharge device of each batcher cannot be actuated if the charging device is open.
- The discharge device of each batcher cannot be actuated until the indicated material is within the allowable tolerances.
- One admixture is batched automatically with the water.
- Each additional admixture is batched automatically with a separate portion of the water or with the fine aggregate.

- g. The mixers cannot be discharged until the required mixing time has elapsed.

2.3.4.8 Recorder

Provide an accurate recorder or recorders conforming to the following detailed requirements:

- a. Produce a graphical or digital record on a single visible chart or tape of the weight or volume of each material in the batchers at the conclusion of the batching cycle. Produce record prior to delivery of the materials to the mixer. After the batchers have been discharged, show the return to empty condition.
- b. House graphical recording or digital printout unit completely in a single cabinet that is capable of being locked.
- c. Mark the chart or tape so that each batch may be permanently identified and so that variations in batch weights of each type of batch can be readily observed. Provide chart or tape which is easily interpreted in increments not exceeding 0.5 percent of each batch weight.
- d. Show time of day at intervals of no more than 15 minutes.
- e. The recorder chart or tape will become the property of the Government.
- f. Place recorder in a position convenient for observation by the concrete plant operator and the Government inspector.
- g. The recorded weights or volumes when compared to the weights or volumes actually batched must be accurate within ± 2 percent.

2.3.4.9 Batch Counters

Include devices for automatically counting the total number of batches of all concrete batched and the number of batches of each preset mixture.

2.3.4.10 Rescreening Plant

Locate, arrange, and operate rescreening plant in a manner that all coarse aggregate will be routed through the plant and that its operation will ensure delivery to the mixers of graded coarse aggregate free from excessive variation and conforming to the size groups and grading of paragraph AGGREGATES above and with moisture content conforming to the provisions of paragraph MOISTURE CONTENT above. Coarse aggregate may be rescreened and delivered to the batch plant bins one size group at a time or two or more adjacent size groups at a time. Simultaneous rescreening of nonadjacent size groups is not permitted. Waste all material passing the bottom screen of the smallest size of coarse aggregate being screened.

2.3.4.11 Washing Plant

Wash all coarse aggregates immediately prior to entering the rescreening plant. Provide rewashing plant containing water nozzles and vibrating screens to remove foreign materials and coatings from aggregate particles. Use water for washing meeting the requirements of paragraph WATER above.

2.3.4.12 Trial Operation

Not less than 7 days prior to commencement of concrete placing, make a test of the batching and mixing plant in the presence of the Contracting Officer to check operational adequacy. Produce the number of full-scale concrete batches required in trial runs as directed, do not exceed 20, and proportion as directed. Waste or use all concrete produced in these tests for purposes other than inclusion in structures covered by this specification. Correct all deficiencies found in plant operation prior to the start of concrete placing operations. No separate payment will be made to the Contractor for labor or materials required by provisions of this paragraph. Notify the Contracting Officer of the trial operation not less than 7 days prior to the start of the trial operation.

2.3.4.13 Protection

Protect weighing, indicating, recording, and control equipment against exposure to dust, moisture, and vibration so that there is no interference with proper operation of the equipment.

2.3.5 Laboratory Areas

**NOTE: The editor should use the alternate sentence
and fill in the correct Section number unless a
laboratory building is to be government furnished.**

Provide a room in the plant to house the moisture and grading testing equipment for aggregate and to provide working space. Provide another room for testing fresh concrete and for fabricating and initial curing of concrete test specimens in accordance with **ASTM C31/C31M**. The size, arrangement, and location of these rooms will be subject to approval. Provide electricity, air conditioning, heat, and water as required for use in these laboratory areas.

[2.3.6 Plant Layout Drawings

**NOTE: The paragraph should be included in projects
for which "onsite" plant is a requirement. The
wording should be modified as necessary to suit the
particular requirements of each project. Drawings
submitted in compliance with this paragraph will
enable the Contracting Officer to determine in
advance of erection whether or not the plant meets
the requirements of these specifications.**

Submit drawings, in triplicate, showing the layout of the plant the Contractor proposes to use on the work for review. Show the locations of the principal components of the construction plant; offices; shop and storage building; housing facilities, if any; and storage areas and yards which the Contractor proposes to construct at the site of the work and elsewhere. Also furnish for review drawings, in triplicate, showing the general features of his aggregate processing plant; aggregate transporting; storage and reclaiming facilities; aggregate rinsing and dewatering plant, if required; coarse aggregate rescreening plant, if

required; concrete batching and mixing plant; concrete conveying and placing plant; and when precooling of concrete is required, the cooling plant. Appropriately show the capacity of each major feature of the plant including the rated capacity of the aggregate production plant in tons (metric) (2000 lb) per hour of fine and coarse aggregates; rated capacity of the aggregate transporting, storage and reclaiming facilities; volume of aggregate storage; capacity of cement and pozzolan storage; rated capacity of the concrete batching and mixing plant in cubic meters yards per hour; rated capacity of the concrete transporting and placing plant in cubic meters yards per hour; and when used rated capacity of plant for precooling of concrete. Submit drawings in triplicate showing any changes in plant made during design and erection or after the plant is in operation for review. Two sets of the drawings will be retained and one set will be returned to the Contractor with comments.

12.3.7 Mixers

NOTE: See the concrete materials design memorandum for information on mixer selection and concrete mixers. Truck mixers are not allowed for mixing or transporting concrete with less than 50 mm 2 in. slump or greater than 37 mm 1-1/2 in. nominal maximum size aggregate (NMSA).

Provide stationary mixers [or truck mixers]. Each mixer must combine the materials into a uniform mixture and discharge this mixture without segregation. Do not charge mixers in excess of the capacity recommended by the manufacturer on the nameplate. Excessive over-mixing requiring introduction of additional water will not be permitted. Maintain mixers in satisfactory operating condition, and keep mixer drums free of hardened concrete. Replace mixer blades or paddles when worn down more than 10 percent of their depth when compared with the manufacturer's dimension for new blades. Should any mixer at any time produce unsatisfactory results, discontinue its use promptly until it is repaired or replaced. Submit the make, type, capacity, and number of the concrete mixers proposed for use, 60 days prior to installation for review by the Contracting Officer for conformance with the requirements of paragraph PLANT AND EQUIPMENT.

2.3.7.1 Stationary Mixer Uniformity Requirements

NOTE: The option for the government to perform the initial mixer evaluation may be invoked.

Adjust the size of the batch, the mixing time, the charging sequence, and other factors to provide concrete that meets the uniformity limits specified herein and in paragraph MIXER UNIFORMITY IN PART 3. Perform all testing in accordance with COE CRD-C 55. When regular testing is performed, the concrete must meet the limits of any five of the six uniformity requirements. When abbreviated testing is performed, the concrete must meet only those requirements listed for abbreviated testing. The initial mixer evaluation test is a regular test and perform prior to the start of concrete placement. Use concrete proportions for the evaluation that contains the largest size aggregate on the project and as directed. Regular testing consists of performing all six tests on three batches of concrete. The range for regular testing is the average

of the ranges of the three batches. Abbreviated testing consists of performing the three required tests on a single batch of concrete. The range for abbreviated testing is the range for one batch. If more than one mixer is used and all are identical in terms of make, type, capacity, condition, speed of rotation, etc., the results of tests on one of the mixers applies to the others, subject to approval. Perform mixer evaluations as specified herein. [However, the initial evaluation will be performed by the Government. Provide labor and equipment as directed to assist the Government in performing any evaluation made by the Government.]

PARAMETER	ABBREVIATED	
	REGULAR TESTS ALLOWABLE MAXIMUM RANGE FOR AVERAGE OF 3 BATCHES	TESTS ALLOWABLE MAXIMUM RANGE FOR 1 BATCH
Unit weight of air-free mortar, kg/m ³ lb/cu ft	322.0	322.0
Air content, percent	1.0	---
Slump, mm inches	251.0	---
Coarse aggregate, percent	6.0	6.0
Compressive strength at 7 days, percent	10.0	10.0
Water content, percent	1.5	---

[2.3.7.2 Truck Mixers

Provide truck mixers and the mixing of concrete therein conforming to the requirements of ASTM C94/C94M. A truck mixer may be used for complete mixing (transit-mixed) or to finish the partial mixing done in a stationary mixer (shrink-mixed). Equip each truck with two counters from which it is possible to determine the number of revolutions at mixing speed and the number of revolutions at agitating speed. Do not use truck mixers to mix or agitate concrete with greater than 37.5 mm 1-1/2 inch nominal maximum-size aggregate or concrete with a slump of 50 mm 2 inches or less. Determine the acceptability of truck mixers by uniformity tests in accordance with ASTM C94/C94M.

]2.3.8 Sampling Facilities

Provide suitable facilities and labor for obtaining representative samples of concrete in accordance with ASTM C172/C172M for Contractor quality control (QC) and Government quality control (QA) testing.

2.3.9 Coarse Aggregate

NOTE: The automatic sampling plant should be required for aggregates in concrete containing larger than 75 mm 3 inch NMSA. For aggregates in concrete containing 75 mm 3 inch NMSA, a cost analysis should be made before specifying the automatic sampling plant. The automatic sampling plant should not be specified for aggregates in

concrete containing 75 or 150 mm 3 or 6 inch NMSA.
 Note that the quarry sloping screens on the
 automatic plant will require slightly larger screens
 than those used for tests by ASTM C136/C136M for
 comparable results.

Provide suitable facilities for readily obtaining representative samples of coarse aggregate for test purposes immediately prior to the material entering the mixer. [Include automatic equipment capable of obtaining, sieving, and weighing samples of the coarse aggregate as follows:

AGGREGATE SIZE (mm) (inch)	APPROXIMATE SIZE OF SAMPLE (kg) (lb)
4.75 to 19.0 No. 4 to 3/4	250 500
19.0 to 37.5 3/4 to 1-1/2	250 500
37.5 to 75 1-1/2 to 3	500 1000
75 to 150 3 to 6	1000 2000

Provide equipment that is capable of running a complete sieving, of any required sample, without the necessity of intermittent loading. Design the assembly to permit selection, screening, and weighing of any individual sample in 10 minutes or less. Provide equipment designed by a company engaged in the design and manufacture of aggregate sieving devices. Provide equipment that will accomplish the desired purpose. Use sieves that meet the applicable requirements of ASTM E11, except for the frame size requirements. Arrange equipment so that all controls will be enclosed and operable from a single position commanding a view of the screen device and the scale or scales. Provide communication from the batch plant operation to this control area. The Contractor is responsible for charging of the assembly as directed, disposal of waste material, and proper service and maintenance of the assembly. Provide each sieve with individual controls for frequency and angle. Run correlation tests with equipment as used for ASTM C136/C136M before concrete placement begins and at least every 60 days while concrete is being placed. The correlation test will determine the optimum angle, volume of feed, and the frequency for each sieve.]

2.3.10 Transporting Equipment

Design, operate, and maintain transporting equipment so that it does not cause or permit segregation or loss of material. Do not drop concrete vertically more than 1.5 m 5 feet except where suitable equipment is provided to prevent segregation and where specifically authorized.

2.3.10.1 Buckets

Use bottom-dump buckets conforming to the following requirements: the interior hopper slope must be no less than 70 degrees from the horizontal; the minimum dimension of the clear gate opening must be at least five times the nominal maximum size of the aggregate, and the area of the gate opening must not be less than 0.2 square meters 2 square feet; the bucket gates must be grout-tight when closed, the double clamshell type, and manually, pneumatically, or hydraulically operated; and design the gate-opening mechanism to close the gates automatically when the control is released or when the air or hydraulic line is broken. If gate actuation is dependent on integral air or hydraulic reservoirs, the capacity of the reservoirs must be sufficient to open and close the gates three times without recharging the reservoir.

2.3.10.2 Trucks

Use truck mixers or agitators for transporting central-mixed concrete conforming to the applicable requirements of ASTM C94/C94M. Do not use truck mixers to transport concrete with larger than 37.5 mm 1-1/2 inch nominal maximum-size aggregate or 50 mm 2 inch or lower slump. Nonagitator trucks may be used for transporting central-mixed concrete over a smooth road when the hauling time is less than 15 minutes and the slump is less than 75 mm 3 inches. Bodies of nonagitator trucks must be smooth, watertight, metal containers specifically designed to transport concrete, shaped with rounded corners to minimize segregation, and equipped with gates that will permit positive control of the discharge of the concrete.

2.3.10.3 Chutes

When concrete can be placed directly from a truck mixer, agitator, or nonagitator truck, the chutes supplied by the truck manufacturer as standard equipment may be used. Use a discharge deflector when required by the Contracting Officer. Separate chutes and other similar equipment are not permitted for conveying concrete except when specifically approved and do not increase slump to accommodate their use.

2.3.10.4 Belt Conveyors

Design and operate belt conveyors to assure a uniform flow of concrete from mixer or delivery truck to final place of deposit without segregation of ingredients or loss of mortar and provide with positive means for preventing segregation of the concrete or loss of mortar at the transfer point(s) and the point of placing. Do not exceed idler spacing of 900 mm 36 inches. Use a minimum belt speed of 90 m 300 feet per minute and a maximum of 230 m 750 feet per minute. Belt width must be a minimum of 600 mm 24 inches if the NMSA is 150 mm 6 inches and must be a minimum of 400 mm 16 inches if the NMSA is 75 mm 3 inches or less. The NMSA required in mixture proportions furnished by the Government will not be changed to accommodate the belt width.

2.3.10.5 Pump Placement

Concrete may be conveyed by positive-displacement pump when approved. Pump placement will be approved only for areas where placement by bucket or conveyor is difficult or impractical. Provide piston or squeeze-pressure type pumping equipment. Provide rigid-steel pipe or heavy-duty flexible hose pipeline. Do not use aluminum pipe. Use pipe

with an inside diameter at least 3 times the nominal maximum size of the coarse aggregate in the concrete to be pumped but no less than 100 mm 4 inches.

PART 3 EXECUTION

3.1 PREPARATION FOR PLACING

3.1.1 Vibrators

Keep an adequate number of vibrators on hand to meet placing requirements, and spare vibrators available to maintain production in the event of breakdown. Make adequate air pressure available for air vibrators and adequate voltage for electric vibrators. Use vibrators of the proper size, frequency, and amplitude for the type of work being performed in conformance with the following requirements:

APPLICATION	HEAD DIAMETER (mm) (inch)	FREQUENCY VPM	AMPLITUDE (mm) (inch)
Thin walls, beams, etc.	32 - 64 1-1/4 - 2-1/2	9,000 - 13,500	0.5 - 1.0 0.020 - 0.04
General construction	50 - 88 2 - 3-1/2	8,000 - 12,000	0.6 - 1.2 0.025 - 0.05
Heavy sections	75 - 150 3 - 6	7,000 - 10,500	0.75 - 1.5 0.030 - 0.06
Mass concrete	125 - 175 5 - 7	5,500 - 8,500	1.0 - 2.0 0.04 - 0.08

Use frequency and amplitude within the range indicated in the tabulation as determined in accordance with paragraph TESTS AND INSPECTIONS below.

3.1.2 Embedded Items

Before placing concrete, take care to determine that all embedded items are securely fastened in place as indicated in the drawings or required. Provide embedded items that are free of oil and other foreign matter such as loose coatings of rust, paint, and scale. The embedding of wood in concrete will be permitted only when specifically authorized or directed. Provide any air or water lines or other materials embedded in structures, as authorized construction expedients, conforming to the above requirements and upon completion of their use backfill with concrete or mortar as directed. Welding will not be permitted on embedded or otherwise exposed metals which are in contact with concrete surfaces. Tack welding of or to embedded items will not be permitted.

3.1.3 Concrete on Earth Foundations

Place concrete on earth foundations that are clean, damp, and free from frost, ice, and standing or running water. Prior to placement of concrete, compact the earth foundation satisfactorily in accordance with the provisions of Section 31 00 00 EARTHWORK.

3.1.4 Concrete on Rock Foundations

Place concrete on rock surfaces that are clean and free from oil, standing or running water, ice, mud, drummy rock, coatings, debris, and loose, semidetached, overhanging, or unsound fragments. Clean faults or joints to a satisfactory depth and to firm rock on the sides as directed by the Contracting Officer. Immediately before concrete is placed, clean all

rock surfaces thoroughly by the use of air-water jet, high-pressure water jet, or sandblasting as described in the paragraph below. Keep all rock surfaces continuously wet for at least 24 hours immediately prior to placing concrete thereon. Cover all approximately horizontal surfaces immediately before the concrete is placed with a 13 mm 1/2 inch layer of mortar composed of the same sand and cementitious materials used in the concrete. The sand-cementitious materials ratio and the water-cementitious material ratio of the mortar must be approximately the same as those used in the concrete mixture. Cover mortar with concrete before the mortar has reached its initial time of setting.

3.1.5 Construction Joint Treatment

Submit the method and equipment proposed for joint cleanup and waste disposal, for review 30 days before concrete placement begins.

3.1.5.1 Joint Preparation

Prepare concrete surfaces to which other concrete is to be bonded for receiving the next lift or adjacent concrete by cleaning by sandblasting, high-pressure water jet, or air-water cutting. Surface cutting by air-water jets will not be permitted for concrete surfaces congested with reinforcing steel or if they are relatively inaccessible. If, for any other reason, it is considered undesirable to disturb the surface of a lift before it has hardened, the use of sandblasting or high-pressure water jet after hardening will be required. Regardless of the method used, the resulting surface must be free from all laitance and inferior concrete so that clean, well-bonded coarse aggregate particles are exposed uniformly over the lift surface. Apply joint treatment method such that the edges of the larger particles of aggregate are not undercut. Where joint preparation occurs more than 2 days prior to placing the next lift or where the work in the area subsequent to the joint preparation causes dirt or debris to be deposited on the surface, clean the surface as the last operation prior to placing the next lift. Keep the surface of the construction joint continuously wet for the first 12 hours of the 24 hours prior to placing concrete, except that the surface must be damp with no free water at the time of placement.

3.1.5.2 Air-Water Cutting

Perform air-water cutting of a construction joint at the proper time, generally between 4 and 12 hours after placement and only on horizontal construction joints. This period may be modified if a retarder is used to prolong the setting of the cement at surface of the concrete. Use an air pressure of 620 to 760 kPa 90 to 110 psi in the jet, and use sufficient water pressure to bring the water into effective influence of the air pressure. When approved a surface retarder complying with the requirements of COE CRD-C 94 may be applied to the surface of the lift to prolong the period of time during which air-water cutting is effective. Prior to receiving approval, furnish samples of the material to be used and demonstrate the method to be used in its application. After cutting, wash and rinse the surface until the wash water is no longer cloudy. If air-water cutting does not produce acceptable results, prepare the surface by high-pressure water jet or sandblasting.

3.1.5.3 High-Pressure Water Jet

A stream of water under a pressure of not less than 21 MPa 3,000 psi may be used for cleaning. Delay its use until the concrete is sufficiently

hard so that only the surface skin or mortar is removed and there is no undercutting of coarse-aggregate particles. If the high-pressure water jet is incapable of a satisfactory cleaning, clean the surface by sandblasting.

3.1.5.4 Wet Sandblasting

This method of joint preparation may be used when the concrete has reached sufficient strength to prevent undercutting of coarse aggregate particles. Continue the operation until all accumulated laitance, coatings, stains, debris, and foreign materials are removed. Then wash the surface of the concrete thoroughly to remove all loose material. This method may be used on both horizontal and vertical surfaces.

3.1.5.5 Waste Water Disposal

**NOTE: Specification Writer will fill in the section
number for the Environment Protection Plan.**

Use a method in disposing of waste water employed in cutting, washing, and rinsing of concrete surfaces such that the waste water does not stain, discolor, or affect exposed surfaces of the structures, or damage the environment of the project area. The method of disposal must meet all requirements of Section 01 57 19 TEMPORARY ENVIRONMENTAL CONTROLS.

3.2 TRANSPORTING AND PLACING

3.2.1 Transporting

Methods and equipment for conveying and depositing the concrete into the form are subject to approval. Provide transporting system with sufficient capacity to supply concrete at a rate to prevent cold joints forming during placement. A properly designed and sized elephant trunk and rigid drop chute bottom section which will prevent free-fall within the elephant trunk and rigid drop chute will be used if concrete is to drop more than 1.5 m 5 feet. If concrete is to be placed through installed horizontal or sloping reinforcing bars, discharge the concrete into a pipe or elephant trunk that is long enough to extend through the reinforcing bars to within 1.5 m 5 feet of the placing surface. In no case will concrete be discharged to free fall through the reinforcing bars.

3.2.1.1 Transporting by Bucket

Provide indicating and signaling devices to control the identification of types or classes of concrete as they are mixed and discharged into buckets for transfer to the forms. Identify each type or class of concrete visually by placing a colored tag or marker on a bucket as it leaves the mixing plant so that the concrete may be positively identified in the forms and placed in the structure in the desired position.

3.2.1.2 Transporting by Pump

The nominal maximum-size coarse aggregate will not be reduced or mixture proportions changed to accommodate a pump except as specifically determined appropriate. The distance and height to be pumped must not exceed limits recommended by the pump manufacturer. Supply concrete to the pump continuously. When pumping is completed, eject concrete

remaining in the pipeline without contamination of concrete in place. After each operation clean the equipment thoroughly and waste flushing water outside the forms.

3.2.1.3 Transporting by Belt Conveyor

Methods and equipment for transporting the concrete by belt conveyor into the form are subject to approval.

3.2.2 Placing

Provide placing system with sufficient capacity to supply concrete at a rate which will prevent cold joints in any placement. Work concrete into the corners and angles of the forms and around all reinforcement and embedded items without permitting the material to segregate. Deposit concrete as close as possible to its final position in the forms, and in so depositing, there must be no vertical drop greater than 1.5 m 5 feet except where suitable equipment is provided to prevent segregation and where specifically authorized. Regulate depositing of concrete so that it will be effectively placed and consolidated in horizontal layers not exceeding 1.5 m 5 feet in thickness with a minimum of lateral movement. Deposit amount of concrete such that it can be readily and thoroughly consolidated and do not exceed 3 cubic meters 4 cubic yards in one pile. All concrete-placing equipment and methods are be subject to approval. Concrete placement will not be permitted when, in the opinion of the Contracting Officer, weather conditions prevent proper placement and consolidation.

3.2.2.1 Time Interval Between Mixing and Placing

Place concrete mixed in stationary mixers and transported by nonagitating equipment within 30 minutes after it has been mixed, unless otherwise authorized. When concrete is truck mixed or when a truck mixer or agitator is used for transporting concrete mixed by stationary mixers, deliver the concrete to the site of the work, and complete discharge within 1 hour after introduction of the cement to either the water or aggregate.

3.2.2.2 Hot-Weather Placing

NOTE: See EM 1110-2-2000 for the proper placing temperature.

The temperature of the concrete when deposited in the forms during hot weather must not exceed [_____] degrees C F except as further required above. An approved retarding admixture may be used in accordance with paragraph RETARDING ADMIXTURE to facilitate placing and finishing. Cool steel forms and reinforcement and conveying and placing equipment if necessary to assist in maintaining specified concrete-placing temperature. Measure the temperature of the fresh concrete in accordance with ASTM C1064/C1064M. Submit a description of the materials and methods proposed for protection of the concrete 60 days in advance of anticipated need date for review, when concrete is to be placed under hot-weather conditions.

3.2.2.3 Cold Weather Placing

The temperature of the concrete when deposited in the forms must not be less than 5 degrees C 40 degrees F. The ambient temperature of the placement area and all surfaces to receive concrete must be above 0 degrees C 32 degrees F. Materials entering the mixer must be free from ice, snow, and frozen lumps. Closely regulate heating of mixing water or aggregates necessary to keep the concrete temperature above 5 degrees C 40 degrees F so that the concrete temperature does not exceed 15 degrees C 60 degrees F. An accelerator may be used when approved in advance.

[3.2.2.4 Special Temperature-Controlled Concrete

NOTE: See the appropriate concrete materials design memorandum or thermal study to fill in blanks

Special temperature control is applicable to concrete in the following structures: [____]; [____]; [____]. Regardless of requirements specified above, the concrete must have a temperature of no more than [____] degrees C F and no less than 5 degrees C 40 degrees F when measured at least 20 minutes after mixing. Heating of the mixing water or aggregates will not be permitted until the temperature of the concrete has decreased to 7 degrees C 45 degrees F. Heat materials in such a manner that they will be free from ice, snow, and frozen lumps before entering the mixer. Submit methods and equipment for review and comment 60 days in advance of anticipated date required for use, when special temperature controls are required.

]3.2.2.5 Concrete Lifts

NOTE: The required construction joints should be shown in the drawings.

The depth of concrete placed in each lift will be as shown in the drawings. Deposit all concrete in approximately horizontal layers about 0.5 m 1-1/2 feet in thickness in stepped progression at such a rate that the formation of cold joints will be prevented. Place slabs in one lift, unless 0.8 m 2.5 foot or more deep. Where 2.3 m 7.5 foot or greater lift depths are permitted, furnish approved cantilever forms that are jointed or hinged approximately midheight to facilitate placement against surfaces sloping more than 10 degrees from vertical. At the beginning of the placing of a lift, retract the top half of a hinged or jointed form to such a position that it does not interfere with the operation of buckets placing concrete adjacent to the form. Use a minimum of five successive horizontal layers in stepped progression for 2.3 m 7.5 foot lifts. Where 1.5 m 5 foot lifts are required, use a minimum of three successive horizontal layers in stepped progression. Place each new layer of concrete on the oldest exposed layer. Do not exceed 12 m 40 feet maximum exposed bulkhead face of concrete between adjacent monoliths except as otherwise approved. Submit a lift drawing and bill of materials for each lift of concrete. (Show only one lift on a drawing). These drawings must be to scale and show all embedded items in sufficient detail for the proper installation and prosecution of the work. Identify all embedded electrical and/or mechanical items. The drawings must not be less than 594 by 841 mm 22 by 34 inches in size and use a sufficiently large scale

to clearly show all details of the structure covered by these drawings. Include a note on each lift drawing indicating all contract drawings from which the lift drawing was prepared. Submit [_____] copies of each drawing for review at least 60 days prior to scheduling the lift for placement.

3.2.2.6 Consolidation

Immediately after placing, consolidate each layer of concrete by internal vibrating equipment. Do not use vibrators to cause concrete to flow for significant distances within the forms. Hand spading may be used if necessary together with internal vibration along formed surfaces permanently exposed to view. Do not use form vibrators unless forms are specifically designed for this use and unless specifically approved. Insert vibrator vertically at uniform spacing over the entire area of placement. Use distance between insertions that is approximately 1.5 times the radius of action of the vibrator. The vibrator must penetrate rapidly to the bottom of the layer and at least 150 mm 6 inches into the preceding unhardened layer if such exists. Hold it stationary until the concrete is consolidated and then withdraw slowly. Consolidate slabs 200 mm 8 inches or less in depth by approved methods.

[3.2.2.7 Placing Concrete in Unformed Curved Sections

Finish the unformed portion of the ogee crest, spillway bucket, and similar features by placing concrete slightly above grade, consolidating and striking off to grade by accurate screeding. Screeding may be accomplished by semimechanical devices or by a mechanical screed that consolidates and screeds the surface in one operation. Ribs embedded in the fresh concrete as guides for screeds will not be permitted.

]3.2.2.8 Placing Concrete Underwater

Deposit concrete, described in Bid Item [____], through water by a tremie or concrete pump. Submit the methods and equipment used in advance of placement for review. Concrete buckets may be used only to charge the hopper on top of the tremie. Do not lower concrete buckets under water and discharge the concrete subaqueously. Ensure tremie is watertight and sufficiently large to permit a free flow of concrete. Keep discharge end of the pump line or tremie pipe submerged continuously in the concrete after placement starts. Effect underwater seal in a manner that will not produce undue contamination of the concrete or turbulence in the water. Placement must proceed without interruption until the concrete has been brought to the required height. Do not move tremie or pump lines horizontally during a placing operation, unless removed, moved, and properly restarted, and provide a sufficient number of tremies or pump lines so that the maximum horizontal flow will be limited to 4.5 m 15 feet.

]3.3 FINISHING

3.3.1 Unformed Surfaces

The ambient temperature of spaces adjacent to surfaces being finished must be no less than 5 degrees C 40 degrees F. In hot weather when the rate of evaporation of surface moisture, as determined by use of Figure 2.1.5 of ACI 305R, may reasonably be expected to exceed 1.0 kg/square meter 0.2 psf per hour, make provisions for windbreaks, shading, fog spraying, or evaporation retarding film in advance of placement to prevent plastic shrinkage cracks, and take such protective measures before, during, and

immediately after finishing as operations require. All unformed surfaces of concrete that are not to be covered by additional concrete or backfill must have a float finish, unless a trowel finish is specified, and must be true to elevation as shown on the drawings. Bring surfaces to receive additional concrete or backfill to the elevation shown and leave true and regular. Slope exterior surfaces for drainage unless otherwise shown in the drawing or directed. Make joints carefully with a jointing or edging tool. Protect finished surfaces from stains or abrasions. Consolidate concrete thoroughly before finishing operations commence or before leaving it for future concrete or backfill placement.

3.3.1.1 Float Finish

Surfaces to receive a float finish must be screeded and darbied or bullfloated to bring the surface to the required finish level with no coarse aggregate visible. Do not add water, cement, or mortar to the surface during the finishing operation. Floating may be performed by use of suitable hand floats or power-driven equipment. Use aluminum or magnesium hand floats. After the water sheen has disappeared, float the concrete, while still green but sufficiently hardened to bear a man's weight without deep imprint, to a true even plane.

3.3.1.2 Trowel Finish

**NOTE: Refer to the appropriate design memorandum
for surfaces to be trowel finished. Be sure these
are shown in the drawings.**

Apply a trowel finish to the following surfaces [____]; [____]; [____]. First, give concrete surfaces a float finish. After surface moisture has disappeared, trowel the surface to a smooth, even, dense finish, free from blemishes, including trowel marks. In lieu of hand finishing, an approved power finishing machine may be used in accordance with the directions of the machine manufacturer. A final hard steel troweling must be done by hand. Make joints carefully with a jointing or edging tool. Protect finished surfaces from stains or abrasions. Protect surface or edges likely to be injured during the construction period from damage.

[3.3.1.3 Broom Finish

**NOTE: Refer to the appropriate design memorandum
for surfaces to be broom finished. Be sure these
are shown in the drawings.**

Apply a broom finish to the following surfaces: [____]; [____]; [____]. The concrete surface to be broom finished must first be given a float finish. The surface must then be broomed with a [stiff fiber-bristle broom] [hair broom in a direction transverse to that of the traffic].

]3.3.1.4 Abrasive Aggregate Finish

NOTE: Refer to the appropriate design memorandum

for surfaces to receive the abrasive aggregate finish. Be sure this is shown in the drawings.

Apply an abrasive aggregate finish to the following surfaces: [____]; [____]; [____]. First, give concrete surface a float finish. Sprinkle abrasive aggregate uniformly over the surface immediately after floating, at a rate of no less than 1.22 kg/square meter 1/4 psf. Refloat the surface and then trowel to a smooth even finish that is uniform in texture and appearance including trowel marks. Immediately after curing, remove cement coating or laitance covering the abrasive aggregate by wire brushing, rubbing with abrasive stone, or sandblasting to expose the abrasive particles.

]3.3.1.5 High Velocity Finishes

NOTE: Refer to the appropriate design memorandum for surfaces to receive high velocity finishes. Be sure these are shown in the drawings.

Unformed surfaces subjected to high velocity flow (12 m/s) (40 fps) must receive a trowel finish.

]3.3.2 Formed Surface Repair

NOTE: Refer to EM 1110-2-2000 for direction on class of finish. Please note that definitions for class of finish have been changed recently. Class of finish must also be shown in the drawings. Paragraph CONSTRUCTION TOLERANCES, in PART 2, presents surface tolerances. Section 03 30 00 CAST-IN-PLACE CONCRETE presents materials for each class.

After removal of forms, remove all ridges, lips, and bulges on surfaces permanently exposed. Complete all repairs within 48 hours after form removal.

3.3.2.1 Classes A, A-HV, & B Finishes

For surfaces listed in Section 03 30 00 CAST-IN-PLACE CONCRETE, paragraph [____], and as shown in the drawings to have classes A, A-HV, and B finishes, repair surface defects as follows: chip defective areas, voids, and honeycombs smaller than 10 000 square mm 16 square inches in area and less than 13 mm 1/2 inches deep; bug holes exceeding 13 mm 1/2 inch in diameter and fill with dry-packed mortar; ream holes left by removal of tie rods and fill with the below specified material; define defective and unsound concrete areas larger than described by 13 mm 1/2 inch deep dovetailed saw cuts in a rectangular pattern with lines parallel to the formwork, remove the defective concrete by chipping and repair the void with replacement concrete. Brush-coat the prepared area with an epoxy resin meeting the requirements of ASTM C881/C881M, Type V; a latex bonding agent meeting the requirements of ASTM C1059/C1059M, Type II; or a neat cement grout after dampening the area with water. Fill the void with replacement concrete in accordance with the paragraph MATERIAL AND

PROCEDURE FOR REPAIRS below.

3.3.2.2 Class C Finish

For surfaces listed in Section 03 30 00 CAST-IN-PLACE CONCRETE, paragraph [____], and as shown in the drawings, repair defects as follows: chip defective areas, voids, and honeycombs smaller than 15 000 square mm 24 square inches and less than 50 mm 2 inches deep; bug holes exceeding 38 mm 1-1/2 inches in diameter and fill with dry-packed mortar; and ream holes left by removal of the tie rods and fill with dry-packed mortar. Define defective and unsound concrete areas larger than 15,000 square mm 24 square inches and deeper than 38 mm 1-1/2 inches by 13 mm 1/2 inch deep dovetailed saw cuts in a rectangular pattern, remove the defective concrete by chipping, and repair the void with replacement concrete. Brush-coat the prepared area with an epoxy resin meeting the requirements of ASTM C881/C881M, Type V; a latex bonding agent meeting the requirements of ASTM C1059/C1059M, Type II; or a neat cement grout after dampening the area with water. Fill the void with replacement concrete in accordance with the paragraph below.

3.3.2.3 Class D Finish

For surfaces listed in Section 03 30 00 CAST-IN-PLACE CONCRETE, paragraph [____], and as shown in the drawings to have class D finish, repair surface defects as follows: define defective areas, voids, and honeycombs greater than 30,000 square mm 48 square inches in area or more than 50 mm 2 inches deep by 13 mm 1/2 inch deep dovetailed saw cuts in a rectangular pattern, remove the defective concrete by chipping and repair the void with replacement concrete. Brush-coat the prepared area with an epoxy resin meeting the requirements of ASTM C881/C881M, Type V; a latex bonding agent meeting the requirements of ASTM C1059/C1059M, Type II; or a neat cement grout after dampening the area with water. Fill the void with replacement concrete in accordance with the following paragraph.

3.3.2.4 Material and Procedure for Repairs

Use cement in the dry-packed mortar or replacement concrete that is a blend of the cement used for production of project concrete and white portland cement properly proportioned so that the final color of the mortar or concrete will match adjacent concrete. Use trial batches to determine the proportions required to match colors. Provide dry-packed mortar consisting of one part cement to two and one-half parts fine aggregate. Use fine aggregate for production of project concrete. Remix the mortar over a period of at least 30 minutes without addition of water until it obtains the stiffest consistency that will permit placing. Compact mortar thoroughly into the prepared void by tamping, rodding, ramming, etc. and struck off to match adjacent concrete. Produce replacement concrete using project materials and proportion as directed by the Contracting Officer. Thoroughly compact it into the prepared void by internal vibration, tamping, rodding, ramming, etc. and strike off and finish to match adjacent concrete. Use forms to confine the concrete. If an expanding agent is used in the repair concrete, confine the repair thoroughly on all sides including the top surface. Do not use metal tools to finish permanently exposed surfaces. Cure repaired areas for 7 days. The temperature of the in situ concrete, adjacent air, and replacement mortar or concrete must be above 5 degrees C 40 degrees F during placement, finishing, and curing. Packaged materials meeting the requirements of ASTM C928/C928M may be used in lieu of dry-packed mortar when approved. Other methods and materials for repair may be used only

when approved in writing. Repairs of the so called "plaster-type" will not be permitted.

3.3.3 Grout-Cleaned Finish

NOTE: See the appropriate design memorandum and EM 1110-2-2000 for surfaces to receive a grout cleaned finish. Be sure this is shown in the drawings.

Give the surfaces of [_____] a grout-cleaned finish as hereinafter described, as approved by the Contracting Officer and after all required curing, cleaning, and repairs have been completed. Moist cure surfaces to be grout-cleaned for the required period of time before application of the grout-cleaned finish. Delay grout-cleaning until near the end of construction on all surfaces not to be painted to achieve uniformity of appearance and reduce the chance of discoloring caused by subsequent construction operations. The temperature of the air adjacent to the surface must be no less than 5 degrees C 40 degrees F for 24 hours prior to and 72 hours following the application of the finish. Complete finish for any area in the same day, and make the limits of a finished area at natural breaks in the finished surface. Wet surface to receive grout-cleaned finish thoroughly to prevent absorption of water from the grout but have no free water present. Then coat the surface with grout. Apply grout as soon as the surface of the concrete approaches surface dryness and vigorously and thoroughly rub over the area with clean burlap pads, cork floats, or stones to fill all voids. Compose grout of one part portland cement as used on the project, to two parts by volume of well-graded sand passing a 600-µm (No. 30) sieve mixed with water to the consistency of thick paint. Use white cement for all or part of the cement as approved to give the desired finish color. Apply uniform coating, completely filling all pits, air bubbles, and surface voids. While the grout is still plastic, remove all excess grout by working the surface with a rubber float, burlap pad, or other means. Then, after the surface whitens from drying (about 30 minutes at normal temperature), rub vigorously with clean burlap pads. Immediately after rubbing is completed, moist cure the finished surface continuously for 72 hours. Use burlap pads for this operation consisting of burlap stretched tightly around a board to prevent dishing the mortar in the voids.

3.4 CURING AND PROTECTION

Submit the curing media and methods to be used for review 30 days before concrete placement begins.

3.4.1 Curing Time

NOTE: Curing time may be extended if required by the thermal study. See the concrete materials design memorandum for the approved types of cementitious materials.

Cure all concrete by one of the following methods or combination of methods for the period of time given below corresponding to the cementing materials used in the concrete:

Type III portland cement	3 days
Type I portland cement	7 days
Portland cement in combination with silica fume	7 days
Type II portland cement	14 days
Portland cement blended with 25 percent or less fly-ash or GGBF slag	14 days
Portland cement blended with more than 25 percent fly-ash or GGBF slag	21 days

Begin curing immediately after placing. Provide all equipment needed for curing and protection of the concrete on hand and ready to install before actual concrete placement begins. Use curing medium and method, or the combination of media and methods, as approved in accordance with paragraph SUBMITTALS, SD-03 Product Data, submittal item "Curing".

3.4.2 Moist Curing

NOTE: This requirement is for hot weather curing only and has to be used under certain conditions only. Thermal cracking can occur when the difference in temperature between the interior concrete is more than 11 degrees C 20 degrees F higher than the surface temperature of a concrete placement. Tepid water is water at a temperature no more than 11 degrees C 20 degrees F cooler than the surface of the concrete placement. For massive placements, thermal insulation should be provided to reduce the temperature gradient between the interior and exterior of the placement.

[Moist cure concrete containing silica fum.] Moist cure horizontal and nearly horizontal surfaces by ponding, by covering with a minimum uniform thickness of 50 mm 2 inches of continuously saturated sand, or by covering with saturated nonstaining burlap or cotton mats. Rinse burlap and cotton mats to remove soluble substances before using. Moist cure other surfaces when approved or directed. Maintain concrete that is moist cured continuously, not periodically, wet for the duration of the entire curing period. Use water for curing complying with the requirements of the paragraph WATER in PART 2. If the water, sand, mats, etc. cause staining or discoloration of permanently exposed concrete surfaces, clean the surfaces by an approved method. When wood forms are left in place during curing, keep the forms continuously wet except for sealed insulation curing in cold weather. When steel forms are left in place on vertical surfaces during curing of concrete, [when using high-strength concrete] [when concrete being cured has a water-cement ratio less than 0.40] [placements with a minimum dimension greater than 600 mm 2 feet] carefully break loose the forms from the hardened concrete and continuously introduce curing water into the void. The temperature of the water should be tepid. Allow horizontal construction joints to dry sufficiently to

remove free water immediately prior to placing the next lift.

3.4.3 Membrane Curing

Membrane curing may be used on surfaces that are not specified or directed to receive moist curing and that are not to receive a grout-cleaned finish. Do not use membrane-forming curing compound on surfaces that contain protruding steel reinforcing, that are heated by free steam, that will have additional concrete bonded to them, or that are to be grout-cleaned.

3.4.3.1 Pigmented Curing Compound

Pigmented compound conforming to [ASTM C309](#), Type 2, Class A, may be used on surfaces that will not be exposed to view when the project is completed. Only pigmented compound of the styrene acrylate or chlorinated rubber formulation conforming to [ASTM C309](#), Class B, requirements may be used on surfaces that are to be painted or to receive bituminous roofing or water proofing or floors that are to receive adhesive applications of resilient flooring. Select curing compound for such use that is compatible with any subsequent paint, roofing, coating, or flooring specified elsewhere in the contract.

3.4.3.2 Nonpigmented Curing Compound

**NOTE: See the concrete materials design memorandum
for guidance on the optional sentence.**

Nonpigmented compound conforming to [ASTM C309](#), Type ID, containing a fugitive dye may be used on surfaces that will be exposed to view when the project is completed. The reflective requirements of [ASTM C309](#) are waived. [Shield surfaces cured with nonpigmented compound from direct rays of the sun for 3 days.]

3.4.3.3 Application

Apply curing compound to formed surfaces immediately after the forms are removed. Moisten surfaces thoroughly with water, and apply the curing compound as soon as free water disappears. Apply curing compound to unformed surfaces as soon as free water has disappeared provided steps have been taken when necessary to prevent premature loss of free water due to excessive evaporation as described in paragraph UNFORMED SURFACES above. Apply curing compound in a two-coat continuous operation by motorized power-spraying equipment or pressure-tank equipment operating at a minimum pressure of [520 kPa](#) [75 psi](#) with provisions for continuous agitation. The application equipment must be approved in advance. Do not use hand-operated pressure applicators ("garden sprayers") except in small, isolated areas as approved. Apply compound at a uniform coverage of no more than [10 square meters/L](#) [400 square feet/gallon](#) for each coat. Apply the second coat perpendicular to the first coat. Respray concrete surfaces that have been subjected to rainfall within 3 hours after the curing compound has been applied by the method and at the coverage specified. Protect all concrete surfaces on which the curing compound has been applied for the duration of the entire curing period from pedestrian and vehicular traffic and from any other influence that will disrupt the continuity of the curing membrane.

[3.4.4 Sheet Curing

NOTE: The only concrete that may be cured using sheet should be horizontal or nearly horizontal finished surfaces such as roof slabs, uncolored floors or the first course of two-course floors, or floors that are to be covered with tile or resilient flooring.

The following concrete surfaces may be cured using sheets: [____]; [____]; [____]. Use sheets only on horizontal or near horizontal surfaces. Use sheets complying with the requirements of ASTM C171, except do not use polyethylene sheet. Wet all surfaces thoroughly and completely cover with waterproof paper, or polyethylene-coated burlap. Lay covering with light-colored side up. Lap covering no less than 100 mm 4 inches and tape to form a continuous cover with completely closed joints. Use weighted sheet to prevent displacement so that it remains in contact with the concrete during the specified length of curing. Fold coverings down over exposed edges of slabs and secure by approved means. Repair sheets immediately or replace if tears or holes appear during the curing period.

]3.4.5 Sealed Insulation Curing

Between dates listed in paragraph COLD WEATHER PROTECTION below where cold weather protection is provided entirely by insulation, seal all joints in the insulation to retard moisture loss and maintain a seal throughout the curing period.

3.4.6 Protection

NOTE: Add more sophisticated requirements for vibration control where appropriate.

No fire or excessive heat is permitted near or in direct contact with concrete at any time. Do not operate vibratory earth compaction equipment or pile-driving equipment within 30 m 100 feet horizontally of concrete less than 5 days old. Blasting is not permitted within 30 m 100 feet horizontally of concrete less than 90 days old. Blasting plans must be approved by the Contracting Officer. Keep all galleries, conduits, and other openings through the concrete closed or sealed during the entire construction period. Protect the surface of the concrete from rain or snow during placing.

3.4.7 Cold Weather-Protection

NOTE: The editor must insert the insulating value and the calendar dates in the appropriate blanks. The values will be taken from the thermal study that was performed during design of the structure. The paragraph may be revised or expanded to provide varying insulating values and dates for various concrete features of the project in accordance with the thermal study.

Between [_____] of each year and [_____] of the following year, cover all concrete [less than 30 days old] [immediately after placing] for a period of [_____] days with insulation that provides an R value no less than [_____] square meter degree Celsius per watt hour square foot degree Fahrenheit per BTU. Submit a description of the materials and methods proposed for protection of the concrete, 60 days in advance of anticipated need date for review, when concrete is to be placed under cold-weather conditions.

- a. Maintain insulation in such a condition that the R value does not diminish during the period of protection. Protect edges and corners of the placement with a double layer of the insulation specified above for a minimum distance of 0.6 m 2 feet in all directions.
- b. Insulate concrete placed prior to the starting date from the starting date until it reaches an age of [_____] days. Insulate concrete placed after the starting date continuously during and subsequent to placement [until it reaches an age of [_____] days or] until the end of the protection period [, whichever comes first].
- c. Insulate forms in such a manner that the combined form-insulation system has a thermal resistance (R value) no less than that specified. Keep insulation and the combined form-insulation system in place for at least 5 days after placement of the concrete. After 5 days, forms and insulation on vertical surfaces may be removed for periods not to exceed 4 hours in a 24 hour period to allow forms to be moved, and insulation on horizontal surfaces may be removed for periods not to exceed 8 hours in a 24 hour period to allow reinforcement to be installed, insulation to be installed, lift joints to be prepared, etc. provided that suitable precautions are taken to prevent the concrete from being subjected at any time to ambient temperatures of minus 7 degrees C 20 degrees F or below.
- d. Insulate the first 1.8 m 6 feet of all steel protruding from insulated concrete with material having an R value as stated. Insulate all form bolts and metal ribs on the forms in a like manner. During the period of protection there must be no holes or openings in the insulation or between the insulation and concrete which permit ambient air to penetrate the insulation except as noted for construction purposes. Give special attention to seams, corners, and edges to prevent holes or openings in the insulation.

3.5 BASE PLATES AND BEARING PLATES

3.5.1 Setting of Plates

After being plumbed and properly positioned, provide full bearing column base plates, bearing plates for beams and similar structural members, and machinery and equipment base plates using nonshrink grout. The space between the top of the concrete bearing surface and the bottom of the plate must not be less than 1/24 of the width of the plate or 13 mm 1/2 inch, whichever is greater. Concrete surfaces must be clean, free of oil, grease, and laitance, and damp. Metal surfaces must be clean and free of oil, grease, and rust.

3.5.2 Nonshrink Grout

Use nonshrink grout conforming to the requirement of paragraph NONSHRINK

GROUT. Water content must be the minimum that will provide a flowable mixture and completely fill the space to be grouted without segregation, bleeding, or reduction of strength.

3.5.2.1 Mixing and Placing

Perform mixing and placing in conformance with the material manufacturer's instructions and as specified. Dry-mix ingredients thoroughly before adding water. After adding water, mix the batch for 3 minutes. Size batches to allow continuous placement of freshly mixed grout. Discard grout not used within 30 minutes after mixing. Fill the space between the top of the concrete or masonry bearing surface and the plate with the grout. Use forms consisting of wood or other suitable material for retaining the grout and remove after the grout has hardened. If Grade "A" grout is used, form all surfaces, including top surfaces, to provide restraint. Work placed grout to eliminate voids; however, avoid overworking and breakdown of the initial set. Do not retemper or subject grout to vibration from any source. Where clearances are unusually small, make placement under pressure with a grout pump. Maintain temperature of the grout, and of surfaces receiving the grout, at 20 to 30 degrees C 65 to 85 degrees F until after setting.

3.5.2.2 Treatment of Exposed Surfaces

Those types of grout containing metallic aggregate, Grade B or C grout, must, after setting, have exposed surfaces under cut back 1 inch from the edge of the base plate and immediately cover with a thick coat of mortar proportioned by weight of one part portland cement, two parts sand, and sufficient water to make the mixture placeable. The parge coat must have a smooth, dense finish. The exposed surface of other types of nonshrink grout must have a smooth, dense finish.

3.5.2.3 Curing

Cure grout and parge coats in conformance with paragraph CURING AND PROTECTION above.

[3.6 BLOCK-OUT CONCRETE

[3.6.1 Composition and Proportions

Provide block-out concrete composed of portland cement, water, fine and coarse aggregate, and admixtures. The concrete mixture proportions, including admixture, will be provided by the Contracting Officer. Use an expansive admixture to cause the blockout concrete to expand to fit snugly in the space that confines it. Use expansive admixture conforming to the requirements of ASTM C937 for grout fluidifier. Waste any block-out concrete not placed within 30 minutes after contact of the cement and admixture. Confine block-out on all sides to provide restraint.

][3.6.2 Placing Block-out Concrete

Provide block-outs as shown on the plans for the embedment of gate seal seats, gate guides, bulkhead guides, beams embedded for bulkhead seals, crane rails, and other embedded metalwork as appropriate. Prior to installation of embedded items, clean the block-outs or recesses in accordance with applicable requirements of the paragraph on construction joint treatment. After installation of embedded items and prior to placing any forms, clean all surfaces of the block-outs or recesses and

surfaces of items to be embedded thoroughly of all loose material, oil, grease, and other contaminants which might reduce the bond between the surfaces of the blockouts or recesses and new concrete. Exercise extreme caution in placing block-out concrete to avoid distortion or displacement of the embedded items.

3.7 TESTS AND INSPECTIONS

3.7.1 General

Perform the following inspection and tests as described, and, based upon the results of these inspections and tests, take the action required and submit reports as required. When, in the opinion of the Contracting Officer, the concreting operation is out of control, cease concrete placement. The laboratory performing the tests must be onsite and conform with the requirements given in **ASTM C1077**. The individuals who sample and test concrete or the constituents of concrete as required in this specification will have demonstrated a knowledge and ability to perform the necessary test procedures equivalent to the ACI minimum guidelines for certification of Concrete Field Testing Technicians, Grade I. The Government will inspect the laboratory, equipment, and test procedures prior to start of concreting operations and at least once per year thereafter for conformance with **ASTM C1077**. The individual who performs the inspection will have demonstrated a knowledge and ability equivalent to the ACI minimum guidelines for certification of [Concrete Transportation Construction Inspector (CTCI)] [Concrete Construction Inspector (CCI)].

3.7.2 Testing and Inspection Requirements

3.7.2.1 Fine Aggregate

NOTE: If the optional requirement to limit the amount of material passing the 75 μ m No. 200 sieve was invoked in paragraph AGGREGATES in PART 2, the requirement to perform ASTM C117 must be invoked in subparagraph a.

3.7.2.1.1 Grading

At least once during each shift when the concrete plant is operating, there make one sieve analysis and fineness modulus determination in accordance with **ASTM C136/C136M** [, **ASTM C117**] and **COE CRD-C 104** for the fine aggregate or for each fine aggregate if it is batched in more than one size or classification. The location at which samples are taken may be selected by the Contractor as the most advantageous for control. However, the Contractor is responsible for delivering fine aggregate to the mixer within specification limits. Record the results on a sheet on which are also shown the specification limits applicable to the project.

3.7.2.1.2 Fineness Modulus Control Chart

Group results for fineness modulus in sets of three consecutive tests, and plot the average and range of each group on a control chart. Draw the upper and lower control limits for average 0.10 units above and below the target fineness modulus, and the upper control limit for range 0.20 units above the target fineness modulus.

3.7.2.1.3 Corrective Action for Fine Aggregate Grading

When the amount passing any sieve is outside the specification limits, resample and retest the fine aggregate immediately. If there is another failure for any sieve, report the fact immediately. Whenever a point on the fineness modulus control chart, either for average or range, is beyond one of the control limits, double the frequency of testing. If two consecutive points are beyond the control limits, consider the process out of control and stop concreting. Notify the Contracting Officer, and take immediate steps to rectify the situation. After two consecutive points have fallen within the control limits, testing at the normal frequency may be resumed.

3.7.2.1.4 Moisture Content Testing

When in the opinion of the Contracting Officer the electric moisture meter is not operating satisfactorily, perform at least four tests for moisture content in accordance with [ASTM C566](#) during each 8-hour period of mixing plant operation. Select times for the tests randomly within the 8-hour period. Make an additional test whenever the slump is shown to be out of control or excessive variation in workability is reported by the placing foreman. When an electric moisture meter is operating satisfactorily, make at least two direct measurements of moisture content per week to check the calibration of the meter. Use results of tests for moisture content to adjust the added water in the control of the batch plant.

3.7.2.1.5 Moisture Content Corrective Action

Whenever the moisture content of the fine aggregate changes by 0.5 percent or more, adjust the scale settings for the fine-aggregate batcher and water batcher (directly or by means of a moisture compensation device).

3.7.2.2 Coarse Aggregate

3.7.2.2.1 Grading

At least once during each shift in which the concrete plant is operating, perform a sieve analysis in accordance with [ASTM C136/C136M](#) for each size of coarse aggregate. The location at which samples are taken may be selected by the Contractor as the most advantageous for production control. However, the Contractor is responsible for delivering the aggregate to the mixer within specification limits. A test record of samples of aggregate taken at the same locations must show the results of the current test as well as the average results of the five most recent tests including the current test. The Contractor may adopt limits for control coarser than the specification limits for samples taken other than as delivered to the mixer to allow for degradation during handling. When facilities are available to test samples five times as large as those required in [ASTM C136/C136M](#), averaging is not permitted.

3.7.2.2.2 Corrective Action for Grading

When the amount passing any sieve is outside the specification limits, resample and retest the coarse aggregate immediately. If the second sample fails on any sieve, report that fact. Where two consecutive averages of five tests (or two consecutive tests where large samples are used) are outside specification limits, consider the operation out of control, and report that fact, stop concreting, and take immediate steps

to correct the grading.

3.7.2.2.3 Coarse Aggregate Moisture Content

Make a test for moisture content of each size group of coarse aggregate at least once a shift. When two consecutive readings for smallest size coarse aggregate differ by more than 1.0 percent, increase frequency of testing to that specified previously for fine aggregate.

3.7.2.2.4 Coarse Aggregate Moisture Corrective Action

Whenever the moisture content of any size of coarse aggregate changes by 0.5 percent or more, adjust the scale setting for the coarse aggregate batcher and the water batcher to compensate for this.

3.7.2.2.5 Particle Shape Testing

When directed, a problem exists in connection with aggregate particle shape, make tests in accordance with [ASTM D4791](#). Testing frequency must not be less than one per day, when directed.

3.7.2.2.6 Particle Shape Corrective Action

When testing for particle shape is required, report two consecutive failures in the same sieve size immediately, and determine what corrective action is needed.

3.7.2.2.7 Material Finer than the [75-µm No. 200 Sieve](#)

When in the opinion of the Contracting Officer, a problem exists in connection with the cleanliness of aggregate, make tests in accordance with [ASTM C117](#). Testing frequency must be as directed.

3.7.2.2.8 Corrective Action for Material Finer than the [75-µm No. 200 Sieve](#)

When material finer than the [75-µm No. 200](#) sieve exceeds 1.0 percent of the weight of the aggregate finer than [37.5 mm 1-1/2 inches](#) or 0.5 percent of the weight of the aggregate coarser than [37.5 mm 1-1/2 inches](#), notify the Contracting Officer and initiate steps, such as washing or other corrective action, immediately.

3.7.2.3 Quality of Aggregates

NOTES: Tests should be those listed in paragraph
QUALITY OF AGGREGATES.

Use petrographic examination to identify deleterious
substances in aggregates. List deleterious
substances individually with respective limits.

3.7.2.3.1 Frequency of Quality Tests

Prior to submitting samples for mixture proportioning studies and 30 days prior to the start of concrete placement, perform the tests for aggregate quality in the following list. In addition, after the start of concrete placement, perform tests for aggregate quality in accordance with the following frequency schedule. Take samples tested after the start of

concrete placement immediately prior to entering the concrete mixer.

PROPERTY	FINE AGGREGATE	FREQUENCY COARSE AGGREGATE	TEST
Specific Gravity	Every 3 months	Every 3 months	ASTM C127 ASTM C128
Absorption	Every 3 months	Every 3 months	ASTM C127 ASTM C128
Durability (Procedure A)	Factor using Every 12 months	Every 12 months	COE CRD-C 144 ASTM C666/C666M
Clay Lumps and Friable Particles	Every 3 months	Every 3 months	ASTM C142/C142M
Material Finer than the 75- μ m (No. 200) Sieve	Every 3 months	Every 3 months	ASTM C117
Organic Impurities	Every 3 months	Not applicable	ASTM C40/C40M
L.A. Abrasion	Not applicable	Every 6 months	ASTM C131/C131M ASTM C535
Soft and Friable (Scratch Hardness)	Not applicable	Every 6 months	COE CRD-C 130
Petrographic Examination	Every 6 months	Every 6 months	ASTM C295/C295M
Chert, less than 2.40 specific gravity	Every 6 months	Every 6 months	ASTM C123/C123M
Coal and lignite, less than 2.00 specific gravity	Every 6 months	Every 6 months	ASTM C123/C123M

3.7.2.3.2 Corrective Action for Aggregate Quality

If the result of a quality test fails to meet the requirements for quality during submittal of samples for mixture-proportioning studies or immediately prior to start of concrete placement, change production procedures or materials and perform additional tests until the material meets the quality requirements prior to proceeding with either mixture-proportioning studies or starting concrete placement. After concrete placement commences, whenever the result of a test for quality fails the requirements, rerun the test immediately. If the second test fails the quality requirement, report the fact and take immediate steps to rectify the situation.

3.7.2.4 Scales

3.7.2.4.1 Weighing Accuracy

Check accuracy of the scales by test weights at least once a month for conformance with the applicable requirements of paragraph PLANT AND EQUIPMENT. Also make such tests as directed whenever there are variations in properties of the fresh concrete that could result from batching errors.

3.7.2.4.2 Batching and Recording Accuracy

Check the accuracy of each batching and recording device once a week during a weighing operation by noting and recording the required weight, recorded weight, and the actual weight batched. Confirm that the calibration devices described in paragraph PLANT AND EQUIPMENT in PART 2, for checking the accuracy of dispensed admixtures, are operating properly.

3.7.2.4.3 Scales Corrective Action

When either the weighing accuracy or batching accuracy does not comply with specification requirements, do not operate the plant until necessary adjustments or repairs have been made. Correct discrepancies in recording accuracies immediately.

3.7.2.5 Batch-Plant Control

Control the measurement of all constituent materials including cementitious materials, each size of aggregate, water, and admixtures continuously. Adjust aggregate weights and amount of added water as necessary to compensate for free moisture in the aggregates. Adjust the amount of air-entraining agent to control air content within specified limits. Prepare a report indicating type and source of cement used, type and source of pozzolan or slag used, amount and source of admixtures used, aggregate source, the required aggregate and water weights per cubic meter yard, amount of water as free moisture in each size of aggregate, and the batch aggregate and water weights per cubic meter yard for each class of concrete batched during plant operation.

3.7.2.6 Concrete

3.7.2.6.1 Air Content

Make at least two tests for air content on randomly selected batches of each concrete mixture produced during each 8 hour period of concrete production. Make additional tests when excessive variation in workability is reported. Make tests in accordance with ASTM C231/C231M. Plot the average of each set of two tests for each mixture on control charts on which the average percent and upper and lower limits are set in accordance with paragraph MATERIALS FOR MIXTURE PROPORTIONING STUDIES, in PART 1, for each NMSA. Plot the range between two consecutive tests for each mixture on a control chart on which the upper control limit is 3.0 percent. Normally take samples for air content at the mixer, however the Contractor is responsible for delivering the concrete to the forms at the proper air content. Take samples at the placement site as often as required, depending on the Contractor's delivery method, to determine any air loss.

3.7.2.6.2 Air Content Corrective Action

Whenever points on the control chart approach the upper or lower control

limits, an adjustment should be made in the amount of air-entraining admixture batched. If a single test result is outside the specification limit, immediate adjustment is mandatory. As soon as practical after each adjustment, make another test to verify the correction of the adjustment. Whenever a point falls above the upper control for range, calibrate the dispenser to ensure that it is operating correctly and with good reproducibility. Whenever two consecutive points either for average or range are outside the control limits, notify the Contracting Officer.

3.7.2.6.3 Slump Testing

Make at least two slump tests in accordance with [ASTM C143/C143M](#) on each concrete mixture produced during each 8-hour period or less of concrete production each day. Make additional tests when excessive variation in workability is reported. Plot the result of each test for each mixture on a control chart on which the upper and lower limits are set as specified in paragraph SLUMP. Plot the range on a control chart on which the upper control limit is [50 mm 2 inches](#). Take samples for slump at the mixer, however the Contractor is responsible for delivering the concrete to the placement site at the stipulated slump. If the Contractor's materials or transportation methods cause slump loss between the mixer and the placement, take samples at the placement site as often as required by the Contracting Officer.

3.7.2.6.4 Slump Corrective Action

Whenever points on the control chart approach the upper or lower control limits, make an adjustment in the batch weights of water and fine aggregate. The adjustments are to be made so that the total water content does not exceed that amount specified in the mixture proportions provided based on the free water available with the aggregates and that amount of water batched. If the adjustments to the batch weights of water and aggregates do not satisfactorily produce the required slump, the Contracting Officer may adjust the mixture proportions if the fine-aggregate moisture content is stable and within the required limits. When a single slump is outside the control limits, such adjustment is mandatory. As soon as practical after each adjustment, make another test to verify the correctness of the adjustment. Whenever two consecutive individual slump tests, made during a period when there was no adjustment of batch weights, produce a point on the control chart for range above the upper control limits, consider the slump to be out of control, halt the concreting operation, and undertake additional testing for aggregate moisture content required, and take action immediately to correct the problem.

3.7.2.6.5 Compression Test Cylinders

Make at least one set of test cylinders each shift on each different concrete mixture placed during the shift. Make additional sets of test cylinders, as directed, when the mixture proportions are changed or when low strengths have been detected. Develop a random sampling plan for approval by the Contracting Officer prior to start of construction. Assure that sampling is done in a completely random and unbiased, not just haphazard, manner. Provide a set of test cylinders for structural concrete containing Type I or Type II portland cement only consisting of four cylinders, two to be tested at 7 days and two at 28 days. Provide a set of test cylinders for all other concrete consisting of six cylinders, two to be tested at 7 days, two at 28 days, and two at 90 days. In addition, for all concrete except that containing Type I or Type II

portland cement only, every 2 months make four additional cylinders and test two at 6 months of age and test two at 12 months of age. Mold and cure all test specimens in accordance with [ASTM C31/C31M](#) and test in accordance with [ASTM C39/C39M](#). Report all compressive strength tests immediately. Keep quality control charts for individual strength tests, moving average for strength and moving average for range for each mixture. The charts must be similar to those found in [ACI 214R](#).

3.7.2.7 Inspection Before Placing

Inspect foundation or construction joints, forms, and embedded items in sufficient time prior to each concrete placement in order to certify that they are ready to receive concrete. Report results of each inspection in writing.

3.7.2.8 Concrete Placement

3.7.2.8.1 Placing Inspection

The placing foreman must supervise all placing operations, must determine that the correct quality of concrete or grout is placed in each location as directed, and is responsible for measuring and recording concrete temperatures and ambient temperature hourly during placing operations, weather conditions, time of placement, volume yardage placed, and method of placement.

3.7.2.8.2 Placing Corrective Action

Do not permit placing to begin until an adequate number of vibrators in working order with competent operators are available is verified. Do not continue placing if any pile of concrete is inadequately consolidated. If any batch of concrete fails to meet the temperature requirements, take immediate steps to improve temperature controls.

3.7.2.9 Vibrators

3.7.2.9.1 Vibrator Testing and Use

Determine frequency and amplitude of each vibrator in accordance with [COE CRD-C 521](#) prior to initial use and at least once a month when concrete is being placed. Make additional tests as directed when a vibrator does not appear to be adequately consolidating the concrete. Determine the frequency while the vibrator is operating in concrete with the tachometer being held against the upper end of the vibrator head while almost submerged and just before the vibrator is withdrawn from the concrete. Determine the amplitude with the head vibrating in air. Take two measurements, one near the tip and another near the upper end of the vibrator head, and average these results. Report make, model, type, and size of the vibrator and frequency and amplitude results in writing.

3.7.2.9.2 Vibrator Corrective Action

Remove any vibrator not meeting the requirements of paragraph PREPARATION FOR PLACING above immediately from service and repair or replace.

3.7.2.10 Curing

3.7.2.10.1 Moist Curing Inspections

At least twice each shift, and twice per day on nonwork days, inspect all areas subject to moist curing. Note and record the surface moisture condition.

3.7.2.10.2 Moist Curing Corrective Action

When a daily inspection report lists an area of inadequate moistness, take immediate corrective action, and extend the required curing period for those areas by one (1) day.

3.7.2.10.3 Membrane Curing Inspection

Do not apply curing compound until the Contractor's authorized representative has verified that the compound is properly mixed and ready for spraying. At the end of each operation, estimate the quantity of compound used by measurement of the container and the area of concrete surface covered and compute the rate of coverage in **square meters/L square feet per gallon**. Note whether or not coverage is uniform.

3.7.2.10.4 Membrane Curing Corrective Action

When the coverage rate of the curing compound is less than that specified or when the coverage is not uniform, spray the entire surface again.

3.7.2.10.5 Sheet Curing Inspection

At least once each shift and once per day on nonwork days, inspect all areas being cured using sheets. Note and record the condition of the covering and the tightness of the laps and tapes.

3.7.2.10.6 Sheet Curing Corrective Action

When a daily inspection report lists any tears, holes, or laps or joints that are not completely closed, repair the tears and holes promptly or replace the sheets, close the joints, and extend the required curing period for those areas by one day.

3.7.2.11 Cold Weather Protection and Sealed Insulation Curing

At least once each shift and once per day on nonwork days inspect all areas subject to cold weather protection. Inspect the protection system for holes, tears, unsealed joints, or other incongruities which could result in damage to the concrete. Take special attention at edges, corners, and thin sections. Note, correct, and report any deficiencies.

3.7.2.12 Cold Weather Protection Corrective Action

When a daily inspection report lists any holes, tears, unsealed joints, or other incongruities, correct the deficiency immediately and extend the period of protection for one (1) day.

3.7.2.13 Mixer Uniformity

NOTE: The optional phrases should be used if the

Contractor is to perform the initial test.
Correlate with paragraph PLANT AND EQUIPMENT in PART
2.

3.7.2.13.1 Stationary Mixers

[Prior to the start of concrete placing and] once every 3 months when concrete is being placed, or once for every 57,000 cubic meters 75,000 cubic yards of concrete placed, whichever results in the longest time, determine interval uniformity of concrete mixing in accordance with paragraph PLANT AND EQUIPMENT in PART 2. [The initial and] every fourth set of tests must be regular tests performed on three batches of concrete. Intermediate uniformity tests must be abbreviated tests performed on a single batch of concrete. If the mixer fails the abbreviated test, perform a regular test immediately. Whenever adjustments in a mixer or increased mixing time are required because of failure of a uniformity test, reevaluate the mixer by a regular test after the adjustments have been completed. If the Contractor proposes to reduce a mixing time, perform a regular test to evaluate the proposed time. Perform additional testing when directed when there is visible evidence of possible improper mixer performance. Report results of all uniformity tests in writing.

3.7.2.13.2 Truck Mixers

Prior to the start of concrete placing and at least once every 6 months when concrete is being placed, determine uniformity of concrete in accordance with ASTM C94/C94M. Select truck mixers randomly for testing. When satisfactory performance is found in one truck mixer, the performance of mixers of substantially the same design and condition of the blades may be regarded as satisfactory. Report results of tests in writing.

3.7.2.14 Mixer Uniformity Corrective Action

When a mixer fails to meet mixer uniformity requirements, either increase the mixing time, change batching sequence, reduce batch size, or make adjustments to the mixer until compliance is achieved.

3.7.3 Reports

Report all results of tests or inspections conducted informally as they are completed and in writing daily. Prepare a weekly report for the updating of control charts covering the entire period from the start of the construction season through the current week. During periods of cold weather protection, make daily reports of pertinent temperatures. These requirements do not relieve the Contractor of the obligation to report certain failures immediately as required in preceding paragraphs. Confirm such reports of failures and the action taken in writing in the routine reports. The Contracting Officer has the right to examine all contractor quality control records.

-- End of Section --