
USACE / NAVFAC / AFCEA UFGS-07212 (August 2004)

Preparing Activity: NAVFAC Superseding
UFGS-07212N (September 1999)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated 23 June 2005

SECTION TABLE OF CONTENTS

DIVISION 07 - THERMAL AND MOISTURE PROTECTION

SECTION 07212

MINERAL FIBER BLANKET INSULATION

08/04

PART 1 GENERAL

- 1.1 REFERENCES
- 1.2 SUBMITTALS
- 1.3 DELIVERY, STORAGE, AND HANDLING
 - 1.3.1 Delivery
 - 1.3.2 Storage
- 1.4 SAFETY PRECAUTIONS
 - 1.4.1 Respirators
 - 1.4.2 Smoking
 - 1.4.3 Other Safety Concerns

PART 2 PRODUCTS

- 2.1 BLANKET INSULATION
 - 2.1.1 Thermal Resistance Value (R-VALUE)
 - 2.1.2 Recycled Materials
 - 2.1.3 Prohibited Materials
- 2.2 SILL SEALER INSULATION
- 2.3 BLOCKING
- 2.4 VAPOR RETARDER
- 2.5 PRESSURE SENSITIVE TAPE
- 2.6 ACCESSORIES
 - 2.6.1 Adhesive
 - 2.6.2 Mechanical Fasteners
 - 2.6.3 Wire Mesh

PART 3 EXECUTION

- 3.1 EXISTING CONDITIONS
- 3.2 PREPARATION
 - 3.2.1 Blocking at Attic Vents and Access Doors
 - 3.2.2 Blocking Around Heat Producing Devices
- 3.3 INSTALLATION
 - 3.3.1 Insulation
 - 3.3.1.1 Electrical wiring

- 3.3.1.2 Continuity of Insulation
- 3.3.1.3 Installation at Bridging and Cross Bracing
- 3.3.1.4 Cold Climate Requirement
- 3.3.1.5 Insulation Blanket with Affixed Vapor Retarder
- 3.3.1.6 Insulation without Affixed Vapor Retarder
- 3.3.1.7 Sizing of Blankets
- 3.3.1.8 Special Requirements for Ceilings
- 3.3.1.9 Installation of Sill Sealer
- 3.3.1.10 Special Requirements for Floors
- 3.3.1.11 Access Panels and Doors
- 3.3.2 Installation of Separate Vapor Retarder

-- End of Section Table of Contents --

USACE / NAVFAC / AFCEA UFGS-07212 (August 2004)

Preparing Activity: NAVFAC Superseding
UFGS-07212N (September 1999)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated 23 June 2005

SECTION 07212

MINERAL FIBER BLANKET INSULATION 08/04

NOTE: This guide specification covers the requirements for mineral fiber blanket thermal insulation in attics, ceilings, walls, and floors.

Comments and suggestions on this guide specification are welcome and should be directed to the technical proponent of the specification. A listing of technical proponents, including their organization designation and telephone number, is on the Internet.

Recommended changes to a UFGS should be submitted as a Criteria Change Request (CCR).

Use of electronic communication is encouraged.

Brackets are used in the text to indicate designer choices or locations where text must be supplied by the designer.

NOTE: This guide specification is intended for both retrofit of existing buildings and new construction.

NOTE: On the drawings, show:

1. Locations where insulation will be used.
2. Thermal resistance value (R-Value) for each location.
3. Location of vapor retarder, if required.
4. Location and size of attic ventilation openings where required.

NOTE: Attic Ventilation

1. Provide net, unobstructed ventilation areas to attics over insulated ceilings as recommended by ASHRAE Handbook of Fundamentals, Chapter 21 and as follows:
2. For attics with vapor retarder, provide 0.1 square meter one square foot of net ventilation area for each 30 square meters 300 square feet of attic floor area.
3. For attics without vapor retarder, provide 0.1 square meter one square foot of net ventilation area for each 15 square meters 150 square feet of attic floor area.
4. For insulation of cathedral ceilings, provide at least a 50 mm 2 inch gap between upper face of insulation and underside of roof sheathing. Provide ventilation openings at bottom and top of ventilated cavity; show on drawings.

NOTE: Develop and specify density, type of material, and thickness of mineral fiber blanket insulation used for sound control based on acoustic analysis. For reduction of sound transmission through walls, select a blanket thickness 13 mm 1/2 inch greater than the wall cavity. Edit this specification accordingly.

PART 1 GENERAL

1.1 REFERENCES

NOTE: Issue (date) of references included in project specifications need not be more current than provided by the latest guide specification. Use of SpecsIntact automated reference checking is recommended for projects based on older guide specifications.

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

ASTM INTERNATIONAL (ASTM)

ASTM C 665	(2001e1) Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured Housing
ASTM C 930	(1999) Potential Health and Safety Concerns Associated with Thermal

Insulation Materials and Accessories

ASTM D 3833/D 3833M	(1996; R 2001) Water Vapor Transmission of Pressure-Sensitive Tapes
ASTM D 4397	(2002) Polyethylene Sheeting for Construction, Industrial, and Agricultural Applications
ASTM D 828	(1997; R 2002) Tensile Properties of Paper and Paperboard Using Constant-Rate-of-Elongation Apparatus
ASTM E 136	(2004) Behavior of Materials in a Vertical Tube Furnace at 750 Degrees C
ASTM E 84	(2004) Surface Burning Characteristics of Building Materials
ASTM E 96	(2000e1) Water Vapor Transmission of Materials

NATIONAL FIRE PROTECTION ASSOCIATION (NFPA)

NFPA 211	(2003) Chimneys, Fireplaces, Vents, and Solid Fuel-Burning Appliances
NFPA 31	(2001) Installation of Oil Burning Equipment
NFPA 54	(2002) National Fuel Gas Code
NFPA 70	(2005) National Electrical Code

TECHNICAL ASSOCIATION OF THE PULP AND PAPER INDUSTRY (TAPPI)

TAPPI T803 OM	(1999) Puncture Test of Container Board
---------------	---

U.S. NATIONAL ARCHIVES AND RECORDS ADMINISTRATION (NARA)

29 CFR 1910.134	Respiratory Protection
-----------------	------------------------

1.2 SUBMITTALS

NOTE: Submittals must be limited to those necessary for adequate quality control. The importance of an item in the project should be one of the primary factors in determining if a submittal for the item should be required.

A "G" following a submittal item indicates that the submittal requires Government approval. Some submittals are already marked with a "G". Only delete an existing "G" if the submittal item is not complex and can be reviewed through the Contractor's Quality Control system. Only add a "G" if the submittal is sufficiently important or complex in context of the project.

For submittals requiring Government approval on Army projects, a code of up to three characters within the submittal tags may be used following the "G" designation to indicate the approving authority. Codes for Army projects using the Resident Management System (RMS) are: "AE" for Architect-Engineer; "DO" for District Office (Engineering Division or other organization in the District Office); "AO" for Area Office; "RO" for Resident Office; and "PO" for Project Office. Codes following the "G" typically are not used for Navy projects.

Submittal items not designated with a "G" are considered as being for information only for Army projects and for Contractor Quality Control approval for Navy projects.

Government approval is required for submittals with a "G" designation; submittals not having a "G" designation are [for Contractor Quality Control approval.] [for information only. When used, a designation following the "G" designation identifies the office that will review the submittal for the Government.] The following shall be submitted in accordance with Section 01330 SUBMITTAL PROCEDURES:

SD-03 Product Data

Blanket insulation

Sill sealer insulation

Vapor retarder

Pressure sensitive tape

Accessories

SD-08 Manufacturer's Instructions

Insulation

1.3 DELIVERY, STORAGE, AND HANDLING

1.3.1 Delivery

Deliver materials to site in original sealed wrapping bearing manufacturer's name and brand designation, specification number, type, grade, R-value, and class. Store and handle to protect from damage. Do not allow insulation materials to become wet, soiled, crushed, or covered with ice or snow. Comply with manufacturer's recommendations for handling, storing, and protecting of materials before and during installation.

1.3.2 Storage

Inspect materials delivered to the site for damage; unload and store out of weather in manufacturer's original packaging. Store only in dry locations, not subject to open flames or sparks, and easily accessible for inspection

and handling.

1.4 SAFETY PRECAUTIONS

1.4.1 Respirators

Provide installers with dust/mist respirators, training in their use, and protective clothing, all approved by National Institute for Occupational Safety and Health (NIOSH)/Mine Safety and Health Administration (MSHA) in accordance with 29 CFR 1910.134.

1.4.2 Smoking

Do not smoke during installation of blanket thermal insulation.

1.4.3 Other Safety Concerns

Consider other safety concerns and measures as outlined in ASTM C 930.

PART 2 PRODUCTS

2.1 BLANKET INSULATION

NOTE: Fire Safety Requirements

1. Most vapor retarder materials and the binder used in some mineral fiber insulations are combustible. Do not leave such material exposed to accessible spaces, but cover with fire retardant finish.

2. See MIL-HDBK-1008, and local building code for fire retardant classifications required, flame spread and smoke developed ratings, and other fire protection requirements, such as finish materials required in various occupancies.

ASTM C 665, Type [I, blankets without membrane coverings] [and] [II, blankets with non-reflecting coverings] [and] [III, blankets with reflective coverings]; Class [A, membrane-faced surface with a flame spread of 25 or less] [B, membrane-faced surface with a flame propagation resistance; critical radiant flux of 0.12 W/m² 0.11 Btu/ft² or greater], except a flame spread rating of [25] [75] [100] or less [and a smoke developed rating of 150 or less] when tested in accordance with ASTM E 84.

2.1.1 Thermal Resistance Value (R-VALUE)

NOTE: Select R-Value for Thermal Insulation required to meet the energy target/budget as indicated in MIL-HDBK-1190, Facility Planning Design Guide. Preferably show R-Value on drawings. If R-Values are not shown on drawings, specify here.

As indicated

2.1.2 Recycled Materials

Provide Thermal Insulation containing recycled materials to the extent practicable, provided the material meets all other requirements of this section. The minimum required recycled materials content by weight are:

Rock Wool: 75 percent slag
Fiberglass: 20 to 25 percent glass cullet

2.1.3 Prohibited Materials

Do not provide asbestos-containing materials.

[2.2 SILL SEALER INSULATION

ASTM C 665, Type I.

]2.3 BLOCKING

Wood, metal, unfaced mineral fiber blankets in accordance with ASTM C 665, Type I, or other approved materials. Use only non-combustible materials meeting the requirements of ASTM E 136 for blocking around chimneys and heat producing devices.

[2.4 VAPOR RETARDER

NOTE:

1. Determine the need for a water vapor retarder and its required permeance value based on a project and climate specific moisture analysis. For guidance see ASHRAE Handbook of Fundamentals, Chapter 20, "Thermal Insulations and Vapor Retarders;" ASTM C 755, "Selection of Vapor Retarders for Thermal Insulations;" and MIL-HDBK-1011/1, "Tropical Engineering" (for humid climates). The computer Program "MOIST" which is on CCB, is a user friendly tool based on hourly weather data that provides information on moisture content of materials and on the duration of high moisture content excursions. Traditionally, vapor retarders were considered materials having a permeance of 5.72×10^{-8} g/Pa.s.m² 1 perm (grain/h*ft²*in.Hg) or less. However, that value may not be adequate for the particular construction or climate and in some instances a much lower value should be specified.

2. Vapor retarders, where required, can be provided as membranes or, alternatively, vapor retardant finishes labeled by manufacturer as having a water vapor permeance of no more than the required value can be used. Alternate materials include: Paints, vinyl wall coverings, or foil-faced gypsum board. Specify these in Sections 09900, "Painting," Section 09955, "Vinyl-Coated Fabric Wall Covering," or Section 09250, "Gypsum Board," respectively and delete all paragraphs and references relating to vapor retarders from this section.

3. A vapor retarder is only effective if it prevents diffusion of water vapor as well as the passage of moisture laden air through openings and around material. Accordingly, proper installation to assure air tightness by sealing of joints, tears, and around utility penetrations is as important as proper selection of water vapor retarder materials.

4. Vapor retarders not only retard movement of water vapor into building envelope cavities, but also retard drying out of moisture that may have infiltrated the cavity. Accordingly, use vapor retarders only where their need is indicated by the moisture analysis.

[a. 0.15 mm 6 mil thick polyethylene sheeting conforming to ASTM D 4397 and having a water vapor permeance of 5.72×10^{-8} g/Pa.s.m2 1 perm or less when tested in accordance with ASTM E 96.]

[b. Membrane with the following properties:

Water Vapor Permeance: ASTM E 96: $[5.72 \times 10^{-8}]$ [_____] g/Pa.s.m2
[1] [_____] perm
[Maximum Flame Spread: ASTM E 84: [25] [50] [_____]]
[Combustion Characteristics: Passing ASTM E 136]
[Puncture Resistance: TAPPI T803 OM: [15] [25] [50]]
[Tensile Strength: ASTM D 828: [15] [20] [35]]]

]2.5 PRESSURE SENSITIVE TAPE

As recommended by the vapor retarder manufacturer and having a water vapor permeance rating of 5.72×10^{-8} g/Pa.s.m2 one perm or less when tested in accordance with ASTM D 3833/D 3833M.

2.6 ACCESSORIES

2.6.1 Adhesive

As recommended by the insulation manufacturer.

2.6.2 Mechanical Fasteners

Corrosion resistant fasteners as recommended by the insulation manufacturer.

2.6.3 Wire Mesh

Corrosion resistant and as recommended by the insulation manufacturer.

PART 3 EXECUTION

3.1 EXISTING CONDITIONS

Note: For retrofit projects, inspect facility to determine conditions which may adversely affect execution of work or create safety hazard. Identify relevant conditions on the drawings and, if

required, develop additional specification sections for corrective actions. Conditions that warrant investigation:

1. Discolorations or mold growth indicating previous water leaks.
2. Heat producing devices, such as recessed lighting fixtures, chimneys, and flues.
3. Faulty electrical systems:
 - (a) Lights dimming or flickering
 - (b) Fuses blowing
 - (c) Circuit breakers tripping frequently
 - (d) Electrical sparks and "glowing" from receptacles
 - (e) Cover plates on switches and outlets warm to touch.

Before installing insulation, ensure that areas that will be in contact with the insulation are dry and free of projections which could cause voids, compressed insulation, or punctured vapor retarders. If moisture or other conditions are found that do not allow the workmanlike installation of the insulation, do not proceed but notify Contracting Officer of such conditions.

3.2 PREPARATION

3.2.1 Blocking at Attic Vents and Access Doors

Prior to installation of insulation, install permanent blocking to prevent insulation from slipping over, clogging, or restricting air flow through soffit vents at eaves. [Install permanent blocking around attic trap doors.] [Install permanent blocking to maintain accessibility to equipment or controls that require maintenance or adjustment.]

3.2.2 Blocking Around Heat Producing Devices

Install non-combustible blocking around heat producing devices to provide the following clearances:

- a. Recessed lighting fixtures, including wiring compartments, ballasts, and other heat producing devices, unless these are certified by the manufacturer for installation surrounded by insulation: 75 mm 3 inches from outside face of fixtures and devices or as required by NFPA 70 and, if insulation is to be placed above fixture or device, 600 mm 24 inches above fixture.
- b. Masonry chimneys or masonry enclosing a flue: 50 mm 2 inches from outside face of masonry. Masonry chimneys for medium and high heat operating appliances: Minimum clearances required by NFPA 211.
- c. Vents and vent connectors used for venting the products of combustion, flues, and chimneys other than masonry chimneys:

Minimum clearances as required by NFPA 211.

f. Gas Fired Appliances: Clearances as required in NFPA 54.

g. Oil Fired Appliances: Clearances as required in NFPA 31.

Blocking around flues and chimneys is not required when insulation blanket, including any attached vapor retarder, passed ASTM E 136, in addition to meeting all other requirements stipulated in Part 2. Blocking is also not required if the chimneys are certified by the manufacturer for use in contact with insulating materials.

3.3 INSTALLATION

3.3.1 Insulation

Install and handle insulation in accordance with manufacturer's instructions. Keep material dry and free of extraneous materials. Ensure personal protective clothing and respiratory equipment is used as required. Observe safe work practices.

3.3.1.1 Electrical wiring

Do not install insulation in a manner that would sandwich electrical wiring between two layers of insulation.

3.3.1.2 Continuity of Insulation

Install blanket insulation to butt tightly against adjoining blankets and to studs, rafters, joists, sill plates, headers and any obstructions. [Where insulation required is thicker than depth of joist, provide full width blankets to cover across top of joists.] Provide continuity and integrity of insulation at corners, wall to ceiling joints, roof, and floor. Avoid creating thermal bridges.

3.3.1.3 Installation at Bridging and Cross Bracing

NOTE: Specify only unfaced blankets in installations with bridging and cross bracing. If a vapor retarder is required, specify a separate vapor retarder.

Insulate at bridging and cross bracing by splitting blanket vertically at center and packing one half into each opening. Butt insulation at bridging and cross bracing; fill in bridged area with loose or scrap insulation.

[3.3.1.4 Cold Climate Requirement

Place insulation to the outside of pipes.

] [3.3.1.5 Insulation Blanket with Affixed Vapor Retarder

Locate vapor retarder as indicated. Do not install blankets with affixed vapor retarders unless so specified. Unless the insulation manufacturer's instructions specifically recommend not to staple the flanges of the vapor retarder facing, staple flanges of vapor retarder at 150 mm 6 inch intervals flush with face or set in the side of truss, joist, or stud.

Avoid gaps and bulges in insulation and "fishmouth" in vapor retarders. Overlap both flanges when using face method. Seal joints and edges of vapor retarder with pressure sensitive tape. Stuff pieces of insulation into small cracks between trusses, joists, studs and other framing, such as at attic access doors, door and window heads, jambs, and sills, band joists, and headers. Cover these insulated cracks with vapor retarder material and tape all joints with pressure sensitive tape to provide air and vapor tightness.

] [3.3.1.6 Insulation without Affixed Vapor Retarder

Provide snug friction fit to hold insulation in place. Stuff pieces of insulation into cracks between trusses, joists, studs and other framing, such as at attic access doors, door and window heads, jambs, and sills, band joists, and headers.

] 3.3.1.7 Sizing of Blankets

Provide only full width blankets when insulating between trusses, joists, or studs. Size width of blankets for a snug fit where trusses, joists or studs are irregularly spaced.

] [3.3.1.8 Special Requirements for Ceilings

Place insulation under electrical wiring occurring across joists. Pack insulation into narrowly spaced framing. Do not block flow of air through soffit vents. [Attach insulation to attic door by adhesive or staples.]

] [3.3.1.9 Installation of Sill Sealer

Size sill sealer insulation and place insulation over top of masonry or concrete perimeter walls or concrete perimeter floor slab on grade. Fasten sill plate over insulation.

] [3.3.1.10 Special Requirements for Floors

Hold insulation in place with corrosion resistant wire mesh, wire fasteners, or wire lacing.

] [3.3.1.11 Access Panels and Doors

Affix blanket insulation to access panels greater than one square foot and access doors in insulated floors and ceilings. Use insulation with same R-Value as that for floor or ceiling.

] [3.3.2 Installation of Separate Vapor Retarder

Apply continuous vapor retarder as indicated. Overlap joints at least 150 mm 6 inches and seal with pressure sensitive tape. Seal at sill, header, windows, doors and utility penetrations. Repair punctures or tears with pressure sensitive tape.

]

-- End of Section --