
USACE / NAVFAC / AFCEC / NASA UFGS-09 65 00 (August 2010)
Change 1 - 02/13

Preparing Activity: USACE Superseding
UFGS-09 65 00 (February 2009)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated July 2015

SECTION TABLE OF CONTENTS

DIVISION 09 - FINISHES

SECTION 09 65 00

RESILIENT FLOORING

08/10

PART 1 GENERAL

- 1.1 REFERENCES
- 1.2 SYSTEM DESCRIPTION
 - 1.2.1 Environmental Data
 - 1.2.2 Fire Resistance Requirements
 - 1.2.3 Other Submittal Requirements
- 1.3 SUSTAINABILITY REPORTING
- 1.4 SUBMITTALS
- 1.5 DELIVERY, STORAGE, AND HANDLING
- 1.6 ENVIRONMENTAL REQUIREMENTS
- 1.7 SCHEDULING
- 1.8 WARRANTY
- 1.9 EXTRA MATERIALS

PART 2 PRODUCTS

- 2.1 VINYL COMPOSITION TILE [TYPE [A][_____]]
- 2.2 SHEET VINYL FLOORING [TYPE [A][_____]]
- 2.3 RUBBER TILE [TYPE [A][_____]]
- 2.4 RUBBER SHEET FLOORING [TYPE [A] [_____]]
- 2.5 SOLID VINYL TILE [TYPE [A][_____]]
- 2.6 SHEET LINOLEUM [TYPE [A][_____]]
- 2.7 LINOLEUM TILE [TYPE [A][_____]]
- 2.8 CORK
- 2.9 WALL BASE
- 2.10 INTEGRAL COVE BASE
- 2.11 STAIR TREADS, RISERS AND STRINGERS
- 2.12 MOULDING
- 2.13 ADHESIVES
- 2.14 SURFACE PREPARATION MATERIALS
- 2.15 POLISH/FINISH
- 2.16 CAULKING AND SEALANTS
- 2.17 MANUFACTURER'S COLOR, PATTERN AND TEXTURE

PART 3 EXECUTION

- 3.1 EXAMINATION
- 3.2 SURFACE PREPARATION
- 3.3 MOISTURE, ALKALINITY AND BOND TESTS
- 3.4 PLACING VINYL COMPOSITION, LINOLEUM AND SOLID VINYL TILES
- 3.5 PLACING SHEET VINYL FLOORING
- 3.6 PLACING SHEET LINOLEUM FLOORING
- 3.7 PLACING RUBBER TILE
- 3.8 PLACING RUBBER SHEET FLOORING
- 3.9 PLACING CORK
- 3.10 PLACING FEATURE STRIPS
- 3.11 PLACING MOULDING
- 3.12 PLACING WALL BASE
- 3.13 PLACING STAIR TREADS, RISERS, AND STRINGERS
- 3.14 PLACING INTEGRAL COVED BASE
- 3.15 CLEANING
- 3.16 PROTECTION

-- End of Section Table of Contents --

USACE / NAVFAC / AFCEC / NASA UFGS-09 65 00 (August 2010)
Change 1 - 02/13

Preparing Activity: USACE Superseding
UFGS-09 65 00 (February 2009)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated July 2015

SECTION 09 65 00

RESILIENT FLOORING
08/10

NOTE: This guide specification covers the requirements for resilient floor coverings, base materials, and accessory items.

Adhere to UFC 1-300-02 Unified Facilities Guide Specifications (UFGS) Format Standard when editing this guide specification or preparing new project specification sections. Edit this guide specification for project specific requirements by adding, deleting, or revising text. For bracketed items, choose applicable items(s) or insert appropriate information.

Remove information and requirements not required in respective project, whether or not brackets are present.

Comments, suggestions and recommended changes for this guide specification are welcome and should be submitted as a Criteria Change Request (CCR).

PART 1 GENERAL

NOTE: Resilient flooring may be used over wood subfloor provided that the subfloor underside is well ventilated and the installation conforms to the manufacturer's recommendations. Note that not all products are recommended for installation over panel type underlayment.

Flooring such as nonslip tile is not included in this specification; appropriate wording must be added when it is required.

Show location of resilient flooring, including types, on the drawings.

1.1 REFERENCES

NOTE: This paragraph is used to list the publications cited in the text of the guide specification. The publications are referred to in the text by basic designation only and listed in this paragraph by organization, designation, date, and title.

Use the Reference Wizard's Check Reference feature when you add a RID outside of the Section's Reference Article to automatically place the reference in the Reference Article. Also use the Reference Wizard's Check Reference feature to update the issue dates.

References not used in the text will automatically be deleted from this section of the project specification when you choose to reconcile references in the publish print process.

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

ASTM INTERNATIONAL (ASTM)

ASTM D4078	(2002; R 2008) Water Emulsion Floor Polish
ASTM D5603	(2001; R 2008) Rubber Compounding Materials - Recycled Vulcanizate Particulate Rubber
ASTM E2129	(2010) Standard Practice for Data Collection for Sustainability Assessment of Building Products
ASTM E648	(2014c) Standard Test Method for Critical Radiant Flux of Floor-Covering Systems Using a Radiant Heat Energy Source
ASTM F1066	(2004; R 2014; E 2014) Standard Specification for Vinyl Composition Floor Tile
ASTM F1303	(2004; R 2014) Sheet Vinyl Floor Covering with Backing
ASTM F1344	(2015) Rubber Floor Tile
ASTM F1482	(2004; E 2009; R 2009) Installation and Preparation of Panel Type Underlayments to Receive Resilient Flooring
ASTM F1700	(2013a) Solid Vinyl Floor Tile

ASTM F1859	(2014) Rubber Sheet Floor Covering Without Backing
ASTM F1860	(2014) Rubber Sheet Floor Covering With Backing
ASTM F1861	(2008; E 2012; R 2012) Resilient Wall Base
ASTM F1869	(2011) Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride
ASTM F1913	(2004; R 2014) Vinyl Sheet Floor Covering Without Backing
ASTM F2034	(2008; R 2013) Sheet Linoleum Floor Covering
ASTM F2169	(2014) Resilient Stair Treads
ASTM F2170	(2011) Determining Relative Humidity in Concrete Floor Slabs in situ Probes
ASTM F2195	(2013) Linoleum Floor Tile
ASTM F710	(2011) Standard Practice for Preparing Concrete Floors to Receive Resilient Flooring

GREEN SEAL (GS)

GS-36	(2011) Commercial Adhesives
-------	-----------------------------

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION (ISO)

ISO 3813	(2004) Resilient Floor Coverings - Cork Floor Tiles
----------	---

NATIONAL FIRE PROTECTION ASSOCIATION (NFPA)

NFPA 253	(2011) Standard Method of Test for Critical Radiant Flux of Floor Covering Systems Using a Radiant Heat Energy Source
----------	---

SOUTH COAST AIR QUALITY MANAGEMENT DISTRICT (SCAQMD)

SCAQMD Rule 1168	(1989; R 2005) Adhesive and Sealant Applications
------------------	--

U.S. GREEN BUILDING COUNCIL (USGBC)

LEED BD+C	(2009; R 2010) Leadership in Energy and Environmental Design(tm) Building Design and Construction (LEED-NC)
-----------	---

1.2 SYSTEM DESCRIPTION

1.2.1 Environmental Data

[Submit Table 1 of ASTM E2129 for the following products: [____].]

1.2.2 Fire Resistance Requirements

NOTE: Choice of critical radiant flux level as it applies to building type and area of application will be made in accordance with the latest edition of UFC 3-600-01, UFC 1-200-01 and NFPA 101. Wherever the use of Class II (0.22) watts finish is required, Class I (0.45) watts will be permitted.

Provide a critical radiant flux of not less than [0.45 watts per square centimeter (Class 1)] [0.22 watts per square centimeter (Class 2)] for flooring in corridors and exits when tested in accordance with ASTM E648 or NFPA 253.

1.2.3 Other Submittal Requirements

NOTE: Drawings are required for projects with floor patterns.

The following shall be submitted in accordance with LEED BD+C:

- a. documentation indicating percentage of post-industrial and post-consumer recycled content per unit of product. Indicate relative dollar value of recycled content products to total dollar value of products included in project.
- b. documentation indicating distance between manufacturing facility and the project site. Indicate distance of raw material origin from the project site. Indicate relative dollar value of local/regional materials to total dollar value of products included in project.
- c. documentation indicating type of biobased material in product and biobased content. Indicate relative dollar value of biobased content products to total dollar value of products included in project.

1.3 SUSTAINABILITY REPORTING

NOTE: The bracketed items are representative of LEED material documentation and requirements that may apply to this project. These items should be edited to reflect the project requirements.

Materials in this technical specification may contribute towards contract compliance with sustainability requirements. See Section 01 33 29 SUSTAINABILITY REPORTING for project LEED BD+C [local/regional materials,] [low-emitting materials,] [recycled content,] [____] [and] [rapidly renewable materials] and LEED documentation requirements.

1.4 SUBMITTALS

NOTE: Review submittal description (SD) definitions in Section 01 33 00 SUBMITTAL PROCEDURES and edit the following list to reflect only the submittals required for the project.

The Guide Specification technical editors have designated those items that require Government approval, due to their complexity or criticality, with a "G." Generally, other submittal items can be reviewed by the Contractor's Quality Control System. Only add a "G" to an item, if the submittal is sufficiently important or complex in context of the project.

For submittals requiring Government approval on Army projects, a code of up to three characters within the submittal tags may be used following the "G" designation to indicate the approving authority. Codes for Army projects using the Resident Management System (RMS) are: "AE" for Architect-Engineer; "DO" for District Office (Engineering Division or other organization in the District Office); "AO" for Area Office; "RO" for Resident Office; and "PO" for Project Office. Codes following the "G" typically are not used for Navy, Air Force, and NASA projects.

An "S" following a submittal item indicates that the submittal is required for the Sustainability Notebook to fulfill federally mandated sustainable requirements in accordance with Section 01 33 29 SUSTAINABILITY REPORTING.

Choose the first bracketed item for Navy, Air Force and NASA projects, or choose the second bracketed item for Army projects.

Government approval is required for submittals with a "G" designation; submittals not having a "G" designation are for [Contractor Quality Control approval.] [information only. When used, a designation following the "G" designation identifies the office that will review the submittal for the Government.] Submittals with an "S" are for inclusion in the Sustainability Notebook, in conformance to Section 01 33 29 SUSTAINABILITY REPORTING. Submit the following in accordance with Section 01 33 00 SUBMITTAL PROCEDURES:

SD-02 Shop Drawings

Resilient Flooring and Accessories; G[, [_____]]

SD-03 Product Data

Resilient Flooring and Accessories; G[, [_____]]
Adhesives; (LEED BD+C)

Vinyl Composition Tile
 Sheet Vinyl Flooring
 Rubber Tile
 Rubber Sheet Flooring
 Solid Vinyl Tile
 Cement-Fiber Board
 Wall Base
 Stair Treads, Risers and Stringers
 [Local/Regional Materials]
 [Environmental Data]
 [Sheet Linoleum]
 Linoleum Tile
 Cork

SD-04 Samples

Resilient Flooring and Accessories; G[, [_____]]

SD-06 Test Reports

Moisture, Alkalinity and Bond Tests; G[, [_____]]

SD-08 Manufacturer's Instructions

Surface Preparation; G[, [_____]]
 Installation; G[, [_____]]

SD-10 Operation and Maintenance Data

Resilient Flooring and Accessories; G[, [_____]]

SD-11 Closeout Submittals

LEED Documentation

1.5 DELIVERY, STORAGE, AND HANDLING

**NOTE: Materials which are woven, fibrous, or porous
 in nature have a high capacity to adsorb VOC
 emissions; for instance, acoustical ceilings,
 carpet, textiles, and unprimed gypsum wall board.
 If specifying porous materials include bracketed
 text and indicate materials to be protected.**

Deliver materials to the building site in original unopened containers
 bearing the manufacturer's name, style name, pattern color name and number,
 production run, project identification, and handling instructions. Store
 materials in a clean, dry, secure, and well-ventilated area free from
 strong contaminant sources and residues with ambient air temperature
 maintained above 20 degrees C 68 degrees F and below 30 degrees C 85
 degrees F, stacked according to manufacturer's recommendations. Remove
 resilient flooring products from packaging to allow ventilation prior to
 installation. Protect materials from the direct flow of heat from hot-air
 registers, radiators and other heating fixtures and appliances. Observe
 ventilation and safety procedures specified in the MSDS. Do not store
 rubber surface products with materials that have a high capacity to adsorb
 volatile organic compound (VOC) emissions, including [_____]. Do not store

exposed rubber surface materials in occupied spaces. [Do not store [_____] near materials that may offgas or emit harmful fumes, such as kerosene heaters, fresh paint, or adhesives.]

1.6 ENVIRONMENTAL REQUIREMENTS

Maintain areas to receive resilient flooring at a temperature above 20 degrees C 68 degrees F and below 30 degrees C 85 degrees F for 3 days before application, during application and 2 days after application, unless otherwise directed by the flooring manufacturer for the flooring being installed. Maintain a minimum temperature of 13 degrees C 55 degrees F thereafter. Provide adequate ventilation to remove moisture from area and to comply with regulations limiting concentrations of hazardous vapors.

1.7 SCHEDULING

Schedule resilient flooring application after the completion of other work which would damage the finished surface of the flooring.

1.8 WARRANTY

Provide manufacturer's standard performance guarantees or warranties that extend beyond a one year period.

1.9 EXTRA MATERIALS

NOTE: To ensure matching flooring that may become damaged and require spot replacement, a supply of extra flooring of same types, colors and dye lot is recommended. Coordinate requirement for extra stock with customer; warehousing may not be available.

Provide extra flooring material of each color and pattern at the rate of [[_____] [5] tiles for each 1000 tiles] [and] [[_____] [0.5] square m [5] square feet for each 92 square m 1000 square feet of sheet flooring] installed. Provide extra wall base material composed of 6 m 20 linear feet of each type, color and pattern. Package all extra materials in original properly marked containers bearing the manufacturer's name, brand name, pattern color name and number, production run, and handling instructions. Provide extra materials from the same lot as those installed. Leave extra stock at the site in location assigned by Contracting Officer.

PART 2 PRODUCTS

NOTE: Appropriate flooring material should be determined by:
 -Amount and type (foot, cart, wheelchair, etc.) of traffic
 -Abrasive-ness of local soil conditions
 -Exposure to water, chemicals, grease, and burns
 -Exposure to in-use damage (cuts, tears, gouges)
 -Exposure to direct sunlight (fading potential)
 -Anticipated type of and frequency of maintenance
 -Cost of maintenance
 -Appearance expectations
Verify proposed use of flooring with manufacturer's

recommendations.

Sheet flooring should be considered for areas such as health care facilities due to the reduced amount of seams. Seam welded sheet flooring without backing provides a monolithic floor impervious to moisture penetration.

Specify special adhesive for resilient flooring installed on floors with radiant heating, wet areas and areas with heavy rolling loads.

If more than one type of resilient flooring is required, a separate paragraph for each type will be used. Each type will be designated with a letter or number symbol. Use the same symbols to key flooring to locations on the drawings and in Section 09 06 90 COLOR SCHEDULE. Delete reference to type symbol if not used.

2.1 VINYL COMPOSITION TILE [TYPE [A][_____]]

NOTE: When vinyl composition tile is used, 3.2 mm 1/8 inch thick should be utilized in high traffic commercial type installations.

Solid color tiles are tiles with uniform color throughout. These are recommended for use as an accent only in small quantities and not as the floor field color. These tiles do not hide soiling well and show scratches easily.

Through pattern tiles are tiles with patterning distributed through the entire thickness.

Conform to ASTM F1066 [Class 1, (solid color tile),] [Class 2, (through pattern tile),] Composition 1, asbestos-free, [300] [_____] mm [12] [_____] inch square and [2.4] [3.2] mm [3/32] [1/8] inch thick. Provide color and pattern uniformly distributed throughout the thickness of the tile. Tile shall contain a minimum of [90] [100] [_____] percent recycled material.

2.2 SHEET VINYL FLOORING [TYPE [A][_____]]

NOTE: Not all sheet vinyl flooring is available with chemically bonded and/or heat welded seams. Research available products.

Conform to [ASTM F1303, Type I, Grade 1, [Class A-non-asbestos formulated fibrous backing] [or] [Class B-nonfoamed plastic backing] (minimum wear layer thickness 0.5 mm 0.020 inch and minimum overall thickness 2 mm 0.080 inch) and a minimum [1800 mm 6 feet] [3660 mm 12 feet] wide.] [ASTM F1303, Type II, Grade 1, without backing (minimum wear layer thickness 2 mm 0.080 inch and minimum overall thickness 2 mm 0.080 inch), and a minimum 1800 mm 6 feet wide. Extend color and pattern through the total thickness of the

material.] [ASTM F1303, Type II, Grade 1, [Class A non-asbestos formulated fibrous backing] [or] [Class B nonfoamed plastic backing] (minimum wear layer thickness 1.27 mm 0.050 inch and minimum overall thickness 2 mm 0.080 inch) and a minimum 1800 mm 6 feet wide. Extend color and pattern throughout the thickness of the wear layer.] [ASTM F1913, (minimum wear layer thickness 1.9 mm 0.075 inch and minimum overall thickness 1.9 mm 0.075 inch) and a minimum 1800 mm 6 feet wide. Extend color and pattern through the total thickness of the material.] As required, provide welding rods as recommended by the manufacturer for heat welding of joints.

2.3 RUBBER TILE [TYPE [A][_____]]

NOTE: Rubber flooring provides slip resistance not usually found with other type floor tiles. Consider for areas such as stairwell landings and ramps. Rubber flooring has a cushioning quality that reduces leg weariness and fatigue.

Some rubber flooring is not resistant to oil and grease and can perform poorly against certain reagents and stain spills. Determine project needs, research available product and add verbiage to paragraph if rubber flooring needs to be resistant to oil and grease and perform against certain reagents and stain spills.

Research available sizes. Manufacturer's sizes vary and not all manufacturers offer all sizes.

Ingredients in rubber flooring may include either natural rubber or synthetic materials. Natural rubber is a renewable raw material that is extracted from the sap of the tropical rubber plant without harming the plant. Typically, no waxes are required to maintain rubber floors.

Conform to ASTM F1344 [Class 1 homogeneous] [Class 2 layered], [Type A (solid color)] [Type B (through mottled)], [300] [450] [600] [900] [_____] mm [12] [18] [24] [36] [_____] inch square. Provide [smooth] [_____] [raised [round] [square] [diamond] surface studs with chamfered edges. Provide [high] [low]] stud profile. Provide [3.2] [_____] mm [0.125] [_____] inch overall thickness. [With Vulcanizate Particulate Rubber, use recycled tire treads in accordance with ASTM D5603, fine mesh size particulate, [Grade 1, 2, or 3] [Grade 4] [Grade 5] [Grade 6]].

2.4 RUBBER SHEET FLOORING [TYPE [A] [_____]]

NOTE: Rubber sheet flooring provides slip resistance not usually found with other type floor tiles. Consider for areas such as stairwell landings and ramps. Rubber flooring has a cushioning quality that reduces leg weariness and fatigue.

Some rubber flooring is not resistant to oil and grease and can perform poorly against certain

reagents and stain spills. Determine project needs, research available product and add verbiage to paragraph if rubber flooring needs to be resistant to oil and grease and perform against certain reagents and stain spills.

The following thicknesses of rubber flooring are recommended for the traffic type shown: 2.0 mm 0.080 inch thickness - low traffic; 2.5 mm 0.100 inch thickness - medium traffic; 3 mm 0.118 inch thickness or greater - heavy traffic.

Research available widths. Manufacturer's widths vary and not all manufacturers offer all sizes.

Conform to [ASTM F1859 (flooring without backing), [Type I homogeneous] [Type II layered]] [or] [ASTM F1860 (flooring with backing), [Type I homogeneous] [Type II layered]], [minimum] [1 m 36 inch] [_____] wide. Provide [smooth] [embossed] [_____] surface. Provide [2] [2.5] [3] [_____] mm [0.080] [0.100] [0.118] [_____] inch overall thickness.[With Vulcanizate Particulate Rubber, use recycled tire treads in accordance with ASTM D5603, fine mesh size particulate, [Grade 1, 2, or 3] [Grade 4] [Grade 5] [Grade 6].]

2.5 SOLID VINYL TILE [TYPE [A][_____]]

NOTE: The product Luxury Vinyl Tile is a Class III tile.

The product Luxury Vinyl Tile (referenced as Printed Film Vinyl Tile in ASTM F1700) is a Class III tile.

Conform to ASTM F1700 [Class I monolithic (minimum wear layer thickness 3 mm 0.125 inch and minimum overall thickness 3 mm 0.125 inch) [Class III printed film minimum wear layer thickness 0.50 mm 0.020 inch and minimum overall thickness 3 mm 0.125 inch], Type [A (smooth)] [B (embossed)]. Provide [300] [400] [450] [600] [900] [_____] mm [12] [16] [18] [24] [36] [_____] inch square tile.

2.6 SHEET LINOLEUM [TYPE [A][_____]]

NOTE: The 2002 Farm Bill - Section 9002, Federal Procurement of Biobased Products, requires each Federal Agency to develop a procurement program which will ensure that items composed of biobased products will be purchased to the maximum extent practicable and which is consistent with applicable provisions of Federal procurement law. Biobased materials like linoleum shall have preference over inert or non-recycled alternatives.

Conform to ASTM F2034 and consist of a homogeneous layer of a mixture of linoleum cement (binder in linoleum consisting of a mixture of linseed oil, pine rosin, fossil, or other resins or rosins, or an equivalent oxidized

oleoresinous binder), cork and/or wood flour, mineral fillers, and pigments bonded to a jute backing. Provide a minimum 1800 mm 6 feet wide and overall thickness not less than [2.0 mm 0.080 inch] [2.5 mm 0.100 inch] [3.2 mm 0.125 inch] for linoleum. As required, provide welding rods as recommended by the manufacturer for heat welding of joints.

2.7 LINOLEUM TILE [TYPE [A][____]]

Conform to ASTM F2195 and consist of a homogeneous layer of a mixture of linoleum cement (binder in linoleum consisting of a mixture of linseed oil, pine rosin, fossil, or other resins or rosins, or an equivalent oxidized oleoresinous binder), cork and/or wood flour, mineral fillers, and pigments bonded to a [polyester] [____] backing. Provide square tiles a minimum [450 mm 18 inch] [____] square and overall thickness [2.0 mm 0.08 inch] [____] minimum for linoleum tile.

2.8 CORK

NOTE: Cork granules used for cork flooring and linoleum are by-products from bottle-cork manufacturing. Some cork floors use synthetic binders in the manufacturing process and synthetic finishes to provide more durable walking surfaces. Typically available only in tile form, cork usually provides better sound absorption characteristics than most vinyl flooring but is less durable than commercial vinyl and rubber flooring.

Conform to ISO 3813, and be [300] [____] mm [12] [____] inches square and [0.05] [____] m [3/16] [____] inches to [0.08] [____] m [5/16] [____] inches thick. [Provide cork-faced MDF tongue-and-groove planks with cork facing.] Do not use products made with urea-formaldehyde binder.

2.9 WALL BASE

NOTE: Job formed corners are recommended. The return on preformed corners is not always long enough to hold the piece in place and the corners can be knocked off during vacuuming and other cleaning operations.

Base is available in different lengths ranging from 1220 mm 4 feet pieces to 30480 mm 100 feet or 36576 mm 120 feet rolls. Availability and roll lengths vary dependent on manufacturer. Identify required length if it impacts design intent. Some manufacturers of Type TS (vulcanized thermoset rubber) base offer only 1220 mm 4 feet lengths and not roll goods.

Conform to ASTM F1861, [[Type TS (vulcanized thermoset rubber)] [or] [Type TP (thermoplastic rubber)]] [, or] [Type TV (thermoplastic vinyl)], [Style A (straight - installed with carpet)] [,] [and] [Style B (coved - installed with resilient flooring)] [,] [and] [Style C (butt toe cove installed with 3 mm 1/8 inch thick flooring)]. Provide [100] [150] mm [4]

[6] inch high and a minimum 3.175 mm 1/8 inch thick wall base. Provide [preformed] [job formed] corners in matching height, shape, and color. [With Vulcanizate Particulate Rubber, use recycled tire treads in accordance with ASTM D5603, fine mesh size particulate, [Grade 1, 2, or 3] [Grade 4] [Grade 5] [Grade 6].]

2.10 INTEGRAL COVE BASE

NOTE: Integral coves can be used in many situations in which sheet vinyl and linoleum flooring are used to enhance the sanitary capacity inherent in seamless construction.

Consider specifying corner protectors in high traffic areas and areas that may receive some abuse.

Corner protectors are preferred in naval installations.

Extend integral coved base for [[sheet vinyl] [and] [sheet linoleum] flooring up the wall [100] [150] mm [4] [6] inch]. Provide a [vinyl] [or] [rubber] [clear anodized aluminum], [square] [round] cap strip and vinyl, rubber, or wood fillet strip with a minimum radius of 19 mm 3/4 inch for integral coved bases [at perimeter and fixed vertical interruptions to flooring] [as shown]. Provide integral cove of the same material as flooring. [Provide inside and outside corner protectors of [[____]-colored anodized aluminum] [clear anodized aluminum] [or] [plastic] approved by flooring manufacturer.]

2.11 STAIR TREADS, RISERS AND STRINGERS

Conform to ASTM F2169, [[Type TS (vulcanized thermoset rubber)] [or] [Type TP (thermoplastic rubber)]] [or] [Type TV (thermoplastic vinyl)]. Conform to ASTM F2169 for surface of treads [Class 1 smooth] [[Class 2 raised [round] [square] [diamond] stud] [ribbed] pattern] [and have [Group 1 abrasive non-slip strip] [Group 2 strip for visually impaired of contrasting [____] color of [same] [abrasive] material]]. Provide [square] [or] [round] nosing. Provide either a one piece nosing/tread/riser or a two piece nosing/tread design with a matching coved riser.[With Vulcanizate Particulate Rubber, use recycled tire treads in accordance with ASTM D5603, fine mesh size particulate, [Grade 1, 2, or 3] [Grade 4] [Grade 5] [Grade 6].]

2.12 MOULDING

Provide tapered mouldings of [[vinyl] [or] [rubber]] [[____]-colored anodized aluminum] [clear anodized aluminum] and types as recommended by flooring manufacturer for both edges and transitions of flooring materials specified. Provide vertical lip on moulding of maximum 6 mm 1/4 inch. Provide bevel change in level between 6 and 13 mm 1/4 and 1/2 inch with a slope no greater than 1:2.

2.13 ADHESIVES

NOTE:

Adhesives may be a source of VOCs. Some styles of

plastic flooring are available in loose-laid design (puzzle pieces that are tapped together with a rubber mallet) that can be installed without adhesive.

Provide adhesives for flooring, base and accessories as recommended by the manufacturer and comply with local indoor air quality standards. [VOC content shall be less than [50 grams/L] [the current VOC content limits of [GS-36]] and [SCAQMD Rule 1168]].] Submit manufacturer's descriptive data, documentation stating physical characteristics, and mildew and germicidal characteristics.

2.14 SURFACE PREPARATION MATERIALS

NOTE: Panel type underlayments, such as plywood and hardboard, are specified in Section 06 10 00 ROUGH CARPENTRY. Coordinate underlayments requirements with the ROUGH CARPENTRY specifications.

Provide surface preparation materials, such as panel type underlayment, lining felt, and floor crack fillers as recommended by the flooring manufacturer for the subfloor conditions. Comply with ASTM F1482 for panel type underlayment products. Use one of the following substrates:

- [a. Particleboard: As specified in Section 06 10 00 ROUGH CARPENTRY.]
- [b. Fiberboard: As specified in Section 06 10 00 ROUGH CARPENTRY.]
- [c. Cork: As specified in Section 06 10 00 ROUGH CARPENTRY]
- [d. Cement-fiber board: Portland cement, sand, recycled cellulose[with a minimum of [5] [10] [_____] percent post-consumer recycled content, or [20] [40] [_____] percent post-industrial recycled content].]
- [e. Plywood: As specified in Section 06 10 00 ROUGH CARPENTRY.]
- [f. Concrete.]

2.15 POLISH/FINISH

Provide polish finish as recommended by the manufacturer and conform to ASTM D4078 for polish.

2.16 CAULKING AND SEALANTS

Provide caulking and sealants in accordance with Section 07 92 00 JOINT SEALANTS.

2.17 MANUFACTURER'S COLOR, PATTERN AND TEXTURE

NOTE: Editing of color reference sentence(s) shall be coordinated with the Government. Generally the Section 09 06 90 COLOR SCHEDULE or drawings are used when the project is designed by an Architect or Interior designer. Color shall be selected from

manufacturer's standard colors or identified in this specification only when the project has minimal finishes.

When the government directs that color be located in the drawings, a note will be added that states:
"Where color is shown as being specific to one manufacturer, an equivalent color by another manufacturer may be submitted for approval. Manufacturers and materials specified are not intended to limit the selection of equal colors from other manufacturers. The word "color" as used herein includes surface color and pattern."

When more than one type, pattern or color is specified identify location.

When a manufacturer's name, stock number, pattern, and color is specified for color, be certain that the product conforms to the specification, as edited.

NOTE: Drawings are required for projects with floor patterns.

Provide color, pattern and texture for resilient flooring and accessories [in accordance with Section 09 06 90 COLOR SCHEDULE] [as indicated on the drawings] [selected from manufacturer's standard colors] [[____]]. Color listed is not intended to limit the selection of equal colors from other manufacturers]. [Provide floor patterns as specified on the [drawings Sheet No. [____]] [____].] Provide flooring in any one continuous area or replacement of damaged flooring in continuous area from same production run with same shade and pattern. Submit scaled drawings indicating patterns (including location of patterns and colors) and dimensions. Submit manufacturer's descriptive data and [three] [____] samples of each indicated color and type of flooring, base, mouldings, and accessories sized a minimum 60 by 100 mm 2-1/2 by 4 inch. Submit Data Package 1 in accordance with Section 01 78 23 OPERATION AND MAINTENANCE DATA.

PART 3 EXECUTION

3.1 EXAMINATION

Examine and verify that site conditions are in agreement with the design package. Report all conditions that will prevent a proper installation. Do not take any corrective action without written permission from the Government. Work will proceed only when conditions have been corrected and accepted by the installer. Submit manufacturer's printed installation instructions for all flooring materials and accessories, including preparation of substrate, seaming techniques, and recommended adhesives.

3.2 SURFACE PREPARATION

Provide a smooth, true, level plane for surface preparation of the flooring, except where indicated as sloped. Floor to be flat to within 4.75 in 3048 mm 3/16 inch in 10 feet. Prepare subfloor in accordance with flooring manufacturer's recommended instructions. Prepare the surfaces of lightweight concrete slabs (as defined by the flooring manufacturer) as recommended by the flooring manufacturer. Comply with ASTM F710 for

concrete subfloor preparation. Floor fills or toppings may be required as recommended by the flooring manufacturer. Install underlayments, when required by the flooring manufacturer, in accordance with manufacturer's recommended printed installation instructions. Comply with ASTM F1482 for panel type underlayments. Before any work under this section is begun, correct all defects such as rough or scaling concrete, chalk and dust, cracks, low spots, high spots, and uneven surfaces. Repair all damaged portions of concrete slabs as recommended by the flooring manufacturer. Remove concrete curing and sealer compounds from the slabs, other than the type that does not adversely affect adhesion. Remove paint, varnish, oils, release agents, sealers, waxes, and adhesives, as required by the flooring product in accordance with manufacturer's printed installation instructions.

3.3 MOISTURE, ALKALINITY AND BOND TESTS

Determine the suitability of the concrete subfloor for receiving the resilient flooring with regard to moisture content and pH level by moisture and alkalinity tests. Conduct moisture testing in accordance with ASTM F1869 or ASTM F2170, unless otherwise recommended by the flooring manufacturer. Conduct alkalinity testing as recommended by the flooring manufacturer. Determine the compatibility of the resilient flooring adhesives to the concrete floors by a bond test in accordance with the flooring manufacturer's recommendations. Submit copy of test reports for moisture and alkalinity content of concrete slab, and bond test stating date of test, person conducting the test, and the area tested.

3.4 PLACING VINYL COMPOSITION, LINOLEUM AND SOLID VINYL TILES

Install tile flooring and accessories in accordance with manufacturer's printed installation instructions. Prepare and apply adhesives in accordance with manufacturer's directions. Keep tile lines and joints square, symmetrical, tight, and even. Keep each floor in true, level plane, except where slope is indicated. Vary edge width as necessary to maintain full-size tiles in the field, no edge tile to be less than one-half the field tile size, except where irregular shaped rooms make it impossible. Cut flooring to fit around all permanent fixtures, built-in furniture and cabinets, pipes, and outlets. Cut, fit, and scribe edge tile to walls and partitions after field flooring has been applied.

3.5 PLACING SHEET VINYL FLOORING

**NOTE: Determine if welded seams are necessary to
meet project requirements.**

Install sheet vinyl flooring and accessories in accordance with manufacturer's printed installation instructions. Prepare and apply adhesives in accordance with manufacturer's printed directions. Provide square, symmetrical, tight, and even flooring lines and joints. Keep each floor in true, level plane, except where slope is indicated. Cut flooring to fit around all permanent fixtures, built-in furniture and cabinets, pipes, and outlets. Lay out sheets to minimize waste. Cut, fit, and scribe flooring to walls and partitions after field flooring has been applied. [Provide [chemically bonded] [or] [heat welded] seams and edges [in rooms [____]] [shown on the drawings] in accordance with the manufacturer's written installation instructions. Finish joints flush, free from voids, recesses, and raised areas.] [Install flooring with an integral coved base.]

3.6 PLACING SHEET LINOLEUM FLOORING

**NOTE: Determine if welded seams are necessary to
meet project requirements.**

Install sheet linoleum flooring and accessories in accordance with manufacturer's printed installation instructions. Prepare and apply adhesives in accordance with manufacturer's printed directions. Provide square, symmetrical, tight, and even flooring lines and joints. Keep each floor in true, level plane, except where slope is indicated. Cut flooring to fit around all permanent fixtures, built-in furniture and cabinets, pipes, and outlets. Lay out sheets to minimize waste. Cut, fit, and scribe flooring to walls and partitions after field flooring has been applied. Cut seams by overlapping or underscribing as recommended by the manufacturer. [Provide heat welded seams [in rooms [_____]] [as shown on the drawings] in accordance with there manufacturer's written installation instructions.] Finish joints flush, free from voids, recesses, and raised areas. [Install flooring with an integral coved base.]

3.7 PLACING RUBBER TILE

Install rubber tile and accessories in accordance with manufacturer's printed installation instructions. Prepare and apply adhesives in accordance with manufacturer's printed directions. Provide square, symmetrical, tight, and even flooring lines and joints. Keep each floor in true, level plane, except where slope is indicated. Vary width of edge tiles as necessary to maintain full-size tiles, except where irregular-shaped rooms makes it impossible. Cut flooring to fit around, all permanent fixtures, built-in furniture and cabinets, pipes, and outlets. Cut, fit, and scribe flooring to walls and partitions after field flooring has been applied.

3.8 PLACING RUBBER SHEET FLOORING

Install rubber sheet flooring and accessories in accordance with manufacturer's printed installation instructions. Prepare and apply adhesives in accordance with manufacturer's printed directions. Provide square, symmetrical, tight, and even flooring lines and joints. Keep each floor in true, level plane, except where slope is indicated. Cut seams by overlapping or underscribing as recommended by the manufacturer. Lay out sheets to minimize waste. Cut flooring to fit around all permanent fixtures, built-in furniture and cabinets, pipes, and outlets. Cut, fit, and scribe flooring to walls and partitions after field flooring has been applied.

3.9 PLACING CORK

Cork [tile] [plank flooring] and accessories shall be installed in accordance with manufacturer's installation instructions. Adhesives shall be prepared and applied in accordance with manufacturer's directions. Flooring lines and joints shall be square, symmetrical, tight, and even. Keep each floor in true, level plane, except where slope is indicated. [Vary width of edge tiles as necessary to maintain full-size tiles in field, but no edge tile shall be less than one-half full size, except where irregular-shaped rooms makes it impossible.] Flooring shall be cut to, and fitted around, all permanent fixtures, built-in furniture and cabinets,

pipes, and outlets. Flooring shall be cut, fitted, and scribed to walls and partitions after field flooring has been applied.

3.10 PLACING FEATURE STRIPS

Install feature strips in accordance with manufacturer's printed installation instructions. Prepare and apply adhesives in accordance with manufacturer's printed directions.

3.11 PLACING MOULDING

Provide moulding where flooring termination is higher than the adjacent finished flooring and at transitions between different flooring materials. When required, locate moulding under door centerline. Moulding is not required at doorways where thresholds are provided. [Secure moulding with adhesive as recommended by the manufacturer. Prepare and apply adhesives in accordance with manufacturer's printed directions.] [Anchor aluminum moulding to floor surfaces as recommended by the manufacturer.]

3.12 PLACING WALL BASE

Install wall base in accordance with manufacturer's printed installation instructions. Prepare and apply adhesives in accordance with manufacturer's printed directions. Tighten base joints and make even with adjacent resilient flooring. Fill voids along the top edge of base at masonry walls with caulk. Roll entire vertical surface of base with hand roller, and press toe of base with a straight piece of wood to ensure proper alignment. Avoid excess adhesive in corners.

3.13 PLACING STAIR TREADS, RISERS, AND STRINGERS

NOTE: Installation of stringers can be labor intensive. Dependent on the project requirements consider other stringer finish alternatives, an example would be a painted stringer.

Secure and install stair treads, risers, and stringers in accordance with manufacturer's printed installation instructions. Cover the surface of treads and risers[the full width of the stairs][within 150 mm6 inch to the stair edges]. Provide equal length pieces butted together to cover the treads and risers for stairs wider than manufacturer's standard lengths. [Provide stringer angles on both the wall and banister sides of the stairs, and landing trim.]

3.14 PLACING INTEGRAL COVED BASE

Install integral cove base in accordance with manufacturer's printed installation instructions. Prepare and apply adhesives in accordance with manufacturer's printed directions. Shape integral coved base by extending the flooring material [100] [150] [_____] mm [4] [6] [_____] inch onto the wall surface. Support cove by a filler. Provide a cap strip at the top of the base. Fill voids along the top edge of base at masonry walls with caulk.

3.15 CLEANING

NOTE: Some activities prefer no-wax maintenance;
others prefer waxing. Pre-waxed flooring and
flooring that does not require wax need not be waxed
after installation if properly protected.
Coordinate any requirements for application of
polish/floor finish with the end user. Modify
paragraph accordingly.

Immediately upon completion of installation of flooring in a room or an area, dry/clean the flooring and adjacent surfaces to remove all surplus adhesive. Clean flooring as recommended in accordance with manufacturer's printed maintenance instructions and within the recommended time frame. As required by the manufacturer, apply the recommended number of coats and type of polish and/or finish in accordance with manufacturer's written instructions.

3.16 PROTECTION

From the time of installation until acceptance, protect flooring from damage as recommended by the flooring manufacturer. Remove and replace flooring which becomes damaged, loose, broken, or curled and wall base which is not tight to wall or securely adhered.

-- End of Section --