
USACE / NAVFAC / AFCEA UFGS-07110A (November 2004)

Preparing Activity: USACE Superseding
UFGS-07110A (February 2004)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated 22 December 2004

Latest change indicated by CHG tags

SECTION TABLE OF CONTENTS

DIVISION 07 - THERMAL AND MOISTURE PROTECTION

SECTION 07110A

BITUMINOUS DAMPPROOFING

11/04

PART 1 GENERAL

- 1.1 REFERENCES
- 1.2 SUBMITTALS
- 1.3 QUALIFICATIONS
- 1.4 DELIVERY, STORAGE AND HANDLING

PART 2 PRODUCTS

- 2.1 EMULSION-BASED ASPHALT DAMPPROOFING
 - 2.1.1 Fibered Emulsion-Based Asphalt
 - 2.1.2 Non-Fibered Emulsion-Based Asphalt
- 2.2 SOLVENT-BASED ASPHALT DAMPPROOFING
 - 2.2.1 Asphaltic Primer
 - 2.2.2 Fibered Asphalt

PART 3 EXECUTION

- 3.1 SURFACE PREPARATION
 - 3.1.1 Protection of Surrounding Areas
 - 3.1.2 Masonry Surfaces
 - 3.1.3 Concrete Surfaces
 - 3.1.4 Metal Surfaces
- 3.2 APPLICATION OF BITUMINOUS DAMPPROOFING
 - 3.2.1 Emulsion-Based Asphalt
 - 3.2.2 Solvent-Based Asphalt
- 3.3 CLEAN-UP
- 3.4 PROTECTION

-- End of Section Table of Contents --

USACE / NAVFAC / AFCESA UFGS-07110A (November 2004)

Preparing Activity: USACE Superseding
UFGS-07110A (February 2004)

UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated 22 December 2004

Latest change indicated by CHG tags

SECTION 07110A

BITUMINOUS DAMPPROOFING 11/04

NOTE: This guide specification covers the requirements for bituminous dampproofing for above-grade use only to resist passage of moisture/water in the absence of hydrostatic pressure.

Comments and suggestions on this guide specification are welcome and should be directed to the technical proponent of the specification. A listing of technical proponents, including their organization designation and telephone number, is on the Internet.

Recommended changes to a UFGS should be submitted as a Criteria Change Request (CCR).

Use of electronic communication is encouraged.

Brackets are used in the text to indicate designer choices or locations where text must be supplied by the designer.

PART 1 GENERAL

1.1 REFERENCES

NOTE: Issue (date) of references included in project specifications need not be more current than provided by the latest guide specification. Use of SpecsIntact automated reference checking is recommended for projects based on older guide specifications.

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

ASTM INTERNATIONAL (ASTM)

ASTM D 1187	(1997; R 2002e1) Asphalt-Base Emulsions for Use as Protective Coatings for Metal
ASTM D 1227	(1995; R 2000) Emulsified Asphalt Used as a Protective Coating for Roofing
ASTM D 41	(1994; R 2000e1) Asphalt Primer Used in Roofing, Dampproofing, and Waterproofing
ASTM D 4479	(2000) Asphalt Roof Coatings - Asbestos Free

1.2 SUBMITTALS

NOTE: Submittals must be limited to those necessary for adequate quality control. The importance of an item in the project should be one of the primary factors in determining if a submittal for the item should be required.

A "G" following a submittal item indicates that the submittal requires Government approval. Some submittals are already marked with a "G". Only delete an existing "G" if the submittal item is not complex and can be reviewed through the Contractor's Quality Control system. Only add a "G" if the submittal is sufficiently important or complex in context of the project.

For submittals requiring Government approval on Army projects, a code of up to three characters within the submittal tags may be used following the "G" designation to indicate the approving authority. Codes for Army projects using the Resident Management System (RMS) are: "AE" for Architect-Engineer; "DO" for District Office (Engineering Division or other organization in the District Office); "AO" for Area Office; "RO" for Resident Office; and "PO" for Project Office. Codes following the "G" typically are not used for Navy projects.

Submittal items not designated with a "G" are considered as being for information only for Army projects and for Contractor Quality Control approval for Navy projects.

Government approval is required for submittals with a "G" designation; submittals not having a "G" designation are for [Contractor Quality Control approval.] [information only. When used, a designation following the "G" designation identifies the office that will review the submittal for the Government.] The following shall be submitted in accordance with Section 01330 SUBMITTAL PROCEDURES:

SD-07 Certificates

Materials

Certificates attesting that the materials meet the requirements specified.

1.3 QUALIFICATIONS

Work shall be performed by skilled laborers thoroughly experienced in the type of bituminous dampproofing work specified to meet the requirements of the contract.

1.4 DELIVERY, STORAGE AND HANDLING

Dampproofing materials shall be delivered to the project site in the original sealed containers bearing the name of manufacturer, contents and brand name, and stored in a weathertight enclosure to prevent moisture damage and absorption. Dampproofing materials shall be protected from freezing. Asphalt shall be stored off the ground on pallets, and covered on top and all sides with breathable-type canvas tarpaulins. Plastic sheets cause condensation buildup; and therefore, shall not be used to cover dampproofing materials. Care shall be taken during storage to avoid separation or settlement of the emulsion components. Damaged or deteriorated materials shall be removed from the project site.

PART 2 PRODUCTS

2.1 EMULSION-BASED ASPHALT DAMPPROOFING

2.1.1 Fibered Emulsion-Based Asphalt

NOTE: Type II Class 1 or 2 fibered emulsion-based asphalt is typically used as a protective coating against dampness on interior surfaces above grade and exterior surfaces of concrete, metal and wood above or below grade. Type II Class 1 or 2 is also used as a vapor barrier when applied to interior surfaces.

Fibered emulsion-based asphalt dampproofing shall be cold-applied type conforming to ASTM D 1227 Type II Class 1 or 2, asbestos-free, manufactured of refined asphalt, emulsifiers and selected clay, fibrated with mineral fibers. For spray or brush application, emulsion shall contain a minimum of 59 percent solids by weight, 56 percent solids by volume. For trowel application, emulsion shall contain a minimum of 58 percent solids by weight, 55 percent solids by volume.

2.1.2 Non-Fibered Emulsion-Based Asphalt

NOTE: Non-fibered emulsion-based asphalt is typically used as a protective coating against dampness on interior surfaces of concrete, metal and wood above or below grade.

Non-fibered emulsion-based asphalt dampproofing shall be cold-applied type

conforming to ASTM D 1187 Type II or ASTM D 1227 Type III, manufactured of refined asphalt, emulsifiers and selected clay. Asphalt shall contain a minimum 58 percent solids by weight, 55 percent solids by volume.

2.2 SOLVENT-BASED ASPHALT DAMPPROOFING

2.2.1 Asphaltic Primer

Primer for cold-applied solvent-based asphalt dampproofing shall conform to ASTM D 41, asbestos-free, non-fibred, manufactured with highly ductile soft asphalts and selected hydrocarbons.

2.2.2 Fibered Asphalt

NOTE: Fibered solvent-based asphalt is typically used to dampproof masonry and concrete exterior surfaces below grade and interior surfaces above grade. Fibered asphalt is also used as a general protective coating for wood, steel and backup materials for masonry walls such as stone, brick and concrete.

Fibered solvent-based asphalt dampproofing shall be cold-applied type conforming to ASTM D 4479 Type I, asbestos-free, manufactured with selected asphalts, stabilizers, mineral spirits and fibred with mineral fibers. Solvent-based asphalt shall contain 72 percent solids by weight, 65 percent solids by volume.

PART 3 EXECUTION

3.1 SURFACE PREPARATION

Surfaces scheduled for bituminous dampproofing shall be prepared in accordance with dampproofing manufacturer's recommendations. Surface preparation shall be approved prior to dampproofing application.

3.1.1 Protection of Surrounding Areas

Before starting the dampproofing work, the surrounding areas and surfaces shall be protected from spillage and migration of asphalt onto other work. Drains and conductors shall be protected from clogging with asphalt.

3.1.2 Masonry Surfaces

Surfaces shall be free of oil, grease, dirt, laitance, loose material, frost, debris and other contaminants. Mortar joints shall be flush and free of extraneous mortar and chipped or broken masonry.

3.1.3 Concrete Surfaces

Surfaces shall be properly cured, free of form release agents, oil, grease, dirt, laitance, loose material, frost, debris and other contaminants. Form ties shall be cut flush with surface. Sharp protrusions and form match lines shall be removed. Holes, voids, spalled areas and cracks which can damage the dampproofing materials and impair performance shall be repaired. Rough surfaces shall be parged with a well-adhering coat of cement mortar.

3.1.4 Metal Surfaces

Metal surfaces shall be dry and be free of rust, scale, loose paint, oil, grease, dirt, frost and debris.

3.2 APPLICATION OF BITUMINOUS DAMPPROOFING

3.2.1 Emulsion-Based Asphalt

Emulsion-based asphalt dampproofing work shall not be performed in temperatures below 4 degrees C 40 degrees F. Emulsions shall have a smooth and uniform consistency at time of application. Dampproofing materials shall be applied in accordance with manufacturer's published instructions to produce a smooth uniform dry film of not less than 0.3 mm 12 mils thick without voids or defects. Dull or porous spots shall be recoated. Dampproofing materials shall seal tightly around pipes and other items projecting through dampproofing. Rates of application shall be as follows:

- a. Primer: 0.2 L/square meter 1/2 gallon per 100 square feet, cold-applied.
- b. Fibrated Dampproofing: 0.8 L/square meter 2 gallons per 100 square feet, cold-applied with spray, brush or trowel.
- c. Non-fibrated Dampproofing: 0.8 L/square meter 2 gallons per 100 square feet, cold-applied with spray, brush or trowel.

3.2.2 Solvent-Based Asphalt

Solvent-based asphalt dampproofing work shall not be performed in temperatures below 4 degrees C 40 degrees F. Dampproofing materials shall be applied in accordance with manufacturer's published instructions to produce a smooth uniform dry film not less than 0.3 mm 12 mils thick without voids or defects. Dull or porous spots shall be recoated. Dampproofing materials shall seal tightly around pipes and other items projecting through dampproofing. Rates of application shall be as follows:

- a. Primer: 0.4 L/square meter 1/2 gallon per 200 square feet, cold-applied.
- b. Dampproofing Coat: 0.8 L/square meter 2 gallons per 100 square feet, cold-applied with spray, brush or trowel.

3.3 CLEAN-UP

Surfaces of other work which are stained with dampproofing materials shall be cleaned with a cleaner recommended by dampproofing manufacturer.

3.4 PROTECTION

The completed dampproofing work shall be protected from damage during and after construction.

-- End of Section --